

This is a preview of "ISO 13357-1:2017". [Click here to purchase the full version from the ANSI store.](#)

Second edition
2017-05

Petroleum products — Determination of the filterability of lubricating oils —

Part 1: Procedure for oils in the presence of water

*Produits pétroliers — Détermination de la filtrabilité des huiles
lubrifiantes —*

Partie 1: Méthode pour les huiles en présence d'eau



Reference number
ISO 13357-1:2017(E)

© ISO 2017

This is a preview of "ISO 13357-1:2017". [Click here to purchase the full version from the ANSI store.](#)



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

This is a preview of "ISO 13357-1:2017". [Click here to purchase the full version from the ANSI store.](#)

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Principle	2
5 Reagents and materials	2
6 Apparatus	3
7 Samples and sampling	5
8 Preparation of apparatus	5
9 Procedure	6
10 Calculations	8
10.1 Stage I filterability.....	8
10.2 Stage II filterability.....	8
11 Expression of results	8
11.1 General.....	8
11.2 Assessment of validity.....	8
12 Precision	9
13 Test report	9
Annex A (informative) Suitable procedure for the addition of graduations to a measuring cylinder	10
Bibliography	12

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

The committee responsible for this document is ISO/TC 28, *Petroleum and related products: fuels and lubricants from natural or synthetic sources*.

This second edition cancels and replaces the first edition (ISO 13357-1:2002), of which it constitutes a minor revision including alternative membranes in order to enable the continued use of this document.

A list of all parts in the ISO 13357 series can be found on the ISO website.

This is a preview of "ISO 13357-1:2017". [Click here to purchase the full version from the ANSI store.](#)

Introduction

As the fluid in a hydraulic system acts as a lubricant to minimize wear of the components, it is important to reduce the concentrations of circulating hard contaminant particles. This is particularly necessary when the performance of the system depends on the maintenance of small clearances and orifices. Removal of these contaminants is effected by the use of filters. The ability of a hydraulic fluid to pass through fine filters, without plugging them, is called its "filterability". This document describes a laboratory test procedure for assessing the filterability of mineral oils which have been heat-soaked in the presence of water. Filterability so determined is not a physical characteristic of the oil, but represents an estimation of its behaviour in service.

This document describes two measurements, referred to as "stages". The Stage I determination is based on a comparison of the mean flow rate of a fluid through a test membrane with its initial flow rate. Oils having good Stage I filterability, but only a poor Stage II performance (see below), would be unlikely to give performance problems in use, unless extremely fine system filters are utilized.

The Stage II determination is based upon the ratio between the initial flow rate of fluid through the test membrane and the rate at the end of the test. It is considered that this part of the procedure is a more severe test, and is more sensitive to the presence of gels and fine silts in the oil. Silts and gels may be present in an oil when it is produced, or could be formed as an oil ages, especially when hot. An oil with good Stage II filterability would be unlikely to give filtration problems even in the most extreme conditions, and with fine (less than 5 μm) filtration present. It would thus be suitable for use in more critical hydraulic and lubrication systems.

The procedure has been evaluated with mineral oils up to ISO viscosity grade 100. There would appear to be no reason why it should not be used with oils of higher viscosity grade (ISO viscosity grade 220 is a practical maximum), but the data obtained could not be claimed to be completely in accordance with this method. Similarly, it should be possible to extend the test procedure to fluids other than mineral oils. However, some fluids, e.g. fire-resistant fluids, will not be compatible with the specified test membranes, and the test could only be used for comparison purposes even when suitable membranes, with similar pore size/pore density characteristics to those specified in this procedure, have been identified.