

This is a preview of "ISO 13438:2004". [Click here to purchase the full version from the ANSI store.](#)

First edition
2004-11-01

Geotextiles and geotextile-related products — Screening test method for determining the resistance to oxidation

Géotextiles et produits apparentés — Méthode de détermination de la résistance à l'oxydation



Reference number
ISO 13438:2004(E)

© ISO 2004

This is a preview of "ISO 13438:2004". [Click here to purchase the full version from the ANSI store.](#)

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

© ISO 2004

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

This is a preview of "ISO 13438:2004". [Click here to purchase the full version from the ANSI store.](#)

Contents

Page

Foreword	iv
Introduction	v
1 Scope.....	1
2 Normative references	1
3 Methods A1, A2, B1 and B2	1
3.1 Principle	1
3.2 Specimens	2
3.3 Apparatus	2
3.4 Conditioning	2
3.5 Test procedure	2
4 Methods C1 and C2.....	3
4.1 Principle	3
4.2 Apparatus and reagents	3
4.3 Test procedure	4
5 Determination of mechanical properties	5
6 Test report	6
Annex A (informative) Background information on oxidation processes and oxidation measurements.....	7
Bibliography	9

This is a preview of "ISO 13438:2004". [Click here to purchase the full version from the ANSI store.](#)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 13438 was prepared by the European Committee for Standardization (CEN) Technical Committee CEN/TC 189, *Geosynthetics* in collaboration with Technical Committee ISO/TC 221, *Geosynthetics*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This is a preview of "ISO 13438:2004". [Click here to purchase the full version from the ANSI store.](#)

Introduction

In many civil engineering applications geotextiles and geotextile-related products may come into contact with water or aqueous solutions present in the soil environment. At the same time, in specific parts of the construction, they may be exposed to oxygen, giving rise to oxidative degradation processes. These processes are usually very slow.

Polyolefin materials such as polypropylene (PP) and polyethylene (PE) are inherently more sensitive to oxidation than those based on polyethylene terephthalate (PET). This behaviour can be improved very effectively by the use of appropriate stabilizing additives.

It is the purpose of this international standard to provide a method for screening the resistance to oxidation of geotextiles and geotextile-related products in service up to 25 years. In order to achieve the sufficiently short exposure times needed for screening tests, it is necessary to accelerate the oxidative degradation process. This acceleration can be achieved either by raising the temperature or by increasing the concentration of the active reaction partner. Raising the temperature may lead to the oxidation rate being limited by oxygen diffusion, thus invalidating the acceleration. This applies particularly to materials with a low surface-to-volume ratio and less to nonwovens made from fine fibres. Two methods are therefore proposed.

Methods A1, A2, B1 and B2 use temperature alone as the accelerating factor.

Methods C1 and C2 operate at moderately high temperatures and at the same time the oxygen concentration is increased by using pure oxygen at high pressure.

Each test may be performed at a shorter duration for non-reinforcing materials (A1, B1, C1) or for a longer duration for reinforcing materials (A2, B2, C2).

NOTE This International Standard should be used with reference to ISO/TR 13434. For further information see Annex A.