Second edition 2008-12-15

Metallic materials — Charpy pendulum impact test —

Part 2: **Verification of testing machines**

Matériaux métalliques — Essai de flexion par choc sur éprouvette Charpy —

Partie 2: Vérification des machines d'essai (mouton-pendule)



Reference number ISO 148-2:2008(E)

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.



COPYRIGHT PROTECTED DOCUMENT

© ISO 2008

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents		Page
Forewordi		
Introduction		ν
1	Scope	1
2	Normative references	2
3 3.1 3.2 3.3	Terms and definitions Definitions pertaining to the machine Definitions pertaining to energy Definitions pertaining to test pieces	2 2
4	Symbols and abbreviated terms	4
5	Testing machine	6
6 6.1 6.2 6.3 6.4 6.5 6.6	Direct verification	6 6 7
7 7.1 7.2 7.3 7.4 7.5	Indirect verification by use of reference test pieces Reference test pieces used Absorbed energy levels Requirements for reference test pieces Limited direct verification Bias and repeatability	12 12 12 12
8	Frequency of verification	13
9 9.1 9.2 9.3	Verification report	14 14
10	Uncertainty	14
Annex	A (informative) Measurement uncertainty of the result of the indirect verification of a Charpy pendulum impact machine	
Annex	B (informative) Measurement uncertainty of the results of the direct verification of a Charpy pendulum impact testing machine	25
Annex	CC (informative) Direct method of verifying the geometric properties of pendulum impact testing machines using a jig	31
Biblio	graphy	38

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 148-2 was prepared by Technical Committee ISO/TC 164, *Mechanical testing of metals*, Subcommittee SC 4, *Toughness testing* — *Fracture* (*F*), *Pendulum* (*P*), *Tear* (*T*).

This second edition cancels and replaces the first edition (ISO 148-2:1998), which has been technically revised.

ISO 148 consists of the following parts, under the general title *Metallic materials* — *Charpy pendulum impact test*:

- Part 1: Test method
- Part 2: Verification of testing machines
- Part 3: Preparation and characterization of Charpy V-notch test pieces for indirect verification of pendulum impact machines

Introduction

The suitability of a pendulum impact testing machine for acceptance testing of metallic materials has usually been based on a calibration of its scale and verification of compliance with specified dimensions, such as the shape and spacing of the anvils supporting the specimen. The scale calibration is commonly verified by measuring the mass of the pendulum and its elevation at various scale readings. This procedure for evaluation of machines had the distinct advantage of requiring only measurements of quantities that could be traced to national standards. The objective nature of these traceable measurements minimized the necessity for arbitration regarding the suitability of the machines for material acceptance tests.

However, sometimes two machines that had been evaluated by the direct-verification procedures described above, and which met all dimensional requirements, were found to give significantly different impact values when testing test pieces of the same material. This difference was commercially important when values obtained using one machine met the material specification, while the values obtained using the other machine did not. To avoid such disagreements, some purchasers of materials added the requirement that all pendulum impact testing machines used for acceptance testing of material sold to them must be indirectly verified by testing reference test pieces supplied by them. A machine was considered acceptable only if the values obtained using the machine agreed, within specified limits, with the value furnished with the reference test pieces.