Fourth edition 2020-11

Petroleum and natural gas industries — Materials for use in H₂S-containing environments in oil and gas production —

Part 3:

Cracking-resistant CRAs (corrosion-resistant alloys) and other alloys

Industries du pétrole et du gaz naturel — Matériaux pour utilisation dans des environnements contenant de l'hydrogène sulfuré (H_2S) dans la production de pétrole et de gaz —

Partie 3: ARC (alliages résistants à la corrosion) et autres alliages résistants à la fissuration



Reference number ISO 15156-3:2020(E)

ISO 15156-3:2020(E)

This is a preview of "ISO 15156-3:2020". Click here to purchase the full version from the ANSI store.



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Email: copyright@iso.org Website: www.iso.org

Published in Switzerland

Con	tent	S	Page
Forew	ord		iv
Intro	luctio	n	vi
1	Scope	e	1
2	Norn	native references	2
3		ns and definitions	
4		bols and abbreviated terms	
5	Facto	ors affecting the cracking-resistance of CRAs and other alloys in H ₂ S-containing ronments	
6		ification and selection of CRAs and other alloys with respect to SSC, SCC, and C in H ₂ S-containing environments General Evaluation of materials properties	6 7
	6.3	 6.2.1 Hardness of parent metals 6.2.2 Cracking-resistance properties of welds 6.2.3 Cracking-resistance properties associated with other fabrication methods PREN 	7 8
7	Purcl 7.1 7.2	hasing information and marking Information that should be supplied for material purchasing Marking, labelling, and documentation	9
Annex		ormative) Environmental cracking-resistant CRAs and other alloys (including e A.1 — Guidance on the use of the materials selection tables)	11
Annex	B (no	ormative) Qualification of CRAs for H ₂ S-service by laboratory testing	57
Annex	C (inf	formative) Information that should be supplied for material purchasing	67
Annex	D (in	formative) Nominated sets of test conditions	69
		ny	

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 67, *Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries,* in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 12, *Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries,* in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This fourth edition cancels and replaces the third edition (ISO 15156-3:2015), which has been technically revised. The main changes compared to the previous edition are as follows:

- <u>Table A.27</u> UNS S17400 (17-4PHSS) has new limits. The use of the alloy at the annotated environmental conditions is now limited to applications where sustained stress is no more than 50 % of SMYS;
- Table A.32 new limits and annotations for UNS N09946 separate from UNS N09945;
- <u>Table A.41</u> inclusion of UNS R55400 (new a-b Ti alloy);
- Table A.3 UNS S20910 (Nitronic 50) note modifications;
- Tables A.22, A.23, A.26 through A.30, and A.33 temperature conversion corrections;
- Table A.23 new note for maximum design tensile stress for UNS J91540;
- Table A.32 newly added UNS N07718 (high strength Alloy 718, with two-step aging cycle, meeting API 6A CRA composition and a maximum hardness of 45 HRC) and UNS N09955 requirements and note letters designation changes on UNS N09925, N09935, N09945 and N09946;
- <u>Table A.40</u> title modification and note clarification;
- <u>Clause A.13</u> Cladding, overlays, and wear-resistant alloys modifications;
- <u>Table A.18</u> and <u>Table A.19</u> (Martensitic SS) remarks modifications;
- <u>Table A.24</u> Duplex SS Hot Isostatically Pressed (HIP) inclusion and remarks modification;

- the informative Annex D, "Materials chemical compositions and other information", has been removed due to copyright reasons;
- additions to the bibliography.

A list of all parts in the ISO 15156 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

The consequences of sudden failures of metallic oil and gas field components associated with their exposure to $\rm H_2S$ -containing production fluids led to the preparation of the first edition of NACE MR0175 which was published in 1975 by the National Association of Corrosion Engineers, now known as NACE International.

The original and subsequent editions of NACE MR0175 established limits of H_2S partial pressure above which precautions against sulfide stress cracking (SSC) were always considered necessary. They also provided guidance for the selection and specification of SSC-resistant materials when the H_2S thresholds were exceeded. In more recent editions, NACE MR0175 has also provided application limits for some corrosion-resistant alloys in terms of environmental composition and pH, temperature, and H_2S partial pressures.

In separate developments, the European Federation of Corrosion issued EFC Publication 16 in 1995 and EFC Publication 17 in 1996. These documents are generally complementary to those of NACE, though they differed in scope and detail.

In 2003, the publication of the ISO 15156 series and NACE MR0175/ISO 15156 was completed for the first time. These technically identical documents utilized the above sources to provide requirements and recommendations for materials qualification and selection for application in environments containing wet $\rm H_2S$ in oil and gas production systems. They are complemented by NACE TM0177 and NACE TM0284 test methods.

The revision of this document, i.e. ISO 15156, involves a consolidation of all changes agreed and published in the Technical Circular 1, ISO 15156-3:2015/Cir.1:2016, the Technical Circular 2, ISO 15156-3:2015/Cir.2:2018 and the Technical Circular 3, ISO 15156-3:2015/Cir.3:2019, published by the ISO 15156 series Maintenance Agency secretariat at DIN.

The changes were developed by, and approved by the ballot of, representative groups from within the oil and gas production industry. The great majority of these changes stem from issues raised by document users. A description of the process by which these changes were approved can be found at the ISO 15156 series maintenance website: www.iso.org/iso15156maintenance.

When found necessary by oil and gas production industry experts, future interim changes to this document will be processed in the same way and will lead to interim updates to this document in the form of Technical Corrigenda or Technical Circulars. Document users should be aware that such documents can exist and can impact the validity of the dated references in this document.

The ISO 15156 series Maintenance Agency at DIN was set up after approval by the ISO Technical Management Board given in document 34/2007. This document describes the makeup of the agency, which includes experts from NACE, EFC, and ISO/TC 67, and the process for approval of amendments. It is available from the ISO 15156 series maintenance website and from the ISO/TC 67 Secretariat. The website also provides access to related documents that provide more detail of the ISO 15156 series maintenance activities.