

This is a preview of "ISO 16866:2020". [Click here to purchase the full version from the ANSI store.](#)

First edition
2020-10

Metallic and other inorganic coatings — Simultaneous thickness and electrode potential determination of individual layers in multilayer nickel deposits (STEP test)

Revêtements métalliques et autres revêtements inorganiques — Détermination simultanée de l'épaisseur et du potentiel d'électrode de couches individuelles dans des dépôts de nickel multicouches (essai STEP)



Reference number
ISO 16866:2020(E)

© ISO 2020



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

This is a preview of "ISO 16866:2020". [Click here to purchase the full version from the ANSI store.](#)

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Test equipment	1
4.1 Construction of the measuring cell.....	1
4.2 Composition of the test solution.....	2
5 Requirements	3
6 Sampling	3
7 Factors influencing measurement accuracy	3
7.1 Electrolyte.....	3
7.2 Conditioning.....	3
7.3 Ni deposits.....	3
7.4 Surface cleanliness.....	3
7.5 Measurement area and contact pressure.....	3
7.6 Electrical contact.....	4
7.7 Complete dissolution.....	4
8 Procedure	4
8.1 General.....	4
8.2 Measurement.....	4
8.3 Evaluation.....	5
9 Measurement uncertainty	8
10 Test report	9
Annex A (informative) Precision data obtained by a round robin test	10
Bibliography	11

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by the European Committee for Standardization (CEN) (as EN 16866:2017) and was adopted, without modification, by Technical Committee ISO/TC 107, *Metallic and other inorganic coatings*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

This is a preview of "ISO 16866:2020". [Click here to purchase the full version from the ANSI store.](#)

Introduction

The abbreviated term "STEP" represents "Simultaneous Thickness and Electrode Potential determination".

The STEP test can be used to measure, in one single operating step, the parameters (thickness of the individual nickel layers and the potential differences among them) relevant for the course of corrosion in a multilayer nickel system. Provided suitable instruments are applied, it can also be used to document them.

The test is a modification of the well-known coulometric method for the measurement of the coating thickness. This method takes advantage of the fact that, following the anodic dissolution of a nickel coating, a potential jump takes place of which the magnitude can be measured against a reference electrode.

Although, nowadays, the STEP test has been incorporated into a number of company standards, particularly in the automobile industry, there are currently no uniform and generally acknowledged potential difference values available. At present, values between 80 mV and 150 mV are assumed for double nickel layers, with the semi-bright nickel layer always being nobler than the bright one.

Likewise, no obligatory numerical values are available, currently, regarding the potential difference between bright nickel layers and existing special nickel layers (e.g. in the case of micro-porous chromium plating). According to the current practical experience, the potential difference is larger than approximately 20 mV, with the bright nickel layer always having to be less noble than the special nickel layer.