

First edition
2015-12-15

Solid biofuels — Determination of mechanical durability of pellets and briquettes —

Part 1: Pellets

Biocombustibles solides — Détermination de la résistance mécanique des granulés et des briquettes —

Partie 1: Granulés



Reference number
ISO 17831-1:2015(E)

© ISO 2015



COPYRIGHT PROTECTED DOCUMENT

© ISO 2015, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

This is a preview of "ISO 17831-1:2015". Click here to purchase the full version from the ANSI store.

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Apparatus	1
6 Sample preparation	3
7 Procedure	3
7.1 Tumbling procedure.....	3
7.2 Sieving procedure.....	3
8 Calculation of the mechanical durability	4
9 Performance characteristics	4
9.1 General.....	4
9.2 Repeatability.....	4
9.3 Reproducibility.....	4
10 Test report	4
Annex A (informative) Example of pellets tester with two boxes	6
Bibliography	7

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 238, *Solid biofuels*.

ISO 17831 consists of the following parts under the general title *Solid Biofuels — Determination of mechanical durability of pellets and briquettes*:

- *Part 1: Pellets*
- *Part 2: Briquettes*

This is a preview of "ISO 17831-1:2015". [Click here to purchase the full version from the ANSI store.](#)

Introduction

Compressed solid biomass fuel is usually classified either as pellets or briquettes, of which pellets usually have a diameter below 25 mm while for briquettes the diameter is higher (see ISO 17225-1). To account for the different particle dimensions, it was necessary to define different test apparatuses for determination of durability for pellets and briquettes.