

This is a preview of "ISO 179-2:1997". Click here to purchase the full version from the ANSI store.

STANDARD

179-2

First edition  
1997-12-15

---

---

## Plastics — Determination of Charpy impact properties —

### Part 2: Instrumented impact test

*Plastiques — Détermination des caractéristiques au choc Charpy —  
Partie 2: Essai de choc instrumenté*

This material is reproduced from ISO documents under International Organization for Standardization (ISO) Copyright License number IHS/ICC/1996. Not for resale. No part of these ISO documents may be reproduced in any form, electronic retrieval system or otherwise, except as allowed in the copyright law of the country of use, or with the prior written consent of ISO (Case postale 56, 1211 Geneva 20, Switzerland, Fax +41 22 734 10 79), IHS or the ISO Licensor's members.



Reference number  
ISO 179-2:1997(E)

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 179-2 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 2, *Mechanical properties*.

ISO 179 consists of the following parts, under the general title *Plastics — Determination of Charpy impact properties*:

- *Part 1: Non-instrumented impact test*
- *Part 2: Instrumented impact test*

Annexes A to C of this part of ISO 179 are for information only.

© ISO 1997

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization  
Case postale 56 • CH-1211 Genève 20 • Switzerland  
Internet central@iso.ch  
X.400 c=ch; a=400net; p=iso; o=isocs; s=central

Printed in Switzerland

# Plastics — Determination of Charpy impact properties —

## Part 2: Instrumented impact test

### 1 Scope

**1.1** This part of ISO 179 specifies a method for determining Charpy impact properties of plastics from force-deflection diagrams. Different types of rod-shaped test specimen and test configuration, as well as test parameters depending on the type of material, the type of test specimen and the type of notch are defined in part 1 of ISO 179.

Dynamic effects such as load-cell/striker resonance, test specimen resonance and initial-contact/inertia peaks are described (see figure 1, curve b, and annex A).

**1.2** For the comparison between Charpy and Izod test methods, see ISO 179-1, clause 1.

ISO 179-1 is suitable for characterizing the impact behaviour by the impact strength only and for using apparatus whose potential energy is matched approximately to the particular energy to break to be measured (see ISO 13802, annex C). This part of ISO 179 is used if a force-deflection or force-time diagram is necessary for detailed characterization of the impact behaviour, and for developing automatic apparatus, i.e. avoiding the need, mentioned above, to match energy.

**1.3** For the range of materials which may be tested by this method, see ISO 179-1, clause 1.

**1.4** For the general comparability of test results, see ISO 179-1, clause 1.

**1.5** The method may not be used as a source of data for design calculations on components. However, the possible use of data is not the subject of this part of ISO 179. Any application of data obtained using this part of ISO 179 should be specified by a referring standard or agreed upon by the interested parties.

Information on the typical behaviour of materials can be obtained by testing at different temperatures, by varying the notch radius and/or specimen thickness and by testing specimens prepared under different conditions.

It is not the purpose of this part of ISO 179 to give an interpretation of the mechanism occurring at every point on the force-deflection diagram. These interpretations are a task for on-going scientific research.

**1.6** The test results are comparable only if the conditions of test specimen preparation, as well as the test conditions, are the same. Comprehensive evaluation of the reaction to impact stress requires that determinations be made as a function of deformation rate and temperature for different material variables such as crystallinity and moisture content. The impact behaviour of finished products cannot, therefore, be predicted directly from this test, but test specimens may be taken from finished products for testing by this method.

**1.7** Impact strengths determined by this method may replace those determined using ISO 179-1 if comparability has been established by previous tests.