



ISO 182-3

Third edition
2025-10

Plastics — Determination of the tendency of compounds and products based on vinyl chloride homopolymers and copolymers to evolve hydrogen chloride and any other acidic products at elevated temperatures —

Part 3: Conductometric method

Plastiques — Détermination de la tendance des compositions et produits à base d'homopolymères et de copolymères du chlorure de vinyle à dégager du chlorure d'hydrogène et éventuellement d'autres produits acides à températures élevées —

Partie 3: Méthode conductimétrique

This is a preview of ISO 182-3:2025. [Click here to purchase the full version from the ANSI store.](#)



COPYRIGHT PROTECTED DOCUMENT

© ISO 2025

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Principle	2
5 Reagents	2
6 Apparatus	2
7 Preparation of test samples	7
7.1 General.....	7
7.2 PVC plastisols.....	7
7.3 PVC pellets, extrudates, mouldings, thick sheet, etc.....	7
7.4 PVC film and sheet.....	7
7.5 PVC coatings.....	7
7.6 Cable and conductor insulation or sheathing.....	7
8 Number of tests	7
9 Temperatures for dehydrochlorination	7
10 Test procedure	8
10.1 Preparation of test portion.....	8
10.2 Preliminary operations.....	8
10.3 Special precautions when using dehydrochlorination cell A.....	8
10.4 Preparation of the measurement cell.....	8
10.5 Decomposition of the test portion.....	8
11 Expression of results	9
12 Test report	9
13 Precision	9
13.1 General.....	9
13.2 Repeatability.....	10
13.3 Reproducibility.....	10
13.4 Comparison with the pH-meter method (ISO 182-2).....	10
13.5 Factors affecting the stability time.....	10
13.6 Conclusions.....	12
Annex A (informative) Cleaning of the apparatus	13
Annex B (informative) Calculation of repeatability and reproducibility — Conductometric and pH-meter methods	14
Annex C (informative) Interlaboratory test	16
Bibliography	18

This is a preview of ISO 182-3:2025. [Click here to purchase the full version from the ANSI store.](#)

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 9, *Thermoplastic materials*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 249, *Plastics*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This third edition cancels and replaces the second edition (ISO 182-3:2023), of which it constitutes a minor revision.

The changes are as follows:

- the reference to ISO 182-4 in the Scope has been placed in a Note;
- the unit min has been added to m , r , and R in [Clause 13](#);
- the code for stability time in [Table 1](#) has been corrected to t_s ;
- the unit of t_s in [Table 2](#) has been corrected to min.

A list of all parts in the ISO 182 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.