



ISO 18553

Method for the assessment of the degree of pigment or carbon black dispersion in polyolefin pipes, fittings and compounds

Méthode d'estimation de la dispersion du pigment et du noir de carbone dans les tubes, raccords et compositions à base de polyoléfines

**Second edition
2025-03**



COPYRIGHT PROTECTED DOCUMENT

© ISO 2025

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

This is a preview of ISO 18553:2025. [Click here to purchase the full version from the ANSI store.](#)

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Apparatus	2
5.1 General.....	2
5.2 For the microtome procedure (see 6.1.2).....	2
5.3 For the compression procedure (see 6.1.3).....	2
6 Procedure	2
6.1 Test piece preparation.....	2
6.2 Microscopic examination.....	5
6.2.1 Examination for assessment of the grade of dispersion.....	5
6.2.2 Examination for rating of appearance.....	5
7 Expression of results	5
7.1 Grading of particle and agglomerate size.....	5
7.2 Rating of appearance.....	5
8 Test report	5
Annex A (normative) Grading tables for particles and agglomerates and for rating of appearance	7
Annex B (normative) Photomicrographs (reference pictures)	9
Annex C (informative) Grading of particles and agglomerates, and rating of appearance — Examples	14
Annex D (informative) Basic specification	16
Annex E (informative) Example of an agglomerate spread by compression procedure	17

This is a preview of ISO 18553:2025. [Click here to purchase the full version from the ANSI store.](#)

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 5, *General properties of pipes, fittings and valves of plastic materials and their accessories -- Test methods and basic specifications*.

This second edition cancels and replaces the first edition (ISO 18553:2002), which has been technically revised. It also incorporates the Amendment ISO 18553:2002/Amd. 1:2007.

The main changes are as follows:

- the microtome method for preparing test pieces has been made the primary method, but the compression method remains an option;
- for testing of materials, samples can now be taken from pellet, moulded sheet or melt index extrudate, using test pieces cut by microtome;
- more prescriptive descriptions of preparing samples and test pieces from pipe and fittings have been given;
- the magnification to be used to assess the size of particles and agglomerates is no longer specified (a magnification appropriate to allow identification of the different size ranges is to be used);
- for the rating of appearance, a more precise evaluation has been given.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

This is a preview of ISO 18553:2025. [Click here to purchase the full version from the ANSI store.](#)

Thermoplastic products manufactured for pipeline systems are normally pigmented. Typically, fine carbon black particles or pigments are used. These are normally incorporated into the raw material prior to either extrusion of pipe or injection moulding of pipe fittings. The purpose of colouring is to allow identification of the pipeline in service and, in the case of carbon black, to act as protection of the polymer from degradation by ultra-violet light if the product is stored outdoor or used for outdoor service. It is important that the carbon black or pigment particles are correctly dispersed in the polymer, and hence the final product, to ensure that the physical, mechanical and surface protection properties are maintained. Correct dispersion can also be an indication that antioxidants and ultra-violet stabilizers are correctly dispersed, and that the size of agglomerates or particles is not excessive.

This method provides procedures for assessing the degree of dispersion by physical measurement of the size of the dispersed particles and arithmetic grading of the particle size distribution. It also provides photographs for comparison with microscopic images of samples taken from raw-material compounds or products in order to judge subjectively the acceptability of carbon black or pigment dispersion.

A recommended limit of particles/agglomerate size grading and an acceptable rating of appearance is given in [Annex D](#).