

First edition
2021-11

Imaging materials and prints — Abrasion resistance —

Part 1: General rub testing methods

*Matériaux pour l'image et les impressions — Résistance à
l'abrasion —*

Partie 1: Méthodes d'essai de frottement générales



Reference number
ISO 18947-1:2021(E)

© ISO 2021



COPYRIGHT PROTECTED DOCUMENT

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

This is a preview of ISO 18947-1:2021. Click [here](#) to purchase the full version from the ANSI store.

| Contents | | Page |
|---|--|-----------|
| Foreword..... | | iv |
| Introduction..... | | v |
| 1 | Scope | 1 |
| 2 | Normative references | 1 |
| 3 | Terms and definitions | 1 |
| 4 | Principle | 3 |
| 5 | Test device | 4 |
| | 5.1 Test device description..... | 4 |
| | 5.2 Test device preparation..... | 4 |
| 6 | Samples | 5 |
| | 6.1 General..... | 5 |
| | 6.2 Preparation of samples and selection of the receptor material..... | 5 |
| 7 | Test procedure | 5 |
| 8 | Evaluation | 6 |
| | 8.1 General..... | 6 |
| | 8.2 Visual evaluation..... | 6 |
| | 8.3 Optical measurements..... | 7 |
| 9 | Test report | 8 |
| Annex A (informative) Examples of test equipment and corresponding procedures and operating parameters | | 9 |
| Bibliography | | 18 |

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 42, *Photography*, in cooperation with ISO/TC 130, *Graphic Technology* and ISO/IEC JTC 1/SC 28, *Office equipment*.

This second edition cancels and replaces the first edition (ISO 18947:2013), which has been technically revised. The main changes compared to the previous edition are as follows:

- graphic prints and office prints are also covered,
- more test devices have been introduced,
- visual evaluation was added.

A list of all parts in the ISO 18947 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

This is a preview of ISO 18947-1:2021. [Click here to purchase the full version from the ANSI store.](#)

Introduction

This method is one of a series relating to permanence and durability of image prints, which is the resistance to physical, mechanical, chemical and/or environmental stresses in conditions of use. The permanence of the image under environmental stresses is tested by each stress factor individually: light (ISO 18937^[11]), heat (ISO 18936^[10]), ozone (ISO 18941^[12]), and humidity (ISO 18946^[13]). These stress factors are given by the ambient conditions, over which the user often has limited control. The exposure to mechanical and physical stress may often be controlled by the user, unless intense handling is integral to intended use. Tests for rubbing of prints resulting in abrasion or smearing of the image are handled in the series 18947, scratch resistance is addressed in ISO 18922^[8] (for film) and in the series ISO 18951 (all parts) (for reflection prints, currently under development), respectively, and durability tests to simulate accidental exposure to water or food spill is described ISO 18935^[9].

The process of rubbing a surface may result in different types of degradations, e.g. abrasion, scuffing, smudging, and others. They may be observed as loss of colour intensity, scratches, changes in gloss, coloration of former uncoloured areas, (coloured) material transfer to a receptor and others.

This document provides standardized requirements to evaluate the abrasion resistance of image prints in their various formats.

Abrasion and smudge can include both accidental and repeating stresses resulting from handling of the image. The following are some examples of sources of abrasions:

- dirt particles rubbing on printed surface;
- sheet-to-sheet abrasion (sliding motion of sheets relative to each other);
- prints sliding on tables or other flat surfaces;
- interaction with dirt or components inside of printers;
- magnets or other items used in the display of images.

This second edition transforms ISO 18947 into a multipart standard to extend the applicability of this standard to analogue and digital photographic, graphic and office prints. In addition, this second edition allows for the use of additional types of rub testers. The level of abrasion observed in a test depends on the combination of many factors, including factors of the print material under test as well as the test apparatus.

Different test devices show different levels of rub work, depending on the force of the device, relative movement of the samples (direction and speed), test length on the device and the selection of the material and geometry of the abrading receptor.

Material factors that contribute to friction coefficients and therefore influence the susceptibility of printed image to abrasive conditions include surface roughness, surface elasticity, substrate porosity of samples and the chemical formulation, mobility as well as localization of the colorants on the surface or within a receiver layer.

A research project^[23] performed to develop content for the expansion of the applicability of this standard to prints of all kinds tried to link the magnitude of abrasion to a combination of surface roughness, surface elasticity, substrate porosity, direction of the paper fibres and ingredients of inks. The samples used were black sheet-fed offset prints. Substrates, prints and tested samples were investigated with respect to the mentioned properties. Receptors were investigated with respect to the degree of material transfer using scanning densitometry, colour measurement using diffuse sample illumination and two different scanner based image analysis systems. Unfortunately, no correlation of the optical measurements to the visual assessments could be established. This is the background that this document also requires visual assessments of rub sample series.

For photographic prints on coated photo-grade papers, a correlation between abrasion results on reciprocating, flat abrasion testers was found in a round robin study (several laboratories tested

This is a preview of ISO 18947-1:2021. [Click here to purchase the full version from the ANSI store.](#)

samples of the same origin) of TC 42/WG 5, that included imaging technologies such as silver halide, inkjet, electro-photographic and dye diffuse thermal transfer. Together with results from IPI^[22] this round robin study serves as background for ISO 18947-2, which is dedicated to (quasi-) linear, reciprocating, abrasion testing of photographic prints on photo-grade papers, including resin coated (RC photo-grade), barrier coated (water impermeable) paper and coated (water permeable) paper, as well as photo-grade films. The term (quasi-)linear considers that the test movement on the Sutherland type tester (see [A.1](#)) follows an arc segment of a circle with a large diameter, resulting in a mainly linear motion with a small orthogonal component.