

This is a preview of "ISO 21182:2013". [Click here to purchase the full version from the ANSI store.](#)

Second edition  
2013-02-15

---

---

## Light conveyor belts — Determination of the coefficient of friction

*Courroies transporteuses légères — Détermination du coefficient  
de frottement*



Reference number  
ISO 21182:2013(E)

© ISO 2013

This is a preview of "ISO 21182:2013". [Click here to purchase the full version from the ANSI store.](#)



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2013

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

This is a preview of "ISO 21182:2013". [Click here to purchase the full version from the ANSI store.](#)

## Contents

	Page
<b>Foreword</b> .....	<b>iv</b>
<b>Introduction</b> .....	<b>v</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Principle</b> .....	<b>2</b>
4.1 Dynamic coefficient of friction .....	2
4.2 Static coefficient of friction .....	2
<b>5 Apparatus (see Figure 2)</b> .....	<b>2</b>
<b>6 Test piece</b> .....	<b>3</b>
6.1 Test piece material .....	3
6.2 Number and dimensions of test pieces .....	3
6.3 Conditioning .....	4
<b>7 Procedure</b> .....	<b>6</b>
<b>8 Calculation and expression of results</b> .....	<b>6</b>
8.1 Dynamic friction, $\mu_D$ .....	6
8.2 Static friction $\mu_S$ .....	7
8.3 Examples for recorded graph of $\mu_S$ (force/path diagrams) .....	7
<b>9 Test report</b> .....	<b>9</b>
<b>Bibliography</b> .....	<b>10</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 21182 was prepared by Technical Committee ISO/TC 41, *Pulleys and belts (including veebelts)*, Subcommittee SC 3, *Conveyor belts*.

This International Standard is based on EN 1724:1998, prepared by CEN/TC 188.

This second edition cancels and replaces the first edition (ISO 21182:2005), of which it constitutes a minor revision.

This is a preview of "ISO 21182:2013". [Click here to purchase the full version from the ANSI store.](#)

## Introduction

The coefficient of friction of light conveyor belts has to be seen from two different aspects relevant to the choice of the reference material. One aspect is the friction of the underside of the belt. In practice, this is not critical because it is low. Regardless of whether a table of steel or of wood is used, the coefficient of friction is within the range from 0,2 to 0,3 in most cases.

Contrary to this, the top face covers show values over an extended range dependent on their actual function. To achieve this function, the material itself can be modified as well as the surface pattern but the test procedure is the same in every case. So it becomes clear that the chosen steel panel represents a compromise. Its main properties are reproducibility of the surface finish and uncritical friction behaviour against any kind of belt cover.

This International Standard allows comparison of all kinds of conveyor belt to obtain reliable results as a reference. This can be helpful to buyers who need guidance in choosing the right belt for their particular application.

The tests in accordance with this International Standard are limited to dynamic coefficients of friction ( $\mu_D$ ) up to 1,0 and static coefficients of friction ( $\mu_S$ ) up to 1,5. Higher values can show a mixture of friction, adhesion, deformation and other effects occurring, especially where the surface texture is coarse and is therefore unsuitable for this test.

The method using the standardized metallic test panel is intended especially to compare the coefficients of friction of different light conveyor belts. The values received under practice conditions always depend on the frictional partners.

To determine these effects, it is possible to choose a different frictional partner instead of the panel if required. This is mentioned in the test report.