

This is a preview of "ISO 21575:2018". [Click here to purchase the full version from the ANSI store.](#)

First edition
2018-06

Optics and photonics — Optical materials and components — The powder test method for the water resistance of optical glass

*Optique et photonique — Matériaux et composants optiques —
Méthode d'essai sur poudre pour déterminer la résistance à l'eau des
verres optiques*



Reference number
ISO 21575:2018(E)

© ISO 2018

This is a preview of "ISO 21575:2018". [Click here to purchase the full version from the ANSI store.](#)



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

This is a preview of "ISO 21575:2018". [Click here to purchase the full version from the ANSI store.](#)

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principles	1
5 Reagents	1
5.1 Water.....	1
5.2 Alcohol.....	1
6 Apparatus	2
6.1 Sieve.....	2
6.2 Basket for corrosion test.....	2
6.3 Apparatus for corrosion test.....	2
6.4 Heating bath.....	3
7 Preparation of the specimen of the glass to be tested	3
8 Procedure	3
9 Classification and designation	4
10 Test report	4

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 172, *Optics and photonics*, Subcommittee SC 3, *Optical materials and components*.

This is a preview of "ISO 21575:2018". [Click here to purchase the full version from the ANSI store.](#)

Introduction

There are two commonly used methods for test of the chemical resistance of optical glass: The powder method and the surface method. The powder method has simpler procedures for the sample preparation since it does not require a homogeneously polished surface.