

Second edition  
2017-02

---

---

## **Vitreous and porcelain enamels — Determination of resistance to chemical corrosion —**

### **Part 2: Determination of resistance to chemical corrosion by boiling acids, boiling neutral liquids, alkaline liquids and/or their vapours**

*Émaux vitrifiés — Détermination de la résistance à la corrosion chimique —*

*Partie 2: Détermination de la résistance à la corrosion chimique par des acides bouillants, des liquides neutres bouillants, ou des liquides alcalins et/ou leurs vapeurs*



Reference number  
ISO 28706-2:2017(E)

© ISO 2017

This is a preview of "ISO 28706-2:2017". Click [here](#) to purchase the full version from the ANSI store.



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Ch. de Blandonnet 8 • CP 401  
CH-1214 Vernier, Geneva, Switzerland  
Tel. +41 22 749 01 11  
Fax +41 22 749 09 47  
copyright@iso.org  
www.iso.org

This is a preview of "ISO 28706-2:2017". Click here to purchase the full version from the ANSI store.

## Contents

|  | Page      |
|--|-----------|
| <b>Foreword</b> .....                                    | <b>v</b>  |
| <b>Introduction</b> .....                                | <b>vi</b> |
| <b>1 Scope</b> .....                                     | <b>1</b>  |
| <b>2 Normative references</b> .....                      | <b>1</b>  |
| <b>3 Terms and definitions</b> .....                     | <b>1</b>  |
| <b>4 Principle</b> .....                                 | <b>2</b>  |
| <b>5 Reagents</b> .....                                  | <b>2</b>  |
| <b>6 Apparatus and materials</b> .....                   | <b>3</b>  |
| 6.1 Test apparatus.....                                  | 3         |
| 6.2 Test materials.....                                  | 8         |
| <b>7 Packing rings</b> .....                             | <b>8</b>  |
| 7.1 General.....   | 8         |
| 7.2 Packing A.....                                       | 8         |
| 7.3 Packing B.....                                       | 9         |
| <b>8 Test specimens</b> .....                            | <b>9</b>  |
| <b>9 Procedure</b> .....                                 | <b>9</b>  |
| <b>10 Expression of results</b> .....                    | <b>10</b> |
| 10.1 Total loss in mass per unit area.....               | 10        |
| 10.2 Corrosion rate.....                                 | 10        |
| <b>11 Boiling citric acid</b> .....                      | <b>11</b> |
| 11.1 General.....  | 11        |
| 11.2 Test solution.....                                  | 11        |
| 11.3 Duration of the test.....                           | 11        |
| 11.4 Test report.....                                    | 11        |
| <b>12 Boiling sulfuric acid</b> .....                    | <b>11</b> |
| 12.1 General.....  | 11        |
| 12.2 Test solution.....                                  | 11        |
| 12.3 Duration of the test.....                           | 12        |
| 12.4 Test report.....                                    | 12        |
| <b>13 Boiling hydrochloric acid</b> .....                | <b>12</b> |
| 13.1 General.....  | 12        |
| 13.2 Test solution.....                                  | 12        |
| 13.3 Duration of the test.....                           | 12        |
| 13.4 Test report.....                                    | 13        |
| <b>14 Boiling distilled or demineralized water</b> ..... | <b>13</b> |
| 14.1 General.....  | 13        |
| 14.2 Test solution.....                                  | 13        |
| 14.3 Duration of the test.....                           | 13        |
| 14.4 Test report.....                                    | 14        |
| <b>15 Standard detergent solution</b> .....              | <b>14</b> |
| 15.1 General.....  | 14        |
| 15.2 Test solution.....                                  | 14        |
| 15.3 Test temperature.....                               | 15        |
| 15.4 Duration of the test.....                           | 15        |
| 15.5 Test report.....                                    | 15        |
| <b>16 Other test solutions and/or conditions</b> .....   | <b>15</b> |
| 16.1 General.....  | 15        |

This is a preview of "ISO 28706-2:2017". [Click here to purchase the full version from the ANSI store.](#)

|                           |                           |           |
|---------------------------|---------------------------|-----------|
| 16.2                      | Test solution.....        | 15        |
| 16.3                      | Duration of the test..... | 15        |
| 16.4                      | Test report.....          | 16        |
| <b>Bibliography</b> ..... |                           | <b>17</b> |

This is a preview of "ISO 28706-2:2017". Click here to purchase the full version from the ANSI store.

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 107, *Metallic and other inorganic coatings*.

This second edition cancels and replaces the first edition (ISO 28706-2:2008), which has been technically revised with changes as follows.

- This document can also be used to determine resistance to chemical corrosion using alkaline liquids. The title of this document has therefore been amended and a section on standard detergent solutions has been included.
- Additional reagents can be used for testing purposes and these have been included.

A list of all parts in the ISO 28706 series can be found on the ISO website.

## Introduction

Corrosion of vitreous and porcelain enamels by aqueous solutions is a dissolution process. The main component of the enamel, SiO<sub>2</sub>, forms a three-dimensional silica network. After hydrolysis, it decomposes and forms silicic acid or silicates. These are released into the attacking medium. Other components, mainly metal oxides, are hydrolysed as well and form the corresponding hydrated metal ions or hydroxides. All corrosion products are more or less soluble in the attacking medium. The whole process results in a loss in mass per unit area.

For some aqueous solutions, the attack on the enamel proceeds linearly during the corrosion time; for other aqueous solutions, the attack on the enamel proceeds in a logarithmic manner during the corrosion time. Only for the first series of solutions can a scientifically exact rate of loss in mass per unit area (g/m<sup>2</sup>·h) be calculated as well as a corrosion rate (millimetres per year).

The most important parameters influencing aqueous corrosion of the enamel are the enamel quality, the temperature and the pH value. Inhibition effects resulting from the limited solubility of silica can also contribute. The following list describes different types of enamel attack for different corrosion conditions.

- a) In aqueous alkali solutions such as 0,1 mol/l NaOH (see ISO 28706-4:2016, Clause 9), the silica network of the enamel is considerably attacked at 80 °C. Silicates and most of the other hydrolysed components are soluble in the alkali. Attack proceeds linearly during regular test times. Therefore, test results are expressed in terms of a rate of loss in mass per unit area (mass loss per unit area and time) and a corrosion rate (millimetres per year).
- b) At room temperature, in weak aqueous acids such as citric acid (see ISO 28706-1:2008, Clause 9) or also in stronger acids such as sulfuric acid (see ISO 28706-1:2008, Clause 10), there is only minor attack on the silica network of the enamel. Other constituents are leached to some extent from the surface. Highly resistant enamels will show no visual change after exposure. On less resistant enamels, some staining or surface roughening will occur.
- c) In boiling aqueous acids (as described in this document), the silica network of the enamel is being attacked, and silica as well as the other enamel components are released into solution. However, the solubility of silica in acids is low. Soon, the attacking solutions will become saturated with dissolved silica and will then only leach the surface. The acid attack is inhibited and the rate of corrosion drops markedly.

NOTE The glass test equipment also releases silica by acid attack and contributes to the inhibition of the corrosion.

Inhibition is effectively prevented in vapour phase tests. The condensate formed on the test specimen is free of any dissolved enamel constituents.

Examples of enamel corrosion proceeding in a logarithmic manner [see 1)] and linearly [see 2)] are as follows:

- 1) **Boiling citric acid** (see [Clause 11](#)) and **boiling 30 % sulfuric acid** (see [Clause 12](#)).

Since only minute amounts of these acids are found in their vapours, the test is restricted to the liquid phase. The attack is influenced by inhibition effects and corrosion depends on the time of exposure. Therefore, test results are expressed in terms of loss in mass per unit area; no rate of loss in mass per unit area is calculated.

- 2) **Boiling 20 % hydrochloric acid** (see [Clause 13](#)).

Since this is an azeotropic boiling acid, its concentration in the liquid and the vapour phase are identical, and liquid phase testing need not be performed. Vigorous boiling supplies an uninhibited condensate, and the attack proceeds linearly with time of exposure. Therefore,

This is a preview of "ISO 28706-2:2017". [Click here to purchase the full version from the ANSI store.](#)

test results are only expressed in terms of rate of loss in mass per unit area (mass loss per unit area and time) and the corrosion rate (millimetres per year).

- d) At high temperatures, with tests in the liquid phase under autoclave conditions (see ISO 28706-5), aqueous acid attack is severe. To avoid inhibition, the test time is restricted to 24 h and the ratio of attacking acid to attacked enamel surface is chosen so that it is comparatively high (similar to that in a chemical reaction vessel). In addition, only low-silica water is used for the preparation of test solutions. Under these conditions, attack will proceed linearly with time of exposure. Therefore, test results with 20 % hydrochloric acid (see ISO 28706-5:2010, Clause 8), artificial test solutions (see ISO 28706-5:2010, Clause 10) or process fluids (see ISO 28706-5:2010, Clause 11) are also expressed in terms of a rate of loss in mass per unit area (loss in mass per unit area and time).
- e) In boiling water (see [Clause 14](#)), the silica network is fairly stable. The enamel surface is leached and silica is dissolved only to a small extent. This type of attack is clearly represented by the vapour phase attack. In the liquid phase, some inhibition can be observed with highly resistant enamels. However, if the enamel being tested is weak, leached alkali from the enamel can raise pH values to alkaline levels, thus increasing the attack by the liquid phase. Both liquid and vapour phase testing can give valuable information.
- f) Since the attack may or may not be linear, the results are expressed only in terms of loss in mass per unit area and the test time should be indicated.
- g) For standard detergent solution (see ISO 28706-3:2008, Clause 9), it will not be certain whether the linear part of the corrosion curve will be reached during testing for 24 h or 168 h. Calculation of the corrosion rate is therefore not included in the test report.
- h) For other acids (see [Clause 15](#)) and other alkaline solutions (see ISO 28706-3:2008, Clause 10 and ISO 28706-4:2016, Clause 10), it will also not be known if a linear corrosion rate will be reached during the test period. Calculation of the corrosion rate is therefore not included in the test reports of those parts of this document.

For vitreous enamels fired at temperatures below 700 °C, the test parameters (media, temperatures and times) of this document are not appropriate. For such enamels, for example aluminium enamels, other media, temperatures and/or times should be used. This can be done following the procedures described in the clauses for "Other test solutions" in ISO 28706-1, ISO 28706-2, ISO 28706-3 and ISO 28706-4.