



ISO 294-5

**Plastics — Injection moulding of
test specimens of thermoplastic
materials —**

Part 5:
**Preparation of standard specimens
for investigating anisotropy**

*Plastiques — Moulage par injection des éprouvettes de matériaux
thermoplastiques —*

*Partie 5: Préparation d'éprouvettes normalisées pour déterminer
l'anisotropie*

**Fourth edition
2026-01**

This is a preview of ISO 294-5:2026. [Click here to purchase the full version from the ANSI store.](#)



COPYRIGHT PROTECTED DOCUMENT

© ISO 2026

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

This is a preview of ISO 294-5:2026. [Click here to purchase the full version from the ANSI store.](#)

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Apparatus	2
4.1 Type F ISO mould.....	2
4.2 Injection-moulding machine	4
5 Procedure	4
5.1 Conditioning of material.....	4
5.2 Injection moulding.....	4
5.3 Preparation of test specimen.....	5
6 Report on test specimen preparation	5
Annex A (normative) Preparation of test specimens	6

This is a preview of ISO 294-5:2026. [Click here to purchase the full version from the ANSI store.](#)

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 9, *Thermoplastic materials*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 249, *Plastics*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This fourth edition cancels and replaces the third edition (ISO 294-5:2017), which has been technically revised.

The main changes are as follows:

- size 90 mm × 80 mm × 2 mm plates have been removed;
- the normative references have been updated.

A list of all parts in the ISO 294 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

This is a preview of ISO 294-5:2026. [Click here to purchase the full version from the ANSI store.](#)

Reinforced and self-reinforcing injection-mouldable thermoplastics are used in a wide variety of applications, some of which can be safety-related. During the injection-moulding process, reinforcement fibres can preferentially align with the flow of the molten material and not across the flow direction. This preferential alignment causes an imbalance in the properties of the moulded thermoplastic so that, in the flow direction, the alignment of the reinforcing fibres causes a higher strength and stiffness than in the cross direction with fewer aligned fibres. This difference in properties is termed anisotropy and it can result in an injection-moulded component having less than the desired or designed strength. To aid designers in understanding the potential strength of an injection-moulded component, it is desirable to know about the anisotropy of an injection-moulded component.

During the development of this document, it was found that injection-moulded test specimens do not exhibit the same fibre alignment across their thickness, but that the outer layers have fibres preferentially aligned in the mould filling direction while the core has randomly oriented fibres (i.e. no preferential alignment). The ratio of the cross-sectional area of aligned-fibre orientation (i.e. “skin” layer thickness) to that of random-fibre orientation (i.e. “core” thickness) is affected by the specimen thickness and the mould filling rate, i.e. the average injection velocity. Thicker specimens exhibit a lower proportion of aligned fibres than do thinner specimens. Slower mould fill speeds lead to thicker “skin” layers with aligned fibres. As a result, to obtain meaningful data on a particular design of moulding, an investigator should prepare specimens with the maximum anisotropic properties, as this data will best represent the upper and lower bounds of a composite structure. Since the specimen thickness and injection velocity have a significant influence on the final anisotropy, this document should only be used for determining information that is useful in designing mouldings and not as a quality control test for the plastic material itself.

A survey of more than 10 raw material suppliers worldwide carried out from 2010 to 2013 clearly indicated that the preparation of plates which provide a suitable degree of anisotropy requires plates with non-square shape to ensure a fibre orientation in flow direction. Under the conditions of this study, the highest degree of anisotropy was obtained using a plate with dimensions 120 mm × 80 mm × 2 mm. It can be considered that plates longer than 120 mm will show at least as good results. Square plates (e.g. 80 mm × 80 mm × 2 mm or even 150 mm × 150 mm × 2 mm) resulted in problems sometimes independent of the size. Within this study, the plate with size 90 mm × 80 mm × 2 mm as required in the previous edition of this document did not perform well in any case and was removed from this document.