

ANSI Internat Doc Sec

First edition
1997-06-15

**Extenders for paints — Specifications and
methods of test —**

Part 1:
Introduction and general test methods

*Matières de charge pour peintures — Spécifications et méthodes d'essai —
Partie 1: Introduction et méthodes d'essai générales*



Reference number
ISO 3262-1:1997(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 3262-1 was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 2, *Pigments and extenders*.

Together with the subsequent parts, this International Standard cancels and replaces ISO 3262: 1975 which has been technically revised and divided into parts. Part 1 comprises the definition for the term extender and a number of test methods that are applicable to most extenders, whilst part 2 and the following parts specify requirements and, where appropriate, particular test methods for individual extenders.

At present, the following parts of ISO 3262 are in preparation, under the general title

Extenders for paints - Specifications and methods of test

- *Part 1: Introduction and general test methods*

- *Part 2: Baryte (natural barium sulfate)*

© ISO 1997

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case postale 56 • CH-1211 Genève 20 • Switzerland
Internet central@iso.ch
X.400 c=ch; a=400net; p=iso; o=isocs; s=central

Printed in Switzerland

This is a preview of "ISO 3262-1:1997". [Click here to purchase the full version from the ANSI store.](#)

- *Part 3: Blanc fixe*
- *Part 4: Whiting*
- *Part 5: Natural crystalline calcium carbonate*
- *Part 6: Precipitated calcium carbonate*
- *Part 7: Dolomite*
- *Part 8: Natural clay*
- *Part 9: Calcined clay*
- *Part 10: Natural talc/chlorite in lamellar form*
- *Part 11: Natural talc, in lamellar form, containing carbonates*
- *Part 12: Muscovite-type mica*
- *Part 13: Natural quartz (ground)*
- *Part 14: Cristobalite*
- *Part 15: Vitreous silica*
- *Part 16: Aluminium hydroxides*
- *Part 17: Precipitated calcium silicate*
- *Part 18: Precipitated sodium aluminium silicate*
- *Part 19: Precipitated silica*
- *Part 20: Fumed silica*
- *Part 21: Silica sand (unground natural quartz)*
- *Part 22: Diatomaceous earth (kieselguhr)*

This is a preview of "ISO 3262-1:1997". [Click here to purchase the full version from the ANSI store.](#)

Extenders for paints — Specifications and methods of test —

Part 1: Introduction and general test methods

1 Scope

This part of ISO 3262 gives the definition for the term extender and specifies test methods that are required for most of the subsequent parts of ISO 3262.

The subsequent parts of ISO 3262 specify requirements and the corresponding methods of test for extenders for use in paints and related coating materials. These parts may also be suitable for the various materials covered by the standard when they are used for other applications.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this part of ISO 3262. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this part of ISO 3262 are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 385-1: 1984, *Laboratory glassware - Burettes - Part 1: General requirements.*

ISO 648: 1977, *Laboratory glassware - One-mark pipettes.*

ISO 787-2: 1981, *General methods of test for pigments and extenders - Part 2: Determination of matter volatile at 105 °C.*

ISO 842: 1984, *Raw materials for paints and varnishes - Sampling.*

ISO 1042: 1983, *Laboratory glassware - One-mark volumetric flasks.*

ISO 3696: 1987, *Water for analytical laboratory use - Specification and test methods.*

3 Definition

For the purposes of this part of ISO 3262, the following definition applies: