

Second edition
2019-08

Rubber, vulcanized or thermoplastic — Determination of stress relaxation in compression —

Part 1: Testing at constant temperature

*Caoutchouc vulcanisé ou thermoplastique — Détermination de la
relaxation de contrainte en compression —*

Partie 1: Essais à température constante



Reference number
ISO 3384-1:2019(E)

© ISO 2019



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

This is a preview of "ISO 3384-1:2019". Click here to purchase the full version from the ANSI store.

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Principle	2
5 Apparatus	2
6 Calibration	4
7 Test piece	4
7.1 Type and preparation of test pieces.....	4
7.1.1 General.....	4
7.1.2 Cylindrical test pieces.....	4
7.1.3 Ring test pieces.....	4
7.2 Measurement of dimensions of test pieces.....	4
7.3 Number of test pieces.....	5
7.4 Time interval between forming and testing.....	5
7.5 Conditioning of test pieces.....	5
8 Duration, temperature and test liquid	5
8.1 Duration of test.....	5
8.2 Temperature of exposure.....	6
8.3 Immersion liquids.....	6
9 Procedure	6
9.1 Preparation.....	6
9.2 Thickness measurement.....	6
9.2.1 Cylindrical test pieces.....	6
9.2.2 Ring test pieces.....	6
9.3 Method A.....	6
9.4 Method B.....	7
10 Expression of results	7
11 Precision	8
12 Test report	8
Annex A (informative) Precision	10
Annex B (normative) Calibration schedule	12
Bibliography	14

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 2, *Testing and analysis*.

This second edition cancels and replaces the first edition (ISO 3384-1:2011), which has been technically revised. It also incorporates the Amendment ISO 3384-1:2011/Amd.1:2013.

The main changes compared to the previous edition are as follows:

- test procedures have been improved in detail;
- the requirement for compression device (5.1) has been harmonized with other International Standards;
- content of ISO 3384-1:2011/Amd.1:2013 has been incorporated ([Annex B](#)).

A list of all parts in the ISO 3384 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

This is a preview of "ISO 3384-1:2019". [Click here to purchase the full version from the ANSI store.](#)

Introduction

When a constant strain is applied to rubber, the force necessary to maintain that strain is not constant but decreases with time; this behaviour is called "stress relaxation". Conversely, when rubber is subjected to a constant stress, an increase in the deformation takes place with time; this behaviour is called "creep".

Tests in compression are normally made under continuous stress conditions (i.e. the test piece remains strained throughout the test), and are hence a measure of sealing force. Note that the terms continuous and discontinuous used in this standard refer to whether the measure of force is made continuously or at intervals.

Tests to use stress relaxation in tension as a measure of ageing are given in ISO 6914.

The processes responsible for stress relaxation can be physical or chemical in nature, and under all normal conditions both types of process will occur simultaneously. However, at normal or low temperatures and/or short times, stress relaxation is dominated by physical processes, while at high temperatures and/or long times chemical processes are dominant.

If the life-time of a material is to be investigated, it can be determined using the method described in ISO 11346.

In addition to the need to specify the temperatures and time intervals in a stress relaxation test, it is necessary to specify the initial stress and the previous mechanical history of the test piece since these can also influence the measured stress relaxation, particularly in rubbers containing fillers.

The most important factor in achieving good repeatability and reproducibility when making stress relaxation tests is to keep the temperature and compression constant during all measurements.