

This is a preview of "ISO 3795:1989". [Click here to purchase the full version from the ANSI store.](#)

STANDARD

3795

Second edition
1989-10-15

**Road vehicles, and tractors and machinery for
agriculture and forestry — Determination of
burning behaviour of interior materials**

*Véhicules routiers et tracteurs et matériels agricoles et forestiers — Détermination
des caractéristiques de combustion des matériaux intérieurs*



Reference number
ISO 3795 : 1989 (E)

This is a preview of "ISO 3795:1989". [Click here to purchase the full version from the ANSI store.](#)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council. They are approved in accordance with ISO procedures requiring at least 75 % approval by the member bodies voting.

International Standard ISO 3795 was prepared jointly by Technical Committees ISO/TC 22, *Road vehicles*, and ISO/TC 23, *Tractors and machinery for agriculture and forestry*.

This second edition cancels and replaces the first edition (ISO 3795 : 1976), the scope of which has been extended to include tractors and machinery for agriculture and forestry.

© ISO 1989

All rights reserved. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

This is a preview of "ISO 3795:1989". [Click here to purchase the full version from the ANSI store.](#)

Introduction

Evaluation of burning behaviour of interior materials is based on the assumption that a fire in the passenger compartment is unlikely to occur when the burning rate of the interior material under the action of a small flame is zero or very small.

In the framework of international regulations for motor vehicle safety prepared by the competent groups of the Economic Commission for Europe (ECE/UNO), ISO had been requested to develop a method for the determination of the burning behaviour of interior materials in motor vehicles. Extensive information on existing test methods was collected and evaluated. In view of safety standards which are already mandatory, considerations were based primarily on the test procedure defined in US-FMVSS 302.

Considerable attention was devoted to the problem of ventilation of the combustion chamber. Two series of comparative tests were conducted to investigate different design variations.

After extended discussions, it was decided to incorporate the combustion chamber described in this International Standard.

Furthermore, it was decided to require the presence of supporting wires as part of the standard equipment in order to avoid subjective interpretations of sample behaviour by the test personnel.

This is a preview of "ISO 3795:1989". [Click here to purchase the full version from the ANSI store.](#)

This page intentionally left blank

Road vehicles, and tractors and machinery for agriculture and forestry — Determination of burning behaviour of interior materials

1 Scope

This International Standard specifies a method for determining the horizontal burning rate of materials used in the occupant compartment of road vehicles (for example, passenger cars, lorries/trucks, estate cars, coaches), and of tractors and machinery for agriculture and forestry, after exposure to a small flame.

This method permits testing of materials and parts of the vehicle interior equipment individually or in combination up to a thickness of 13 mm. It is used to judge the uniformity of production lots of such materials with respect to their burning behaviour.

Because of the many differences between the real world situation (application and orientation within vehicle interior, conditions of use, ignition source, etc.) and the precise test conditions specified in this International Standard, this method cannot be considered as suitable for evaluation of all true in-vehicle burning characteristics.

2 Normative reference

The following standard contains provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the edition indicated was valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent edition of the standard indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 2768-1: 1989, *General tolerances — Part 1: Tolerances for linear and angular dimensions without individual tolerance indications*.

3 Definitions

For the purposes of this International Standard, the following definitions apply.

3.1 burning rate: Quotient of the burnt distance measured according to this International Standard and the time taken to burn this distance.

It is expressed in millimetres per minute.

3.2 composite material: Material composed of several layers of similar or different materials intimately held together at their surfaces by cementing, bonding, cladding, welding, etc.

When different materials are connected together intermittently (for example, by sewing, high-frequency welding, riveting), then in order to permit the preparation of individual samples in accordance with clause 6, such materials will not be considered as composite materials.

3.3 exposed side: Side which faces towards the occupant compartment when the material is mounted in the vehicle.

4 Principle

A sample is held horizontally in a U-shaped holder and is exposed to the action of a defined low-energy flame for 15 s in a combustion chamber, the flame acting on the free end of the sample. The test determines if and when the flame extinguishes or the time in which the flame passes a measured distance.

5 Apparatus

5.1 Combustion chamber (see figure 1), preferably of stainless steel and having the dimensions given in figure 2. The front of the chamber contains a flame-resistant observation window, which may cover the front and which can be constructed as an access panel.

The bottom of the chamber has vent holes, and the top has a vent slot all around. The combustion chamber is placed on four feet, 10 mm high.

The chamber may have a hole at one end for the introduction of the sample holder containing the sample; in the opposite end, a hole is provided for the gas line. Melted material is caught in a pan (see figure 3) which is placed on the bottom of the chamber between vent holes without covering any vent hole area.