Third edition 2016-01-15

Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance —

Part 2:

Assessment of degree of blistering

Peintures et vernis — Évaluation de la dégradation des revêtements — Désignation de la quantité et de la dimension des défauts, et de l'intensité des changements uniformes d'aspect —

Partie 2: Évaluation du degré de cloquage



Reference number ISO 4628-2:2016(E)



COPYRIGHT PROTECTED DOCUMENT

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office Ch. de Blandonnet 8 • CP 401 CH-1214 Vernier, Geneva, Switzerland Tel. +41 22 749 01 11 Fax +41 22 749 09 47 copyright@iso.org www.iso.org

Contents		Page	
Fore	Forewordiv		
1	Scope	1	
2	Normative references	1	
3	Terms and definitions	1	
4	Assessment	1	
5	Expression of results	2	
6	Test report	2	
Ann	ex A (normative) Calibration images	7	
Ann	ex B (informative) Correlation between ISO 4628-2 and ASTM D 714 rating systems	12	
Bibl	iography	13	

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword - Supplementary information

The committee responsible for this document is ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*.

This third edition cancels and replaces the second edition (ISO 4628-2:2003), which has been technically revised with the following changes:

- a) a normative reference to ISO 13076 for illumination for the assessment has been added;
- b) a note concerning visibility of S1 size of blisters has been added.

ISO 4628 consists of the following parts, under the general title *Paints and varnishes* — *Evaluation of degradation of coatings* — *Designation of quantity and size of defects, and of intensity of uniform changes in appearance*:

- Part 1: General introduction and designation system
- Part 2: Assessment of degree of blistering
- Part 3: Assessment of degree of rusting
- Part 4: Assessment of degree of cracking
- Part 5: Assessment of degree of flaking
- Part 6: Assessment of degree of chalking by tape method
- Part 7: Assessment of degree of chalking by velvet method
- Part 8: Assessment of degree of delamination and corrosion around a scribe or other artificial defect
- Part 10: Assessment of filiform corrosion