

This is a preview of "ISO 5832-8:1997". [Click here to purchase the full version from the ANSI store.](#)

Second edition  
1997-07-15

---

---

## **Implants for surgery — Metallic materials —**

### **Part 8:**

### **Wrought cobalt-nickel-chromium-molybdenum-tungsten-iron alloy**

*Implants chirurgicaux — Produits à base de métaux —*

*Partie 8: Alliage corroyé à base de cobalt, de nickel, de chrome, de molybdène, de tungstène et de fer*



Reference number  
ISO 5832-8:1997(E)

This is a preview of "ISO 5832-8:1997". [Click here to purchase the full version from the ANSI store.](#)

## Contents

	Page
1 Scope .....	1
2 Normative references .....	1
3 Chemical composition .....	1
4 Microstructure .....	1
5 Mechanical properties .....	2
6 Test methods .....	2

© ISO 1997

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization

Case postale 56 • CH-1211 Genève 20 • Switzerland

Internet: [central@iso.ch](mailto:central@iso.ch)

X.400: c=ch; a=400net; p=iso; o=isocs; s=central

Printed in Switzerland

This is a preview of "ISO 5832-8:1997". [Click here to purchase the full version from the ANSI store.](#)

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 5832-8 was prepared by Technical Committee ISO/TC 150, *Implants for surgery*, Subcommittee SC 1, *Materials*.

This second edition cancels and replaces the first edition (ISO 5832-8:1987), which has been technically revised.

ISO 5832 consists of the following parts, under the general title *Implants for surgery — Metallic materials*:

- *Part 1: Wrought stainless steel*
- *Part 2: Unalloyed titanium*
- *Part 3: Wrought titanium 6-aluminium 4-vanadium alloy*
- *Part 4: Cobalt-chromium-molybdenum casting alloy*
- *Part 5: Wrought cobalt-chromium-tungsten-nickel alloy*
- *Part 6: Wrought cobalt-nickel-chromium-molybdenum alloy*
- *Part 7: Forgeable and cold-formed cobalt-chromium-nickel-molybdenum-iron alloy*
- *Part 8: Wrought cobalt-nickel-chromium-molybdenum-tungsten-iron alloy*
- *Part 9: Wrought high nitrogen stainless steel*
- *Part 10: Wrought titanium 5-aluminium 2,5-iron alloy*
- *Part 11: Wrought titanium 6-aluminium 7-niobium alloy*
- *Part 12: Wrought cobalt-chromium-molybdenum alloy*

This is a preview of "ISO 5832-8:1997". [Click here to purchase the full version from the ANSI store.](#)

## Introduction

No known surgical implant material has ever been shown to cause absolutely no adverse reactions in the human body. However, long-term clinical experience of the use of the material referred to in this part of ISO 5832 has shown that an acceptable level of biological response can be expected, when the material is used in appropriate applications.

This is a preview of "ISO 5832-8:1997". [Click here to purchase the full version from the ANSI store.](#)

# Implants for surgery — Metallic materials —

## Part 8:

## Wrought cobalt-nickel-chromium-molybdenum-tungsten-iron alloy

### 1 Scope

This part of ISO 5832 specifies the characteristics of, and the corresponding test methods for, wrought cobalt-nickel-chromium-molybdenum-tungsten-iron alloy for use in the manufacture of surgical implants.

NOTE — The mechanical properties of a sample obtained from a finished product made of this alloy depend on the treatment undergone, and may not necessarily comply with the specifications given in this part of ISO 5832.

### 2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this part of ISO 5832. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this part of ISO 5832 are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 643:1983<sup>1)</sup>, *Steels — Micrographic determination of the ferritic or austenitic grain size.*

ISO 6892:—<sup>2)</sup>, *Metallic materials — Tensile testing at ambient temperatures.*

### 3 Chemical composition

The heat analysis of a representative sample of the alloy when determined in accordance with clause 6 shall comply with the chemical composition specified in table 1.

### 4 Microstructure

The microstructure<sup>3)</sup> shall be uniform and single-phased in the annealed condition. The grain size in the annealed condition, determined in accordance with clause 6, shall not be coarser than grain size No. 5.

1) ISO 643 is given as a reference, even though the material dealt with in this part of ISO 5832 is not iron-based.

2) To be published. (Revision of ISO 6892:1984)

3) For determination of the microstructure, the following etching reagent may be used: 10 ml of nitric acid ( $\rho_{20} = 1,4$  kg/l) plus 100 ml of hydrochloric acid ( $\rho_{20} = 1,19$  kg/l) plus 0,3 ml of Vogel's Sparbeize plus 100 ml of distilled water.