

This is a preview of "ISO 8013:2019". [Click here to purchase the full version from the ANSI store.](#)

Fourth edition
2019-07

Rubber, vulcanized — Determination of creep in compression or shear

*Caoutchouc vulcanisé — Détermination du fluage en compression ou
en cisaillement*



Reference number
ISO 8013:2019(E)

© ISO 2019



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

This is a preview of "ISO 8013:2019". Click here to purchase the full version from the ANSI store.

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Apparatus	2
4.1 Thickness-measuring device.....	2
4.2 Compression device for measurement in compression.....	2
4.3 Shear device for measurements in shear.....	2
4.4 Temperature-controlled chamber.....	3
4.5 Timer.....	3
5 Calibration	7
6 Test piece	8
6.1 Test piece for measurements in compression.....	8
6.2 Test piece for measurements in shear.....	8
6.3 Number.....	8
7 Time-lapse between vulcanization and testing	9
8 Mechanical conditioning	10
9 Test temperature	10
10 Procedure	10
10.1 Testing.....	10
10.2 Duration of test.....	11
11 Calculation of results	11
11.1 Creep increment.....	11
11.1.1 In compression.....	11
11.1.2 In shear.....	11
11.2 Creep index.....	12
11.2.1 In compression.....	12
11.2.2 In shear.....	12
11.3 Compliance increment.....	13
11.3.1 In compression.....	13
11.3.2 In shear.....	13
12 Expression of results	13
13 Test report	14
Annex A (informative) Values of forces required for rubbers of different hardnesses	15
Annex B (normative) Calibration schedule	16
Bibliography	19

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 2, *Testing and analysis*.

This fourth edition cancels and replaces the third edition (ISO 8013:2012), of which it constitutes a minor revision. A few editorial changes have been made including updating the publication dates of normative references in [Clause 2](#).

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

This is a preview of "ISO 8013:2019". [Click here to purchase the full version from the ANSI store.](#)

Introduction

When a constant stress is applied to rubber, the deformation is not constant but increases gradually with time; this behaviour is called “creep”. Conversely, when rubber is subjected to a constant strain, a decrease in the stress in the material takes place; this behaviour is called “stress relaxation”.

The creep test is of particular interest where vulcanized rubbers are used to support a constant load, such as in bearings or mountings.

The processes responsible for creep can be physical or chemical in nature, and under all normal conditions both processes will occur simultaneously. However, at normal or low temperatures and/or short times, creep is dominated by physical processes, while at high temperatures and/or long times, chemical processes are dominant. In general, physical creep is found to be directly proportional to logarithmic time, and chemical creep to linear time; but great care has to be taken in extrapolating time/creep curves in order to predict creep after periods considerably longer than those covered by the test, and in using tests at higher temperatures as accelerated tests to give information on creep at lower temperatures.

In addition to the need to specify the temperature intervals and time intervals in a creep test, it is also necessary to specify the initial strain and the previous mechanical history of the test piece, since these might also influence the measured creep, particularly in rubbers containing filler.