

# INTERNATIONAL STANDARD



---

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION  
ORGANISATION INTERNATIONALE DE NORMALISATION  
МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ

---

**ISO**  
**8233**

First edition  
1988-12-15

Corrected and reprinted  
1989-05-15

## **Thermoplastics valves — Torque — Test method**

*Robinets en matériaux thermoplastiques — Couple de manœuvre — Méthode d'essai*

This is a preview of "ISO 8233:1988". [Click here to purchase the full version from the ANSI store.](#)

## **Foreword**

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council. They are approved in accordance with ISO procedures requiring at least 75 % approval by the member bodies voting.

International Standard ISO 8233 was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*.

Users should note that all International Standards undergo revision from time to time and that any reference made herein to any other International Standard implies its latest edition, unless otherwise stated.

# Thermoplastics valves — Torque — Test method

## 1 Scope

This International Standard specifies a test method for the determination of the opening and closing torque of thermoplastics valves.

## 2 Field of application

This International Standard applies to all types of thermoplastics valves intended to be used for the transport of fluids.

## 3 References

ISO 161-1, *Thermoplastics pipes for the transport of fluids — Nominal outside diameters and nominal pressures — Part 1: Metric series*.

ISO 6708, *Pipe components — Definition of nominal size*.

ISO 7349, *Thermoplastics valves — Connection references*.

## 4 Definitions

For the purposes of this International Standard, the definition of the nominal diameter (DN) given in ISO 6708 and the following definitions apply.

**4.1 closing torque:** Torque exerted over the full closing operation to achieve full tightness of the valve at nominal pressure.

**4.2 opening torque:** Torque exerted initially to open the valve from fully closed or over the full opening operation.

**4.3 nominal pressure (PN):** Alphanumeric designation, used for reference purposes, related to the mechanical strength of a valve. Usually it corresponds to the service pressure, in bar<sup>1)</sup>, with water at 20 °C, for which the valve is designed (see ISO 161-1).

## 5 Test specimen

The test specimen shall be an unused valve, unless otherwise specified in the specific product standard.

## 6 Test conditions

**6.1** Water or air at the nominal pressure of the valve (0,6 MPa max. when using air), connected in accordance with ISO 7349, at  $23 \pm 2$  °C shall be applied to the test specimen as indicated in clause 8.

**6.2** Other test conditions, including the use of other fluids and/or other temperatures, may also be prescribed by specifications for valves for particular applications, such as those for the transport of gaseous fuels.

## 7 Apparatus

NOTE — If air is used as the test medium, it is necessary to take appropriate safety precautions for the use of compressed gases.

**7.1 Pump,** capable of delivering a pressure at least equivalent to the nominal pressure of the valve under test.

**7.2 Device,** capable of supplying the required torque with an accuracy of  $\pm 2$  %.

**7.3 Measuring instrument,** between the torque device and the valve, which shall permit the continuous reading of the torque with the required accuracy of  $\pm 2$  %, and the recording of its maximum value.

## 8 Procedure

### 8.1 Torque test before conditioning

At least 12 h before carrying out this test, open and close the valve ten times to ensure smooth operation.

**8.1.1** With the valve closed, raise the pressure gradually over 60 s to the nominal pressure of the valve and maintain it for 5 min.

**8.1.2** Connect the valve handle to the torque device and measuring instrument and apply a torque, increasing it gradually until the opening torque is reached. Complete the opening of the valve in accordance with the requirements specified in the table.

1) 1 bar =  $10^5$  Pa