

Third edition
2019-10

Preparation of steel substrates before application of paints and related products — Surface preparation methods —

Part 2: Abrasive blast-cleaning

*Préparation des subjectiles d'acier avant application de peintures et de produits assimilés — Méthodes de préparation des subjectiles —
Partie 2: Décapage par projection d'abrasif*



Reference number
ISO 8504-2:2019(E)

© ISO 2019



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

This is a preview of "ISO 8504-2:2019". [Click here to purchase the full version from the ANSI store.](#)

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Abrasives	2
4.1 Materials and types.....	2
4.2 General requirements.....	4
4.2.1 Technical.....	4
4.2.2 Health and safety.....	4
4.3 Selection considerations.....	4
5 Abrasive blast-cleaning methods	5
5.1 Dry abrasive blast-cleaning.....	5
5.1.1 Centrifugal abrasive blast-cleaning.....	5
5.1.2 Compressed-air abrasive blast-cleaning.....	6
5.1.3 Vacuum or suction-head abrasive blast-cleaning.....	6
5.2 Wet abrasive blast-cleaning.....	7
5.2.1 General.....	7
5.2.2 Moisture-injection abrasive blast-cleaning (compressed-air moisture- injection abrasive blast-cleaning).....	7
5.2.3 Compressed-air wet abrasive blast-cleaning.....	8
5.2.4 Slurry blast-cleaning.....	8
5.2.5 Pressurized-liquid blast-cleaning.....	9
6 Procedure	9
6.1 Preparation before blast-cleaning.....	9
6.2 Blast-cleaning.....	9
6.3 After blast-cleaning.....	10
7 Assessment of the blast-cleaned surface	10
Bibliography	11

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 12, *Preparation of steel substrates before application of paints and related products*.

This third edition cancels and replaces the second edition (ISO 8504-2:2000), which has been technically revised. The main changes compared to the previous edition are as follows:

- update of [Clause 2](#), normative references;
- editorial revision.

A list of all parts in the ISO 8504 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

This is a preview of "ISO 8504-2:2019". [Click here to purchase the full version from the ANSI store.](#)

Introduction

The performance of protective coatings of paint and related products applied to steel is significantly affected by the state of the steel surface immediately prior to painting. The principal factors that are known to influence this performance are

- the presence of rust and mill scale,
- the presence of surface contaminants, including salts, dust, oils and greases, and
- the surface profile.

The ISO 8501 series, the ISO 8502 series and the ISO 8503 series provide methods for assessing these factors, while the ISO 8504 series provides requirements and guidance on the preparation methods that are available for cleaning steel substrates, indicating the capabilities of each in attaining specified levels of cleanliness.

The ISO 8504 series is applicable to new and corroded steel surfaces and to steel surfaces that are uncoated or have been previously coated with paints and related products.

These International Standards do not contain provisions for the protective coating system to be applied to the steel surface. They do not contain provisions for the surface quality requirements for specific situations even though surface quality can have a direct influence on the choice of protective coating to be applied and on its performance. Such provisions are found in other documents such as national standards and codes of practice. Users of these International Standards should ensure the qualities specified are

- compatible and appropriate both for the environmental conditions to which the steel will be exposed and for the protective coating system to be used, and
- within the capability of the cleaning procedure specified.

The primary objective of surface preparation is to ensure the removal of deleterious matter and to obtain a surface that permits satisfactory adhesion of the priming paint to steel. It is also intended to assist in reducing the amounts of contaminants that initiate corrosion.

Abrasive blast-cleaning is a most effective method for mechanical surface preparation. It is widely applicable because this method of surface preparation has a number of versatile features listed below.

- The method allows a high production rate.
- The equipment can be stationary or mobile and is adaptable to the objects to be cleaned.
- The method is applicable to most types and forms of steel surface.
- Many different surface states can be produced, for example different preparation grades and surface profiles.
- Effects such as cleaning, peening, roughening, levelling and lapping can be produced.
- It is possible to remove selectively partly failed coatings, leaving sound coatings intact.
- Abrasive ricochet (rebound) enables the cleaning of otherwise inaccessible areas.