

STANDARD

8688-1

First edition
1989-05-01

Tool life testing in milling —

Part 1 : Face milling

*Essai de durée de vie des outils de fraisage —
Partie 1 : Surfaçage*



Reference number
ISO 8688-1 : 1989 (E)

This is a preview of "ISO 8688-1:1989". [Click here to purchase the full version from the ANSI store.](#)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council. They are approved in accordance with ISO procedures requiring at least 75 % approval by the member bodies voting.

International Standard ISO 8668-1 was prepared by Technical Committee ISO/TC 29, *Small tools*.

Users should note that all International Standards undergo revision from time to time and that any reference made herein to any other International Standard implies its latest edition, unless otherwise stated.

© ISO 1989

All rights reserved. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

This is a preview of "ISO 8688-1:1989". [Click here to purchase the full version from the ANSI store.](#)

Contents

	Page
0 Introduction	1
1 Scope and field of application	1
2 References	2
3 Workpiece	2
3.1 Work material	2
3.2 Dimensions	3
4 Tool : Cutter	3
4.1 Dimensions and tolerances	3
4.2 Tool geometry	3
4.3 Cutting edge and insert surface	3
4.4 Tool material	5
4.5 Mounting of the tool	5
5 Cutting fluid	5
6 Cutting conditions	5
6.1 Recommended cutting conditions	5
6.2 Other cutting conditions	6
6.3 Location of the cutter	6
6.4 Cutting speed	6
7 Tool deterioration and tool-life criteria	6
7.1 Introduction	6
7.2 Definitions	6
7.3 Tool deterioration phenomena	7
7.4 Tool deterioration phenomena used as tool-life criteria	12
7.5 Assessment of tool deterioration	12

This is a preview of "ISO 8688-1:1989". [Click here to purchase the full version from the ANSI store.](#)

8	Equipment	15
8.1	Machine tool	15
8.2	Other equipment	16
9	Procedure	16
9.1	Purpose	16
9.2	Planning	16
9.3	Preparation of material, tools and equipment	17
9.4	Test techniques	17
9.5	Measurements and recording of tool deterioration	18
10	Evaluation of results	18
10.1	General considerations	18
10.2	Treatment of test values	18
10.3	Number of test runs	18
10.4	Diagrams	20
10.5	Statistical interpretation	20
Annexes		
A	Reference work materials	22
B	Tool setting	23
C	Example data sheet	24
D	Statistical calculations	25
	Bibliography	27

Tool life testing in milling —

Part 1 : Face milling

0 Introduction

Procedures and conditions for tool-life testing with single-point turning tools are the subject of ISO 3685. Successful application of ISO 3685 resulted in requests for similar documents relating to other commonly used cutting methods.

This part of ISO 8688 has been developed on the initiative of the International Institution for Production Engineering Research (CIRP) and applies to face milling operations with carbide tools, as illustrated in figure 1, which represent a major manufacturing activity.

The recommendations contained in this part of ISO 8688 are applicable in both laboratories and factories. They are intended to unify procedures in order to increase the reliability and comparability of test results when making comparison of cutting tools, work materials, cutting parameters or cutting fluids. In order to achieve as far as possible these aims, recommended reference materials and conditions are included and should be used as far as is practical.

In addition, the recommendations can be used to assist in establishing recommendable cutting data, or to determine limiting factors and machining characteristics such as cutting forces, machined surface characteristics, chip form, etc. For these purposes in particular, certain parameters, which have been given recommended values, may have to be used as variables.

The test conditions recommended in this part of ISO 8688 have been designed for face milling tests using steel and cast iron workpieces of normal microstructure. However, with suitable modifications, this part of ISO 8688 can be applied to face milling tests on, for example, other work materials or with cutting tools developed for specific applications.

The specified accuracy given in these recommendations should be considered as a minimum requirement. Any deviation from

the recommendations should be reported in detail in the test report.

NOTE — This part of ISO 8688 does not constitute acceptance tests and should not be used as such.

1 Scope and field of application

This part of ISO 8688 specifies recommended procedures for tool-life testing with cemented carbide tools used for face milling of steel and cast iron workpieces. It can be applied to laboratory as well as to production practice.

The cutting conditions in face milling may be considered under two categories as follows :

- a) conditions as a result of which tool deterioration is due predominantly to wear;
- b) conditions under which tool deterioration is due mainly to other phenomena such as edge fracture or plastic deformation.

This part of ISO 8688 considers only those recommendations concerned with testing which results predominantly in tool wear.

Testing for the second group of conditions given above is currently under study.

This part of ISO 8688 establishes specifications for the following factors of tool-life testing with face milling tools in accordance with figure 1: workpiece, tool, cutting fluid, cutting conditions, equipment, assessment of tool deterioration and tool life, test procedures, recording, evaluation and presentation of results.