

INTERNATIONAL STANDARD

ISO
9042

First edition
1988-12-15



INTERNATIONAL ORGANIZATION FOR STANDARDIZATION
ORGANISATION INTERNATIONALE DE NORMALISATION
МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ

Steels — Manual point counting method for statistically estimating the volume fraction of a constituent with a point grid

Aciers — Méthode manuelle d'estimation statistique de la fraction volumique d'un constituant à l'aide de grilles de points

This is a preview of "ISO 9042:1988". [Click here to purchase the full version from the ANSI store.](#)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council. They are approved in accordance with ISO procedures requiring at least 75 % approval by the member bodies voting.

International Standard ISO 9042 was prepared by Technical Committee ISO/TC 17, *Steel*.

Steels — Manual point counting method for statistically estimating the volume fraction of a constituent with a point grid

1 Scope

This International Standard specifies a manual point counting method for statistically estimating the volume fraction of a constituent through the microstructure of a steel by means of a point grid.

It applies to constituents which are clearly identifiable.

NOTE — In this International Standard, the word "constituent" can designate a phase as well as a micrographic constituent composed of two or more phases.

2 Principle

2.1 The basic principle is that a grid with a number of regularly arrayed points, when systematically placed over an image of a micrographic section, can provide, after a representative number of placements on different fields, an unbiased estimation of the volume fraction of the constituent.

2.2 The method consists in superimposing the point grid on a given number of fields of the observed surface and in counting the number of points of the grid included in the constituent and then calculating its volume fraction.

3 Symbols and definitions

For the purpose of this International Standard, the following symbols are used.

n = number of fields observed

P_T = total number of points in the grid

P_i = point count on the i th field

$P_p(i)$ = proportion of grid points in the constituent on the i th observed field, expressed as a percentage of the total number of points in the grid

$$P_p(i) = \frac{P_i}{P_T} \times 100$$

\bar{P}_p = arithmetic average of $P_p(i)$

$$\bar{P}_p = \frac{1}{n} \sum_{i=1}^n P_p(i)$$

\hat{s} = estimate of the standard deviation (σ)

$$\hat{s} = \left\{ \frac{1}{n-1} \sum_{i=1}^n [P_p(i) - \bar{P}_p]^2 \right\}^{1/2}$$

CI = 95 % confidence interval

$$CI = \pm 2 \frac{\hat{s}}{\sqrt{n}}$$

V_V = volume fraction of the constituent expressed as a percentage

$$V_V = \bar{P}_p \pm CI$$

$$\text{Error \%} = \frac{CI}{\bar{P}_p} \times 100$$

= statistical precision

4 Apparatus

4.1 Grid

The grid consists of a specified number of equally spaced points formed by the intersections of very thin lines. The two types of grid (circular or square array) shown in figure 1 are given as examples that can be used.

The grid can be constituted by a reticle placed in the eyepiece of the microscope or reproduced on a transparency which is placed on the viewing screen of the microscope or on micrographs¹⁾.

1) Since the use of micrographs is time-consuming and more costly, it should be avoided if possible.