

This is a preview of "ISO/TS 5660-3:2012". [Click here to purchase the full version from the ANSI store.](#)

First edition  
2012-12-01

---

---

## Reaction-to-fire tests — Heat release, smoke production and mass loss rate —

### Part 3: Guidance on measurement

*Essais de réaction au feu — Débit calorifique, taux de dégagement de  
fumée et taux de perte de masse —*

*Partie 3: Lignes directrices relatives au mesurage*



Reference number  
ISO/TS 5660-3:2012(E)

© ISO 2012



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2012

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

This is a preview of "ISO/TS 5660-3:2012". Click here to purchase the full version from the ANSI store.

## Contents

	Page
<b>Foreword</b> .....	<b>v</b>
<b>Introduction</b> .....	<b>vi</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Capability and limitations of the cone calorimeter</b> .....	<b>1</b>
<b>4 Calibration of the cone calorimeter</b> .....	<b>2</b>
4.1 General.....	2
4.2 Heat flux meter calibration (see 6.12 and 10.3.1 of ISO 5660-1:2002).....	2
4.3 Calibration frequency.....	2
4.4 Oxygen analyser calibration (see 10.1.5, 10.1.6 and 10.2.3 of ISO 5660-1:2002).....	3
4.5 Determining orifice plate calibration factor.....	4
4.6 Additional comments on the orifice calibration factor.....	4
4.7 Calibration of smoke measurement system.....	5
4.8 Precautions in relation to water/CO <sub>2</sub> removal.....	6
4.9 Routine maintenance.....	6
<b>5 Test specimen preparation and presentation</b> .....	<b>6</b>
5.1 General.....	6
5.2 Specimen trays and edge retainer frame.....	8
<b>6 Selection of heat flux</b> .....	<b>9</b>
<b>7 Ignition protocols</b> .....	<b>11</b>
<b>8 Guidance on the testing of non-standard products</b> .....	<b>11</b>
8.1 General.....	11
8.2 Non-planar products.....	11
8.3 Radiation transfer considerations.....	13
8.4 Thermally mobile specimens.....	19
<b>9 Composites and layered products</b> .....	<b>20</b>
9.1 General.....	20
9.2 Non-homogeneous products.....	20
9.3 Specimens with short test duration.....	20
<b>10 Liquids</b> .....	<b>21</b>
10.1 General.....	21
10.2 Testing without the radiant heater.....	21
10.3 Testing with the radiant heater.....	22
<b>11 The theory of oxygen consumption calorimetry</b> .....	<b>22</b>
11.1 General.....	22
11.2 Silicones.....	23
11.3 Effect of additives and fillers.....	24
<b>12 Start and end of test</b> .....	<b>25</b>
12.1 Start of test.....	25
12.2 End of test.....	25
<b>13 Recommendations for presentation of data</b> .....	<b>25</b>
13.1 Current situation.....	25
13.2 Additional useful data.....	26
13.3 Recommendations.....	29
<b>Annex A (informative) Predictive methods from ISO 5660-1 data</b> .....	<b>30</b>
<b>Annex B (informative) Effect of additives and fillers</b> .....	<b>37</b>
<b>Annex C (informative) Measurements at low levels of heat release</b> .....	<b>40</b>

This is a preview of "ISO/TS 5660-3:2012". [Click here to purchase the full version from the ANSI store.](#)

<b>Bibliography</b> .....	<b>42</b>
---------------------------	-----------

This is a preview of "ISO/TS 5660-3:2012". [Click here to purchase the full version from the ANSI store.](#)

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

In other circumstances, particularly when there is an urgent market requirement for such documents, a technical committee may decide to publish other types of document:

- an ISO Publicly Available Specification (ISO/PAS) represents an agreement between technical experts in an ISO working group and is accepted for publication if it is approved by more than 50 % of the members of the parent committee casting a vote;
- an ISO Technical Specification (ISO/TS) represents an agreement between the members of a technical committee and is accepted for publication if it is approved by 2/3 of the members of the committee casting a vote.

An ISO/PAS or ISO/TS is reviewed after three years in order to decide whether it will be confirmed for a further three years, revised to become an International Standard, or withdrawn. If the ISO/PAS or ISO/TS is confirmed, it is reviewed again after a further three years, at which time it must either be transformed into an International Standard or be withdrawn.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO/TS 5660-3 was prepared by Technical Committee ISO/TC 92, *Fire safety*, Subcommittee SC 1, *Fire initiation and growth*.

This first edition of ISO/TS 5660-3 cancels and replaces ISO/TR 5660-3:2003.

ISO 5660 consists of the following parts, under the general title *Reaction to fire tests — Heat release, smoke production and mass loss rate*:

- *Part 1: Heat release rate (cone calorimeter method)*
- *Part 2: Smoke production rate (dynamic measurement)*
- *Part 3: Guidance on measurement* [Technical Specification]

## Introduction

The first edition of ISO 5660-1, which describes a test method for rate of heat release from building products by means of a cone calorimeter, was published in 1993, following approximately 10 years of development within ISO/TC 92, *Fire safety*, Subcommittee SC 1, *Fire initiation and growth*.

The cone calorimeter is a fire test instrument in which horizontal specimens are exposed to controlled levels of radiant heating by means of a truncated cone-shaped heater. Continuous spark ignition is provided and the time to ignition is recorded for specimens which ignite. The rate of heat release from the burning specimen is determined from measurements of the amount of oxygen consumed from the air flowing through the apparatus, which has been demonstrated to equate to heat release. The mass of the specimen is also measured throughout the burning period. The specimens are usually tested under well ventilated conditions.

Results are expressed in terms of peak and average rates of heat release, as well as total heat released and the effective net heat of combustion. ISO 5660-1:2002 limits the specimen type to essentially flat. Several other groups are now utilizing the cone calorimeter, and a number of new parameters in addition to those defined in ISO 5660-1:2002 and ISO 5660-2:2002 have been defined and used. Some of these, including smoke measurement, require that measurements be made from the beginning of the test rather than at the onset of ignition, which is commonly used as the starting point for heat release measurement.

The cone calorimeter is also designed to allow measurement of smoke and gases such as CO and CO<sub>2</sub>. Smoke measurement is the subject of ISO 5660-2:2002. Further work is under way to define a quality control tool for measuring burning rates of building products. ISO 17554 specifies a test apparatus similar to that of ISO 5660-1:2002 but measures only loss of mass when exposed to radiant heat. Mass loss may be a surrogate for measurement of heat release for some classes of building materials. A similar system which measures the temperature of combustion products generated by this apparatus has been standardized as ISO 13927 [23]. The cone calorimeter fire model is used to measure corrosivity of gases products of combustion in ISO 11907-4 [24]. The effect of the evolved gases on the resistance of a printed circuit board target is used to assess corrosivity.

During development of the cone calorimeter it became apparent that there was considerable interest in the use of the instrument for products other than building products. Several standards have been developed by various national and international groups based on ISO 5660-1:2002 and ISO 5660-2:2002.

This part of ISO 5660 provides recommendations for the testing of products in the cone calorimeter and gives guidance on application of the test results. Supplementary guidance is given in documents referred to in References [1] and [2].