

MSS SP-94-2008

**Quality Standard for
Ferritic and
Martensitic Steel Castings
for
Valves, Flanges,
Fittings, and Other
Piping Components**

**Ultrasonic
Examination Method**

Standard Practice
Developed and Approved by the
Manufacturers Standardization Society of the
Valve and Fittings Industry, Inc.
127 Park Street, NE
Vienna, Virginia 22180
Phone: (703) 281-6613
Fax: (703) 281-6671
E-mail: info@mss-hq.org



www.mss-hq.org

This MSS Standard Practice was developed under the consensus of the MSS Technical Committee 304 and the MSS Coordinating Committee. The content of this Standard Practice is the result of the efforts of competent and concerned volunteers to provide an effective, clear, and non-exclusive specification that will benefit the industry as a whole. This MSS Standard Practice is intended as a basis for common practice by the manufacturer, the user, and the general public. The existence of an MSS Standard Practice does not in itself preclude the manufacture, sale, or use of products not conforming to the Standard Practice. Mandatory conformance is established only by reference in a code, specification, sales contract, or public law, as applicable.

Unless otherwise specifically noted in this MSS SP, any standard referred to herein is identified by the date of issue that was applicable to the referenced standard(s) at the date of issue of this MSS SP. (See Annex A.)

In this Standard Practice all notes, annexes, tables, and figures are construed to be essential to the understanding of the message of the standard, and are considered part of the text unless noted as "supplemental". All appendices appearing in this document are construed as "supplemental". "Supplemental" information does not include mandatory requirements.

U.S. customary units in this SP are the standard; the metric units are for reference only.

Non-toleranced Dimensions in this Standard Practice are nominal, and, unless otherwise specified, shall be considered "for reference only."

Any part of this Standard Practice may be quoted. Credit lines should read 'Extracted from MSS SP-94-2008 with permission of the publisher, the Manufacturers Standardization Society.' Reproduction prohibited under copyright convention unless written permission is granted by the Manufacturers Standardization Society of the Valve and Fittings Industry Inc.

Originally Approved September, 1983

Copyright ©, 1985 by
Manufacturers Standardization Society
of the
Valve and Fittings Industry, Inc.
Printed in U.S.A.

FOREWORD

This MSS Standard Practice, SP-94, Quality Standard for Ferritic and Martensitic Steel Castings for Valves, Flanges, Fittings, and other Piping Components, Ultrasonic Examination Method, was first adopted in 1983. It was developed to provide industry with a uniform method of applying the Ultrasonic Examination procedure and interpretation of the results.

The Standard Practice was reaffirmed in 1987 with essentially no changes.

The third edition issued in 1992 was revised to include a surface finish requirement for the calibration blocks. This was necessary as the previously referenced surface comparator of the Alloy Casting Institute was no longer available.

The 1999 edition includes minor revisions and was formatted to conform to current MSS practices

This 2008 edition includes minor revisions and was formatted to conform to current MSS practices

TABLE OF CONTENTS

<u>SECTION</u>		<u>PAGE</u>
1	SCOPE	1
2	DEFINITIONS.....	1
3	BASIS FOR USE.....	1
4	EQUIPMENT	1
5	PERSONNEL REQUIREMENTS.....	3
6	CASTING CONDITIONS.....	3
7	TEST CONDITIONS.....	3
8	PROCEDURE.....	5
9	DATA REPORTING.....	6
10	EVALUATION OF INDICATIONS.....	6
11	ACCEPTANCE STANDARDS	6

TABLE

1	Dimensions and Identification of Reference Block in the Basic Set	2
2	Dimensions of Calibration Blocks for Angle Beam Examination	4

FIGURE

1	Ultrasonic Standard Reference Block.....	2
2	Basic Calibration Block for Angle Beam Examination	4

ANNEX

A	Referenced Standards and Applicable Dates	7
---	-------------------------------------------------	---

QUALITY STANDARD FOR FERRITIC AND MARTENSITIC STEEL CASTINGS FOR VALVES, FLANGES, FITTINGS, AND OTHER PIPING COMPONENTS

ULTRASONIC EXAMINATION METHOD

1. SCOPE

1.1 This Standard Practice provides methods and acceptance standards for ultrasonic examination of ferritic and martensitic steel castings for valves, flanges, fittings, and other piping components. It is applicable to examination of repairs as well as to the initial examination of castings.

1.2 The methods of Section 8 describe uniform procedures which will provide satisfactory and consistent results upon which the acceptance standards of Section 11 may be used.

1.3 It is recognized that ultrasonic examination and radiographic examination are not directly comparable. This Standard Practice is intended to provide a casting of functionally equivalent quality to those accepted by the method of MSS SP-54.

2. DEFINITIONS

For definitions of terms relating to ultrasonic testing see ASTM E 1316.

3. BASIS FOR USE

Critical sections of pressure containing castings shall be examined ultrasonically. These sections will be selected by the purchaser of the castings on the basis of previous experience. They may be considered critical in any one of three senses:

- a) Casting solidification
- b) Stress concentration
- c) Ability to contain pressure

4. EQUIPMENT

4.1 *Electronic Apparatus*

4.1.1 An ultrasonic, pulsed, reflection type of instrument which shall be capable of generating, receiving, and amplifying frequencies of at least 1 MHz to 5MHz.

4.1.2 The ultrasonic equipment shall provide linear presentation (within ± 5 percent) for at least 75 percent of the screen height (sweep line to top of screen). Linearity shall be determined in accordance with ASTM E 317 or equivalent electronic means.

4.1.3 The electronic apparatus shall contain a single attenuator or calibrated gain control which shall be accurate over its useful range to ± 10 percent of the nominal attenuation or gain ratio to allow measurement of signals beyond the linear range of the instrument.

4.2 *Search Units*

4.2.1 Longitudinal Wave internally grounded search units having 1/2 to 1-1/8 inch (13mm to 29mm) diameter or 1 inch (25mm) square piezo electric elements shall be used. Based on the signal to noise ratio of the response pattern of the casting, a frequency in the range of 1MHz to 5MHz shall be used. The background noise shall not exceed 25 percent of the distance amplitude correction (DAC) curve. Transducers shall be utilized at their rated frequencies.

4.2.2 Dual element 5MHz search units are recommended for sections 1 inch (25mm) and under in thickness.

4.2.3 Angle beam search units shall produce a shear wave beam in steel in the range of 40° to 75° inclusive, measured to the perpendicular of the entry surface of the casting being examined and have a frequency of 1MHz to 5MHz.

4.2.4 Other frequencies and sizes of search units may be used for evaluating and pinpointing indications.

4.3 *Reference Blocks*

4.3.1 Reference blocks shall be used to establish test sensitivity.

4.3.2 Reference blocks shall be made from cast steels that give an acoustic response similar to the castings being examined.