



Item No. 21066

Joint Surface Preparation Standard

NACE No. 2/SSPC-SP 10 Near-White Metal Blast Cleaning

This NACE International (NACE)/The Society for Protective Coatings (SSPC) standard represents a consensus of those individual members who have reviewed this document, its scope, and provisions. It is intended to aid the manufacturer, the consumer, and the general public. Its acceptance does not in any respect preclude anyone, whether he or she has adopted the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not addressed in this standard. Nothing contained in this NACE/SSPC standard is to be construed as granting any right, by implication or otherwise, to manufacture, sell, or use in connection with any method, apparatus, or product covered by Letters Patent, or as indemnifying or protecting anyone against liability for infringement of Letters Patent. This standard represents current technology and should in no way be interpreted as a restriction on the use of better procedures or materials. Neither is this standard intended to apply in all cases relating to the subject. Unpredictable circumstances may negate the usefulness of this standard in specific instances. NACE and SSPC assume no responsibility for the interpretation or use of this standard by other parties and accept responsibility for only those official interpretations issued by NACE or SSPC in accordance with their governing procedures and policies which preclude the issuance of interpretations by individual volunteers.

Users of this NACE/SSPC standard are responsible for reviewing appropriate health, safety, environmental, and regulatory documents and for determining their applicability in relation to this standard prior to its use. This NACE/SSPC standard may not necessarily address all potential health and safety problems or environmental hazards associated with the use of materials, equipment, and/or operations detailed or referred to within this standard. Users of this NACE/SSPC standard are also responsible for establishing appropriate health, safety, and environmental protection practices, in consultation with appropriate regulatory authorities if necessary, to achieve compliance with any existing applicable regulatory requirements prior to the use of this standard.

CAUTIONARY NOTICE: NACE/SSPC standards are subject to periodic review, and may be revised or withdrawn at any time in accordance with technical committee procedures. The user is cautioned to obtain the latest edition. NACE and SSPC require that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of initial publication.

Reaffirmed 2006-09-13
Reaffirmed 1999-09-07
Approved October 1994

ISBN 1-57590-108-0

©2006, SSPC: The Society for Protective Coatings and NACE International

NACE International
1440 South Creek Dr.
Houston, TX 77084-4906
(telephone +1 281/228-6200)

SSPC: The Society for Protective Coatings
40 24th Street, Sixth Floor
Pittsburgh, PA 15222
(telephone +1 412/281-2331)

Printed by NACE International

Foreword

This joint standard covers the use of blast cleaning abrasives to achieve a defined degree of cleaning of steel surfaces prior to the application of a protective coating or lining system. This standard is intended for use by coating or lining specifiers, applicators, inspectors, or others who may be responsible for defining a standard degree of surface cleanliness.

The focus of this standard is near-white metal blast cleaning. White metal blast cleaning, commercial blast cleaning, industrial blast cleaning, and brush-off blast cleaning are addressed in separate standards.

Near-white metal blast cleaning provides a greater degree of cleaning than commercial blast cleaning (NACE No. 3/SSPC-SP 6¹) but less than white metal blast cleaning (NACE No. 1/SSPC-SP 5²).

Near-white metal blast cleaning is used when the objective is to remove all rust, coating, and mill scale, but when the extra effort required to remove all stains of these materials is determined to be unwarranted. Staining shall be limited to no more than 5 percent of each unit area of surface.

Near-white metal blast cleaning allows staining on only 5 percent of each unit area of surface, while commercial blast cleaning allows staining on 33 percent of each unit area of surface. White metal blast cleaning does not permit any staining to remain on the surface.

This joint standard was originally prepared in 1994 and reaffirmed in 1999 by the SSPC/NACE Task Group (TG) A on Surface Preparation by Abrasive Blast Cleaning, and NACE Unit Committee T-6G on Surface Preparation. This joint TG includes members of both the SSPC Surface Preparation Committee and the NACE Unit Committee T-6G on Surface Preparation. It was reaffirmed in 2006 by NACE Specific Technology Group (STG) 04, Protective Coatings and Linings: Surface Preparation, and the SSPC Surface Preparation Committee.

In NACE/SSPC standards, the terms *shall*, *must*, *should*, and *may* are used in accordance with Paragraph 2.2.1.8 of the Agreement Between NACE International and SSPC: The Society for Protective Coatings. The terms *shall* and *must* are used to state mandatory requirements. The term *should* is used to state something considered good and is recommended but is not mandatory. The term *may* is used to state something considered optional.

NACE No. 2/SSPC-SP 10

Joint Surface Preparation Standard

NACE No. 2/SSPC-SP 10 Near-White Metal Blast Cleaning

Contents

1. General	1
2. Definitions	1
3. Associated Documents	1
4. Procedures Before Cleaning	1
5. Blast Cleaning Methods and Operation	2
6. Blast Cleaning Abrasives	2
7. Procedures Following Blast Cleaning and Immediately Prior to Coating	2
8. Inspection	3
9. Safety and Environmental Requirements	3
10. Comments (Nonmandatory).....	3
References.....	3
Appendix A: Explanatory Notes (Nonmandatory).....	4

Section 1: General

1.1 This joint standard covers the requirements for near-white metal blast cleaning of uncoated or coated steel surfaces by the use of abrasives. These requirements include the end condition of the surface and materials and procedures necessary to achieve and verify the end condition.

1.2 The mandatory requirements are described in Sections 1 to 9. Section 10, "Comments," and Appendix A,

"Explanatory Notes," are not mandatory requirements of this standard.

1.3 Information about the function of near-white metal blast cleaning is in Paragraph A1 of Appendix A.

1.4 Information about use of this standard in maintenance coating work is in Paragraph A2 of Appendix A.

Section 2: Definitions

2.1 Near-White Metal Blast Cleaned Surface: A near-white metal blast cleaned surface, when viewed without magnification, shall be free of all visible oil, grease, dust, dirt, mill scale, rust, coating, oxides, corrosion products, and other foreign matter. Random staining shall be limited to no more than 5 percent of each unit area of surface (approximately 5,800 mm² [9.0 in.²] (i.e., a square 76 mm x 76 mm [3.0 in. x 3.0 in.]), and may consist of light shadows, slight streaks, or minor discolorations caused by stains of rust, stains of mill scale, or stains of previously applied coating.

2.1.1 Acceptable variations in appearance that do not affect surface cleanliness as defined in Paragraph

2.1 include variations caused by the type of steel, original surface condition, thickness of the steel, weld metal, mill or fabrication marks, heat treating, heat-affected zones, blasting abrasives, and differences because of blasting technique.

2.1.2 SSPC-VIS 1³ may be specified to supplement the written definition. In any dispute, the written definition set forth in this standard shall take precedence over reference photographs and comparators. Additional information on reference photographs and comparators is in Paragraph A3 of Appendix A.

Section 3: Associated Documents

3.1 The latest issue, revision, or amendment of the documents listed in Paragraph 3.3 in effect on the date of invitation to bid shall govern unless otherwise specified.

3.2 If there is a conflict between the requirements of any of the documents listed in Paragraph 3.3 and this standard, the requirements of this standard shall prevail.

3.3 Documents cited in the mandatory sections of this standard include:

Document	Title
SSPC-AB 1 ⁴	Mineral and Slag Abrasives
SSPC-AB 2 ⁵	Cleanliness of Recycled Ferrous Metallic Abrasives
SSPC-AB 3 ⁶	Ferrous Metallic Abrasives
SSPC-SP 1 ⁷	Solvent Cleaning
SSPC-VIS 1	Guide and Reference Photographs for Steel Surfaces Prepared by Dry Abrasive Blast Cleaning

Section 4: Procedures Before Cleaning

4.1 Before blast cleaning, visible deposits of oil, grease, or other contaminants shall be removed in accordance with SSPC-SP 1 or other agreed-upon methods.

4.2 Before blast cleaning, surface imperfections such as sharp fins, sharp edges, weld spatter, or burning slag should be removed from the surface to the extent required by the procurement documents (project specification).

Additional information on surface imperfections is in Paragraph A4 of Appendix A.

4.3 If reference photographs or comparators are specified to supplement the written standard, the condition of the steel prior to blast cleaning should be determined before the blasting commences. Additional information on reference