



Preparation, Installation, Analysis, and Interpretation of Corrosion Coupons in Oilfield Operations

This NACE International standard represents a consensus of those individual members who have reviewed this document, its scope, and provisions. Its acceptance does not in any respect preclude anyone, whether he or she has adopted the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not in conformance with this standard. Nothing contained in this NACE standard is to be construed as granting any right, by implication or otherwise, to manufacture, sell, or use in connection with any method, apparatus, or product covered by letters patent, or as indemnifying or protecting anyone against liability for infringement of letters patent. This standard represents minimum requirements and should in no way be interpreted as a restriction on the use of better procedures or materials. Neither is this standard intended to apply in all cases relating to the subject. Unpredictable circumstances may negate the usefulness of this standard in specific instances. NACE assumes no responsibility for the interpretation or use of this standard by other parties and accepts responsibility for only those official NACE interpretations issued by NACE in accordance with its governing procedures and policies which preclude the issuance of interpretations by individual volunteers.

Users of this NACE standard are responsible for reviewing appropriate health, safety, environmental, and regulatory documents and for determining their applicability in relation to this standard prior to its use. This NACE standard may not necessarily address all potential health and safety problems or environmental hazards associated with the use of materials, equipment, and/or operations detailed or referred to within this standard. Users of this NACE standard are also responsible for establishing appropriate health, safety, and environmental protection practices, in consultation with appropriate regulatory authorities if necessary, to achieve compliance with any existing applicable regulatory requirements prior to the use of this standard.

CAUTIONARY NOTICE: NACE standards are subject to periodic review, and may be revised or withdrawn at any time in accordance with NACE technical committee procedures. NACE requires that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of initial publication and subsequently from the date of each reaffirmation or revision. The user is cautioned to obtain the latest edition. Purchasers of NACE standards may receive current information on all standards and other NACE publications by contacting the NACE *FirstService* Department, 15835 Park Ten Place, Houston, TX 77084-5145 (telephone +1 281-228-6200).

ABSTRACT

This standard outlines procedures for preparing, installing, and analyzing metallic corrosion coupons. Factors considered in the interpretation of results obtained from these corrosion coupons are also included for the use of oil and service industry personnel. This standard is maintained by TG 409.

KEYWORDS

coupons, corrosion, oil and gas.

Foreword

In NACE standards, the terms “shall,” “must,” “should,” and “may” are used in accordance with the definitions of these terms in the NACE Publications Style Manual. The terms “shall” and “must” are used to state a requirement, and are considered mandatory. The term “should” is used to state something good and is recommended, but is not considered mandatory. The term “may” is used to state something considered optional.

This standard practice was prepared to encourage the use of uniform and industry-proven methods to monitor mass-loss and pitting corrosion in oilfield operations. This standard outlines procedures for preparing, installing, and analyzing metallic corrosion coupons. Factors considered in the interpretation of results obtained from these corrosion coupons are also included for the use of oil and service industry personnel.

This standard was originally prepared in 1975 by NACE Task Group T-1C-6, a component of Unit Committee T-1C on Detection of Corrosion in Oil Field Equipment, to provide procedures for the preparation, installation, and analysis of corrosion coupons. It was revised by Task Group T-1C-11 in 1986 and by T-1C-23 in 1991. T-1C was combined with Unit Committee T-1D on Corrosion Monitoring and Control of Corrosion Environments in Petroleum Production Operations, and this standard was revised by Task Group T-1D-54 in 1999. It was reaffirmed in 2005 and in 2012 by Specific Technology Group (STG) 31 on Oil and Gas Production—Corrosion and Scale Inhibition. This standard is issued by NACE International under the auspices of STG 31.

NACE International Standard Practice (SP0775-2018)

Preparation, Installation, Analysis, and Interpretation of Corrosion Coupons in Oilfield Operations

1. General	4
2. Processing of Corrosion Coupons	5
3. Installation of Corrosion Coupons	10
4. Recording Data on Corrosion Coupon Report	14
5. Interpretation of Corrosion Coupon Data	14
References.....	16
Appendix A: Typical Corrosion Coupon Report (Nonmandatory).....	17

Tables

Table 1: Density of Metals.....	8
Table 2: Qualitative Categorization of Carbon Steel Corrosion Rates for Oil Production Systems.....	16

Figures

Figure 1: Circular (washer-type) coupon and typical mounting in a ring joint flange... 10	10
Figure 2: Drill pipe corrosion ring coupon.....	11
Figure 3: Flat coupon holder	11
Figure 4: Round (rod-type) coupon holder	12
Figure 5: Tool for installing and removing coupons in systems under pressure.....	12
Figure 6: Extractor tool for inserting and removing coupons in systems under pressure.....	13
Figure 7: Wire-line-operated tubing stop adapted as downhole coupon holder	13
Figure 8: Choice of location for coupon installation and interpretation of coupon corrosion rate measurements.....	14

Section 1: General

- 1.1** This standard is presented for the use of corrosion coupons in oilfield drilling, production, and transportation operations. Oilfield operations include oil-, water-, and gas-handling systems, and drilling fluids. (When used in this standard, system denotes a functional unit such as a producing well; flowline and tank battery; water, oil, or gas collection facility; water or gas injection facility; or a gas dehydration or sweetening unit.) Corrosion coupon testing consists of the exposure of a small specimen of metal (the coupon) to an environment of interest for a period of time to determine the reaction of the metal to the environment. Corrosion coupons are used to evaluate corrosiveness of various systems, to monitor the effectiveness of corrosion-mitigation programs, and to evaluate the suitability of different metals for specific systems and environments. The coupons may be installed in the system itself or in a special test loop or apparatus. Corrosion rates shown by coupons and most other corrosion-monitoring devices seldom duplicate the actual rate of corrosion on the system piping and vessels. Accurate system corrosion rates can be determined by nondestructive measurement methods or failure frequency curves. Data furnished by corrosion coupons and other types of monitors must be related to system requirements. High corrosion rates on coupons may be used to verify the need for corrective action. If a corrosion-mitigation program is initiated and subsequent coupon data indicate that corrosion has been reduced, the information can be used to approximate the effectiveness of the mitigation program. This standard does not contain information on monitoring for intergranular corrosion, stress corrosion cracking (SCC), or sulfide stress cracking (SSC). The latter aspects are discussed elsewhere.^{1,2}
- 1.2** This standard describes preparation and handling techniques for metal coupons prior to and following exposure. Corrosion rate calculations and a typical form for recording data are also included.
- 1.3** Coupon size, metal composition, surface condition, and coupon holders may vary according to the test system design or the user's requirements. Coupons are often installed in pairs for simultaneous removal and average mass-loss determination. Coupons may be used alone but they should be used in conjunction with other monitoring methods such as test nipples, hydrogen probes, galvanic probes, polarization instruments, resistance-type corrosion monitors, chemical analysis of process streams and nondestructive metal thickness measurements, caliper surveys, and corrosion failure records.
- 1.4** Corrosion coupons used as recommended in this standard measure the total metal loss during the exposure period. They show corrosion that has already occurred. A single coupon cannot be used to determine whether the rate of metal loss was uniform or varying during the exposure period. Information on the change in corrosion rate can be obtained by installing several coupons at one time and removing and evaluating individual coupons at specific short-term intervals. Other monitoring methods mentioned in Paragraph 1.3 can be used to provide more accurate information on short-term rates of corrosion. Data provided by corrosion coupons can provide excellent backup for "event-indicating" corrosion-monitoring instruments.
- 1.5** In addition to mass loss, important factors to consider in the analysis and interpretation of coupon data include location, time on stream, measured pit depth, surface profile (blistering, erosion), corrosion product and/or scale composition, and operating factors (e.g., downtime, system flow velocities, upsets, or inhibition).