



NACE Standard RP0204-2004  
Item No. 21104

## Standard Recommended Practice

# Stress Corrosion Cracking (SCC) Direct Assessment Methodology

This NACE International (NACE) standard represents a consensus of those individual members who have reviewed this document, its scope, and provisions. Its acceptance does not in any respect preclude anyone, whether he has adopted the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not in conformance with this standard. Nothing contained in this NACE standard is to be construed as granting any right, by implication or otherwise, to manufacture, sell, or use in connection with any method, apparatus, or product covered by Letters Patent, or as indemnifying or protecting anyone against liability for infringement of Letters Patent. This standard represents minimum requirements and should in no way be interpreted as a restriction on the use of better procedures or materials. Neither is this standard intended to apply in all cases relating to the subject. Unpredictable circumstances may negate the usefulness of this standard in specific instances. NACE assumes no responsibility for the interpretation or use of this standard by other parties and accepts responsibility for only those official NACE interpretations issued by NACE in accordance with its governing procedures and policies which preclude the issuance of interpretations by individual volunteers.

Users of this NACE standard are responsible for reviewing appropriate health, safety, environmental, and regulatory documents and for determining their applicability in relation to this standard prior to its use. This NACE standard may not necessarily address all potential health and safety problems or environmental hazards associated with the use of materials, equipment, and/or operations detailed or referred to within this standard. Users of this NACE standard are also responsible for establishing appropriate health, safety, and environmental protection practices, in consultation with appropriate regulatory authorities if necessary, to achieve compliance with any existing applicable regulatory requirements prior to the use of this standard.

CAUTIONARY NOTICE: NACE standards are subject to periodic review, and may be revised or withdrawn at any time without prior notice. NACE requires that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of initial publication. The user is cautioned to obtain the latest edition. Purchasers of NACE standards may receive current information on all standards and other NACE publications by contacting the NACE Membership Services Department, 1440 South Creek Dr., Houston, Texas 77084-4906 (telephone +1 281/228-6200).

Approved 2004-11-15

NACE International  
1440 South Creek Dr.  
Houston, Texas 77084-4906  
+1 (281)228-6200

ISBN 1-57590-191-9  
© 2004, NACE International

---

## Foreword

Stress corrosion cracking direct assessment (SCCDA) is a structured process that is intended to assist pipeline companies in assessing the extent of stress corrosion cracking (SCC) on a section of buried pipeline and thus contribute to their efforts to improve safety by reducing the impact of external SCC on pipeline integrity. Primary guidance for assessing the structural integrity of a pipeline that has a significant risk of containing stress corrosion cracks is provided in Part A3 of ASME<sup>(1)</sup> B31.8S,<sup>1</sup> which identifies several options for inspection and mitigation activities. The recommended practice for SCCDA presented in this standard addresses the situation in which a pipeline company has identified a portion of its pipeline as an area of interest with respect to SCC based on its history, operations, and risk assessment process and has decided that direct assessment is an appropriate approach for integrity assessment. This standard provides guidance for managing SCC by selecting potential pipeline segments, selecting dig sites within those segments, inspecting the pipe and collecting and analyzing data during the dig, establishing a mitigation program, defining the reevaluation interval, and evaluating the effectiveness of the SCCDA process.

This standard recommended practice is intended for use by pipeline operators and others who must manage pipeline integrity for the threat of SCC. SCCDA as described in this standard is specifically intended to address buried onshore petroleum (natural gas, crude oil, and refined products) production, transmission, and distribution pipelines constructed from line-pipe steels. Users of this standard must be familiar with all applicable pipeline safety regulations for the jurisdiction in which the pipeline operates. This includes all regulations requiring specific pipeline integrity assessment practices and programs.

This standard was prepared by NACE Task Group (TG) 273 on Stress Corrosion Cracking Direct Assessment, External. TG 273 is administered by Specific Technology Group (STG) 35 on Pipelines, Tanks, and Well Casings. This standard is issued by NACE under the auspices of STG 35.

In NACE standards, the terms *shall*, *must*, *should*, and *may* are used in accordance with the definitions of these terms in the NACE Publications Style Manual, 4th ed., Paragraph 7.4.1.9. *Shall* and *must* are used to state mandatory requirements. The term *should* is used to state something good and is recommended but is not mandatory. The term *may* is used to state something considered optional.

---

<sup>(1)</sup> ASME International (ASME), Three Park Avenue, New York, NY 10016-5990.

RP0204-2004

---

## Standard Recommended Practice

# Stress Corrosion Cracking (SCC) Direct Assessment Methodology

### Contents

1. General .....	1
2. Definitions .....	4
3. Pre-Assessment.....	7
4. Indirect Inspections .....	12
5. Direct Examinations .....	13
6. Post Assessment .....	19
7. SCCDA Records .....	20
References.....	21
Appendix A.....	22
Appendix B.....	23
Appendix C .....	25
Figure 1: Flow Chart for SCCDA Process .....	3
Table 1: Factors to Consider in Prioritization of Susceptible Segments and in Site Selection for SCCDA .....	8
Table 2: Data Collected at a Dig Site in an SCCDA Program and Relative Importance..	13
Table A1: Description of "Stress Corrosion Cracking-Susceptible" Terrain Conditions for Polyethylene Tape-Coated Pipeline (Based on Findings of CEPA Member Companies) .....	22
Table A2: Description of "Stress Corrosion Cracking-Susceptible" Terrain Conditions for Some Asphalt/Coal Tar Enamel Coated Pipelines (Based on Findings of CEPA Member Companies) .....	23
Table B1: Summary of Surface Preparation Techniques Prior to MPI .....	24
Table B2: Comparison of Surface Preparation Techniques vs. Detection Limits and Costs .....	24
Table C1: Advantages and Disadvantages of Various MPI Methods.....	26

## Section 1: General

### 1.1 Introduction

1.1.1 This standard covers the NACE SCCDA process for buried steel pipeline systems. It is intended to serve as a guide for applying the NACE SCCDA process on typical petroleum (natural gas, crude oil, and refined products) pipeline systems. Background information can be obtained from NACE Publication 35103.<sup>2</sup>

1.1.2 SCCDA as described in this standard is specifically intended to address buried onshore petroleum (natural gas, crude oil, and refined products) pipelines constructed from line-pipe steel.

1.1.2.1 This procedure is designed to be applied to both forms of external SCC (near-neutral-pH SCC and high-pH SCC) on these pipelines.

1.1.3 SCCDA requires the integration of data from historical records, indirect surveys, field examinations, and pipe surface evaluations (i.e., direct examination) combined with the physical characteristics and operating history of the pipeline.

1.1.4 This standard was written as a flexible guideline for an operator to tailor the SCCDA process to specific pipeline situations. Nothing in this standard is intended to preclude modifications that tailor the SCCDA process to specific pipeline situations and operators.

1.1.5 SCCDA is a continuous improvement process. Through successive applications, SCCDA should identify and address locations where SCC has occurred, is occurring, or might occur.

1.1.5.1 SCCDA provides the advantage and benefit of indicating areas where SCC might occur in the future rather than only areas where SCC is known to exist.

1.1.5.2 Comparing the results of successive SCCDA applications is one method of evaluating SCCDA effectiveness and demonstrating that confidence in the integrity of the pipeline is continuously improving.

1.1.6 SCCDA was developed as a process for improving pipeline safety. Its primary purpose is to reduce the threat of external SCC on pipeline integrity by means of condition monitoring, mitigation, documentation, and reporting.

1.1.6.1 This standard assumes SCC is a threat to

be evaluated. It can be used to establish a baseline from which future SCC can be assessed for pipelines on which SCC is not currently a significant threat.

1.1.7 SCCDA is complementary with other inspection methods such as in-line inspection (ILI) or hydrostatic testing and is not necessarily an alternative or replacement for these methods in all instances. SCCDA also is complementary with other direct assessment procedures such as those given in the proposed NACE standard recommended practice on internal corrosion direct assessment (ICDA) methodology.<sup>4</sup>

1.1.7.1 ILI or hydrostatic testing might not be warranted if the initial SCCDA assessment indicates that "significant" and extensive cracking is not present on a pipeline system.

1.1.7.2 SCCDA can be used to prioritize a pipeline system for ILI or hydrostatic testing if significant and extensive SCC is found.

1.1.8 SCCDA may detect other pipeline integrity threats, such as mechanical damage, external corrosion, etc. When such threats are detected, additional assessments and/or inspections shall be performed. The pipeline operator shall utilize appropriate methods such as ASME B31.8S,<sup>1</sup> ASME B31.4,<sup>5</sup> ASME B31.8,<sup>6,7</sup> API<sup>(2)</sup> 1160,<sup>8</sup> NACE standards, international standards, and other documents to address risks other than external SCC.

1.1.9 SCCDA can be applied to most onshore petroleum pipelines, regardless of the coating system. Precautions should be taken when applying these techniques just as with other assessment methods.

1.1.10 Given the diversity of pipelines and their operation, this standard recognizes that SCCDA may be inappropriate for some situations because of the complexity of conditions to which buried pipeline systems are exposed.

1.1.11 The provisions of this standard shall be applied under the direction of competent persons who, by reason of knowledge of the physical sciences and the principles of engineering, geosciences, and mathematics, acquired by education and related practical experience, are qualified to engage in the practice of corrosion control, integrity management, and risk assessment on buried steel pipeline systems.

<sup>(2)</sup> American Petroleum Institute (API), 1220 L St. NW, Washington, DC 20005.