

NACE Standard RP0286-2002 Item No. 21032

Standard Recommended Practice

Electrical Isolation of Cathodically Protected Pipelines

This NACE International standard represents a consensus of those individual members who have reviewed this document, its scope, and provisions. Its acceptance does not in any respect preclude anyone, whether he has adopted the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not in conformance with this standard. Nothing contained in this NACE International standard is to be construed as granting any right, by implication or otherwise, to manufacture, sell, or use in connection with any method, apparatus, or product covered by Letters Patent, or as indemnifying or protecting anyone against liability for infringement of Letters Patent. This standard represents minimum requirements and should in no way be interpreted as a restriction on the use of better procedures or materials. Neither is this standard intended to apply in all cases relating to the subject. Unpredictable circumstances may negate the usefulness of this standard in specific instances. NACE International assumes no responsibility for only those official NACE International interpretations issued by NACE International in accordance with its governing procedures and policies which preclude the issuance of interpretations by individual volunteers.

Users of this NACE International standard are responsible for reviewing appropriate health, safety, environmental, and regulatory documents and for determining their applicability in relation to this standard prior to its use. This NACE International standard may not necessarily address all potential health and safety problems or environmental hazards associated with the use of materials, equipment, and/or operations detailed or referred to within this standard. Users of this NACE International standard are also responsible for establishing appropriate health, safety, and environmental protection practices, in consultation with appropriate regulatory authorities if necessary, to achieve compliance with any existing applicable regulatory requirements prior to the use of this standard.

CAUTIONARY NOTICE: NACE International standards are subject to periodic review, and may be revised or withdrawn at any time without prior notice. NACE International requires that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of initial publication. The user is cautioned to obtain the latest edition. Purchasers of NACE International standards may receive current information on all standards and other NACE International publications by contacting the NACE International Membership Services Department, 1440 South Creek Dr., Houston, Texas 77084-4906 (telephone +1[281]228-6200).

Reaffirmed 2002-04-11 Revised 1997-June-27 Approved 1986 NACE International 1440 South Creek Drive Houston, Texas 77084-4906 +1 281/228-6200

ISBN 1-57590-041-6 © 2002, NACE International This is a preview of "NACE Standard RP0286...". Click here to purchase the full version from the ANSI store.

RP0286-2002

Foreword

This standard recommended practice is to be used in conjunction with the latest revisions of NACE Standards RP0169¹ and RP0177.² Each of these standards refers to electrical isolation or isolation joints, but details are not provided. This standard, which was prepared to supplement those standards, provides engineers, designers, and technical personnel dealing with pipelines the necessary information to isolate cathodically protected pipelines electrically.

This standard was originally prepared in 1986 and revised in 1997 by former Task Group T-10A-15 on Electrical Isolation of Cathodically Protected Pipelines, a component of Unit Committee T-10A on Cathodic Protection. The standard was reaffirmed in 2002 by Specific Technology Group (STG) 35 on Pipelines, Tanks, and Well Casings. It is issued by NACE International under the auspices of STG 35.

In NACE Standards, the terms *shall, must, should*, and *may* are used in accordance with the definitions of these terms in the NACE Publications Style Manual, 4th ed., Paragraph 7.4.1.9. *Shall* and *must* are used to state mandatory requirements. The term *should* is used to state something good and is recommended but is not mandatory. The term *may* is used to state something considered optional.

This is a preview of "NACE Standard RP0286...". Click here to purchase the full version from the ANSI store.

RP0286-2002

NACE International Standard Recommended Practice

Electrical Isolation of Cathodically Protected Pipelines

Contents

1. General	. 1
2. Need for Isolation	. 1
3. Methods of Isolation	. 1
4. Isolation from Other Metallic Structures	. 6
5. Selection of Isolation Device or Method	. 8
6. Equipment Specifications	
7. Equipment Installation	
8. Field Testing and Maintenance	
References	16
Figures	
Figure 1a: Full-Length Bolt Sleeves	
Figure 1b: One-Half-Length Bolt Sleeves	
Figure 2: Typical Isolating Monolithic Device	
Figure 3: Typical Isolating Monolithic Joint	
Figure 4: Typical Isolating Yoke-Type Device	
Figure 5: Typical Isolating Union	
Figure 6: Typical Isolating Spools	
Figure 7: Typical Isolating Couplings	
Figure 8: Typical Isolating Tapping Sleeve	
Figure 9: Typical Casing/Sleeve Installation	. 6
Figure 10: Typical Use of Isolating Devices at Each End of a Bridge for a Cathodically	
Protected Pipeline	
Figure 11: Isolating Joint Test Station	
Figure 12: Isolating Device Leakage Test	15

This is a preview of "NACE Standard RP0286...". Click here to purchase the full version from the ANSI store.

RP0286-2002

Section 1: General

1.1 This standard explains the importance of pipeline electrical isolation in achieving and maintaining adequate, reliable, and economical corrosion control. The standard outlines the types of devices used for isolation; precautions to be observed; and selection of devices based on pipeline characteristics, site, and contents. The standard describes isolating flanges, gaskets, sleeves, washers, joints, unions, couplings, and spools, and discusses materials for pipeline casing isolation. Installation, field testing, and maintenance of isolating devices are also included.

1.2 This standard describes the application of isolating devices intended only for cathodic protection purposes when voltages across the isolating device are 1 to 2 volts direct current (DC) and the alternating current (AC)

exposure does not exceed 15 volts root mean square (rms).³

1.3 This standard does not discuss situations in which isolating devices are incorporated purely for safety reasons; in those situations, reference should be made to relevant electrical safety codes. Isolating devices shall not be used in enclosed areas where combustible atmospheres are likely to be present.

1.4 Isolation of cathodically protected pipelines is recommended to minimize current requirements, facilitate testing and troubleshooting, and improve current distribution.

Section 2: Need for Isolation

2.1 Cathodic protection current intended for a given pipeline can flow to other underground facilities or equipment electrically connected to the pipeline. If protection of the other underground facilities is not intended, significant cathodic protection current can be lost unless preventive measures are taken. Generally called a current drain, this current loss can be reduced through electrical isolation of the pipeline.

2.2 Cathodic protection even of well-coated pipelines may not be economical or practical unless electrical isolation is achieved.

2.3 Pipeline casings should be electrically isolated from the carrier pipe.

2.4 If a pipeline passes through the wall of a valve pit or a building, metallic contact can occur between the pipe and the steel reinforcement in the concrete, causing a significant loss of protective current.

2.5 Electrical isolation can minimize or eliminate galvanic corrosion caused by dissimilar metals in contact with each other or caused by similar metals in contact with each other

when one metal is bare or has a dielectric coating system while the other has a permeable (e.g., concrete or mortar) coating system.

2.6 If a pipeline is designed to be electrically continuous but is supported by another metallic structure in contact with soil or groundwater, the pipeline should be isolated from that structure. The isolating supports must prevent damage to the pipeline coating and must accommodate relative movement, vibrations, and temperature differentials.

2.7 Isolation of power and instrumentation grounding systems may be required when electrically operated valves and similar components form part of a pipeline system. All applicable safety codes and standards must be followed.

2.8 If a pipeline is to be protected by more than one type of cathodic protection system, isolation of one or more sections may be desirable.

2.9 Isolation of pipelines can be beneficial in controlling or limiting the effect of stray currents such as telluric currents, currents associated with an electric traction system, or currents from nearby structures under cathodic protection.

Section 3: Methods of Isolation

3.1 Electrically isolating devices may be specially manufactured or prefabricated. It may be possible for existing fittings to be retrofitted with isolating materials to serve as isolating devices. Selection of the type of isolating device depends on the mechanical forces due to its position in the system, the operating temperature range, pressure constraints, and other considerations. Provisions should be

made for the connection of test wires for testing these isolating devices.

3.2 Flanges

3.2.1 A bolted pair of pipeline flanges may be converted into an electrically isolating device by