



NACE Standard RP0490-2001
Item No. 21045

Standard Recommended Practice

Holiday Detection of Fusion-Bonded Epoxy External Pipeline Coatings of 250 to 760 μm (10 to 30 mils)

This NACE International standard represents a consensus of those individual members who have reviewed this document, its scope, and provisions. Its acceptance does not in any respect preclude anyone, whether he has adopted the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not in conformance with this standard. Nothing contained in this NACE International standard is to be construed as granting any right, by implication or otherwise, to manufacture, sell, or use in connection with any method, apparatus, or product covered by Letters Patent, or as indemnifying or protecting anyone against liability for infringement of Letters Patent. This standard represents minimum requirements and should in no way be interpreted as a restriction on the use of better procedures or materials. Neither is this standard intended to apply in all cases relating to the subject. Unpredictable circumstances may negate the usefulness of this standard in specific instances. NACE International assumes no responsibility for the interpretation or use of this standard by other parties and accepts responsibility for only those official NACE International interpretations issued by NACE International in accordance with its governing procedures and policies which preclude the issuance of interpretations by individual volunteers.

Users of this NACE International standard are responsible for reviewing appropriate health, safety, environmental, and regulatory documents and for determining their applicability in relation to this standard prior to its use. This NACE International standard may not necessarily address all potential health and safety problems or environmental hazards associated with the use of materials, equipment, and/or operations detailed or referred to within this standard. Users of this NACE International standard are also responsible for establishing appropriate health, safety, and environmental protection practices, in consultation with appropriate regulatory authorities if necessary, to achieve compliance with any existing applicable regulatory requirements prior to the use of this standard.

CAUTIONARY NOTICE: NACE International standards are subject to periodic review, and may be revised or withdrawn at any time without prior notice. NACE International requires that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of initial publication. The user is cautioned to obtain the latest edition. Purchasers of NACE International standards may receive current information on all standards and other NACE International publications by contacting the NACE International Membership Services Department, 1440 South Creek Drive, Houston, Texas 77084-4906 (telephone +1 [281]228-6200).

Reaffirmed 2001-03-15
Approved April 1990
Reaffirmed March 1995
NACE International
1440 South Creek Drive
Houston, Texas 77084-4906
+ 1 (281) 228-6200

ISBN 1-57590-119-6
©2001, NACE International

Foreword

Detection and correction of defects in protective coatings are important factors in an effective corrosion control program. High-voltage electrical inspection of pipeline coatings prior to installation is one method in general use. Prior to issuance of this NACE International standard, there had been no U.S. standard for electrical inspection of fusion-bonded epoxy pipeline coatings. Although several specifications have been written by operating companies for high-voltage electrical inspection of protective coatings, they apply only to specific coatings. This standard is intended to serve the needs of pipeline owners, coating applicators, coating inspectors, and other interested parties in the electrical inspection of fusion-bonded epoxy pipe coatings.

This standard recommended practice was originally prepared by NACE International Work Group T-10D-9c on Electrical Inspection and its parent, Task Group T-10D-9 on Coating Inspection, a component of Unit Committee T-10D on Protective Coating Systems. Unit Committee T-10D reaffirmed the standard in 1995. This standard, now issued by NACE International under the auspices of Specific Technology Group (STG) 03 on Protective Coatings and Linings – Immersion/Buried, was developed through the joint efforts of representatives of coating manufacturers and applicators, holiday detector equipment manufacturers, corrosion specialists, and others concerned with the construction of underground pipeline facilities, as represented in STG 03. This standard was reaffirmed in 2001.

These recommendations apply only to fusion-bonded epoxy pipeline coatings, which are generally applied at a dry-film thickness of 250 to 760 μm (10 to 30 mils). For other types of patching materials and joint wrap, the manufacturer of the material should be consulted for holiday detection voltages. Conformance to the principles of this standard improves methods of holiday detection and, therefore, the effectiveness of the coating.

In NACE standard, the terms *shall*, *must*, *should* and *may* are used in accordance with the definitions of these terms in the *NACE Publications Style Manual*, 4th ed., Paragraph 7.4.1.9. *Shall* and *must* are used to state mandatory requirements. *Should* is used to state something considered good and is recommended but is not mandatory. *May* is used to state something considered optional.

RP0490-2001

**NACE International
Standard
Recommended Practice**

**Holiday Detection of Fusion-Bonded Epoxy External Pipeline
Coatings of 250 to 760 μm (10 to 30 mils)**

Contents

1. General	1
2. Definitions	1
3. Testing Voltages	1
4. Grounding	2
5. Exploring Electrode	3
6. Travel Speed of Exploring Electrode	3
7. Test Voltage Measurements	3
8. Condition of Coating Surface	3
9. Care of Equipment	4
References	4

Section 1: General

1.1 This standard presents recommended techniques in the operation of holiday detector equipment currently used on fusion-bonded epoxy (FBE) pipeline coatings prior to on-site installation of the pipeline. It also presents recommended voltages for various coating thicknesses. Guidelines for establishing minimum requirements to ensure proper application and performance of plant-applied, fusion-bonded epoxy coatings are presented in NACE Standard RP0394.¹

1.2 Electrical inspection (holiday detection) is a test of the continuity of a protective coating. This type of inspection is not intended to provide information on coating resistivity, bond, physical characteristics, or the overall quality of the coating. It detects voids, cracks, foreign inclusions, or contaminants in the coating that are

of such size, number, or conductivity to significantly lower the electrical resistance or dielectric strength of the coating.

1.3 Use of a holiday detector shall be under the direction of a qualified coating inspector, such as a NACE-certified coating inspector. An initial holiday detector inspection, performed as soon as practical after the application of the coating, assists in verifying conformance to specifications for the materials and the application procedures. Before the coated pipe is placed in the ground, a final electrical coating inspection discloses coating discontinuities or damage that may have occurred during the shipping, storage, or construction period.

Section 2: Definitions

Continuous Direct Current (DC) Voltage Holiday Detector: A holiday detector that supplies a continuous DC test voltage. The continuous DC-type holiday detector is often used in very arid, sandy, or rocky areas and in coating plants where moisture and contamination conditions are controlled. The continuous DC test voltage holiday detector cannot be used where continuous moisture is present on the surface of the coating. For proper inspection using continuous DC-output test voltage, other than in coating plant operations, the fusion-bonded epoxy coating surface must be dry.

Generated Test Voltages: With two types of commercially available detectors, generated-output test voltages are used for the electrical inspection of fusion-bonded epoxy pipeline coatings. They are commonly described as *pulse-DC* and *continuous-DC* test voltages.

Holiday: A discontinuity in a protective coating that exposes unprotected surface to the environment. For the purpose of this standard, the term is used interchangeably with *discontinuity*.

Holiday Detector: An electrical device that locates discontinuities in the protective coating.

Pulse-DC Voltage Holiday Detector: A holiday detector that supplies a high-DC voltage pulse of a very short duration (such as 0.0002 seconds at a rate of 30 pulses or more per second). The pulse-type holiday detector is the most common type used in the industry, and it can be used on damp or dry coatings.

Section 3: Testing Voltages

3.1 All holiday detector output test voltages in this standard refer to pulse-DC and continuous-DC values.

3.2 The minimum effective applied output test voltage is dependent on coating thickness, atmospheric conditions, electrode configuration, and grounding conditions. Therefore, the applied test voltage varies from case to case.

3.3 To determine the minimum effective applied test voltage for a given set of field conditions, the following field calibration should be performed daily:

3.3.1 Make a holiday 790 μm (0.031 in.) in diameter through the fusion-bonded epoxy coating. Ensure that the hole extends completely through the coating to the metal substrate.

3.3.2 Start with the lowest test voltage setting of the holiday detector and slowly increase the test voltage until the manufactured holiday can be positively detected at normal operating speeds (see Paragraphs 5.3 and 9.2 and Section 6).