



NACE SP0206-2006
Item No. 21112

Standard Practice

Internal Corrosion Direct Assessment Methodology for Pipelines Carrying Normally Dry Natural Gas (DG-ICDA)

This NACE International standard represents a consensus of those individual members who have reviewed this document, its scope, and provisions. Its acceptance does not in any respect preclude anyone, whether he or she has adopted the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not in conformance with this standard. Nothing contained in this NACE International standard is to be construed as granting any right, by implication or otherwise, to manufacture, sell, or use in connection with any method, apparatus, or product covered by Letters Patent, or as indemnifying or protecting anyone against liability for infringement of Letters Patent. This standard represents minimum requirements and should in no way be interpreted as a restriction on the use of better procedures or materials. Neither is this standard intended to apply in all cases relating to the subject. Unpredictable circumstances may negate the usefulness of this standard in specific instances. NACE International assumes no responsibility for the interpretation or use of this standard by other parties and accepts responsibility for only those official NACE International interpretations issued by NACE International in accordance with its governing procedures and policies which preclude the issuance of interpretations by individual volunteers.

Users of this NACE International standard are responsible for reviewing appropriate health, safety, environmental, and regulatory documents and for determining their applicability in relation to this standard prior to its use. This NACE International standard may not necessarily address all potential health and safety problems or environmental hazards associated with the use of materials, equipment, and/or operations detailed or referred to within this standard. Users of this NACE International standard are also responsible for establishing appropriate health, safety, and environmental protection practices, in consultation with appropriate regulatory authorities if necessary, to achieve compliance with any existing applicable regulatory requirements prior to the use of this standard.

CAUTIONARY NOTICE: NACE International standards are subject to periodic review, and may be revised or withdrawn at any time in accordance with NACE technical committee procedures. NACE International requires that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of initial publication. The user is cautioned to obtain the latest edition. Purchasers of NACE International standards may receive current information on all standards and other NACE International publications by contacting the NACE International FirstService Department, 1440 South Creek Dr., Houston, Texas 77084-4906 (telephone +1 281/228-6200).

Approved 2006-12-01
NACE International
1440 South Creek Dr.
Houston, Texas 77084-4906
+1 (281)228-6200

ISBN 1-57590-207-9
© 2006, NACE International

Foreword

This standard practice formalizes a methodology termed *internal corrosion direct assessment for pipelines carrying normally dry natural gas (DG-ICDA)*^{1,2,3} that can be used to help ensure pipeline integrity. The methodology is applicable to natural gas pipelines that normally carry dry gas, but may suffer from infrequent, short-term upsets of liquid water (or other electrolyte). This standard is intended for use by pipeline operators and others who manage pipeline integrity.

The basis of DG-ICDA is a detailed examination of locations along a pipeline where water would first accumulate and provides information about the downstream condition of the pipeline. If the locations along a length of pipe most likely to accumulate water have not corroded, other downstream locations less likely to accumulate water may be considered free from corrosion. The presence of extensive corrosion found at many locations during the evaluation suggests that the transported gas was not normally dry, and this standard is not considered applicable.

DG-ICDA methodology for natural gas systems is described in terms of a four-step process. The DG-ICDA method provides the greatest benefit for pipelines that cannot be in-line inspected; however, the method is not limited to unpiggable pipelines. Sample field data are provided in Appendix A (nonmandatory) to illustrate an example application of DG-ICDA. Appendix B (nonmandatory) provides example region definitions.

This standard was prepared by Task Group (TG) 293 on Pipeline Direct Assessment Methodology. TG 293 is administered by Specific Technology Group (STG) 35 on Pipelines, Tanks, and Well Casings. This standard is issued by NACE International under the auspices of STG 35.

In NACE standards, the terms *shall*, *must*, *should*, and *may* are used in accordance with the definitions of these terms in the NACE Publications Style Manual, 4th ed., Paragraph 7.4.1.9. *Shall* and *must* are used to state mandatory requirements. The term *should* is used to state something good and is recommended but is not mandatory. The term *may* is used to state something considered optional.

SP0206-2006

NACE International Standard Practice

Internal Corrosion Direct Assessment Methodology for Pipelines Carrying Normally Dry Natural Gas (DG-ICDA)

Contents

1. General	1
2. Definitions	5
3. Pre-Assessment.....	6
4. Indirect Inspection.....	9
5. Detailed Examinations	11
6. Post Assessment	13
7. DG-ICDA Records	13
References	14
Bibliography.....	15
Appendix A: Example DG-ICDA Application (Nonmandatory).....	16
Appendix B: Example Region Definition (Nonmandatory)	21
Figure 1a: Dry Gas Internal Corrosion Direct Assessment Flow Chart	2
Figure 1b: Dry Gas Internal Corrosion Direct Assessment Flow Chart	3
Figure 1c: Dry Gas Internal Corrosion Direct Assessment Flow Chart.....	4
Figure A1: Example inclination and elevation profiles, with critical inclination angles	18
Figure A2: Example inclination profile, gas flowing south to north (first 6.4 km [4 miles]).....	19
Figure A3: Example inclination profile, gas flowing north to south (first 6.2 km [3.9 miles]).....	20
Figure B1: Illustration of ICDA Region Definitions	21
Table 1: Essential Data for Use of DG-ICDA Methodology	7
Table A1: Example Conditions.....	17
Table A2: Example—Inspection Results.....	19

Section 1: General

1.1 Introduction

1.1.1 This standard covers the NACE internal corrosion direct assessment (ICDA) process for normally dry natural gas pipeline systems. This standard is intended to serve as a guide for applying the NACE DG-ICDA process on natural gas pipeline systems that meet the feasibility requirements of Paragraph 3.3 of this standard.

1.1.2 The primary purposes of the DG-ICDA method are (1) to enhance the assessment of internal corrosion in natural gas pipelines, and (2) to ensure pipeline integrity.

1.1.3 DG-ICDA was developed for natural gas pipelines that normally carry dry gas, but may suffer from infrequent short-term upsets of water. Because of this, DG-ICDA is not applicable to wet gathering and producing pipelines.

1.1.4 One benefit of the DG-ICDA approach is that an assessment can be performed on a pipe segment for which alternative methods (e.g., in-line inspection (ILI), hydrostatic testing, etc.) may not be practical.

1.1.5 The basis of DG-ICDA for gas lines is a detailed examination of locations along a pipeline where water or other electrolyte first accumulates, allowing inferences to be made about the integrity of the remaining downstream length of pipe.

1.1.6 If the locations along a length of pipe that are most likely to accumulate water have not corroded, other locations less likely to accumulate water are unlikely to have suffered corrosion when operating under the same conditions.

1.1.7 Identifying areas in which internal corrosion (or the potential for future internal corrosion) exists, and conversely, where internal corrosion is unlikely, may also be incorporated into corrosion integrity and risk management plans.

1.1.8 In the process of applying DG-ICDA, other pipeline integrity threats, such as external corrosion, mechanical damage, stress corrosion cracking (SCC), etc., may be detected. When such threats are detected, additional assessments or inspections must be performed. The pipeline operator should utilize appropriate methods to address risks other than internal corrosion, such as those described in NACE

standards, ASME⁽¹⁾ B31.8,⁴ API⁽²⁾ 1160,⁵ ANSI⁽³⁾/API 579,⁶ and BS⁽⁴⁾ 7910,⁷ international standards, and other documents.

1.1.9 The DG-ICDA methodology assesses the likelihood of internal corrosion and includes existing methods of examination available to a pipeline operator to determine whether internal corrosion is actually present, or may occur.

1.1.10 DG-ICDA uses flow modeling results and provides a framework to utilize those methods.

1.1.11 DG-ICDA has limitations, and not all pipelines can be successfully assessed with DG-ICDA. These limitations are identified in the pre-assessment step. For accurate and correct application of this standard, it shall be used in its entirety. Using or referring to only specific paragraphs or sections can lead to misinterpretation or misapplication of the recommendations and practices contained herein.

1.1.12 This standard does not designate practices for every specific situation because of the complexity of internal conditions that may be present in various pipeline systems.

1.1.13 This standard does not address specific remedial actions that may be taken when corrosion is found; however, the reader is referred to ASME B31.8⁴ and other relevant documents for guidance.

1.1.14 The provisions of this standard shall be applied by or under the direction of competent persons who, by reason of knowledge of the physical sciences and the principles of engineering and mathematics, acquired by education and related practical experience, are qualified to engage in the practice of corrosion control and risk assessment on pipeline systems. Such persons may be (1) registered professional engineers, (2) recognized as corrosion specialists by organizations such as NACE, or (3) professionals (i.e., engineers or technicians) with professional experience including detection/mitigation of internal corrosion and evaluation of internal corrosion on pipelines.

1.2 Four-Step Process

1.2.1 DG-ICDA requires the integration of data from multiple field examinations and internal pipe surface evaluations, including the pipeline's physical characteristics and operating history.

⁽¹⁾ ASME International (ASME), Three Park Ave., New York, NY, 10016-5990.

⁽²⁾ American Petroleum Institute (API), 1220 L St. NW, Washington, DC 20005.

⁽³⁾ American National Standards Institute (ANSI), 11 W. 42nd St., New York, NY 10036.

⁽⁴⁾ British Standards Institute (BSI), British Standards House, 389 Chiswick High Rd., London W4 4AL, United Kingdom.