



**NACE SP0273-2007
(formerly RP0273)
Item No. 21009**

Standard Practice

Handling and Proper Usage of Inhibited Oilfield Acids

This NACE International standard represents a consensus of those individual members who have reviewed this document, its scope, and provisions. Its acceptance does not in any respect preclude anyone, whether he or she has adopted the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not in conformance with this standard. Nothing contained in this NACE International standard is to be construed as granting any right, by implication or otherwise, to manufacture, sell, or use in connection with any method, apparatus, or product covered by Letters Patent, or as indemnifying or protecting anyone against liability for infringement of Letters Patent. This standard represents minimum requirements and should in no way be interpreted as a restriction on the use of better procedures or materials. Neither is this standard intended to apply in all cases relating to the subject. Unpredictable circumstances may negate the usefulness of this standard in specific instances. NACE International assumes no responsibility for the interpretation or use of this standard by other parties and accepts responsibility for only those official NACE International interpretations issued by NACE International in accordance with its governing procedures and policies which preclude the issuance of interpretations by individual volunteers.

Users of this NACE International standard are responsible for reviewing appropriate health, safety, environmental, and regulatory documents and for determining their applicability in relation to this standard prior to its use. This NACE International standard may not necessarily address all potential health and safety problems or environmental hazards associated with the use of materials, equipment, and/or operations detailed or referred to within this standard. Users of this NACE International standard are also responsible for establishing appropriate health, safety, and environmental protection practices, in consultation with appropriate regulatory authorities if necessary, to achieve compliance with any existing applicable regulatory requirements prior to the use of this standard.

CAUTIONARY NOTICE: NACE International standards are subject to periodic review, and may be revised or withdrawn at any time in accordance with NACE technical committee procedures. NACE International requires that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of initial publication and subsequently from the date of each reaffirmation or revision. The user is cautioned to obtain the latest edition. Purchasers of NACE International standards may receive current information on all standards and other NACE International publications by contacting the NACE International First Service Department, 1440 South Creek Dr., Houston, Texas 77084-4906 (telephone +1 281/228-6200).

Reaffirmed 2007-03-11
Reaffirmed 2001-03-15
Revised March 1995
Approved 1973
NACE International
1440 South Creek Drive
Houston, Texas 77084-4906
+1 281/228-6200

ISBN 1-57590-122-6
© 2007, NACE International

Foreword

Acid solutions are often used to improve the production of fluids from, or injection of fluids in, subterranean formations. The most commonly used acid is hydrochloric acid and solutions thereof, and these solutions are hazardous to personnel and are very corrosive to metal equipment. This standard practice outlines methods and procedures for the handling and use of inhibited hydrochloric acid for oilfield applications. It is intended for individuals who wish to supplement their understanding of oilfield acidizing processes or who handle or use inhibited acids in oilfield operations.

This standard was originally prepared in 1973 by the API⁽¹⁾/NACE Subcommittee on Oilfield Acid Corrosion Inhibitor Evaluation and jointly issued as API Bulletin D-15 (now withdrawn) and NACE Standard RP0273-73. This standard was revised in 1995 by NACE Task Group T-1D-37, a component of Unit Committee T-1D on Corrosion Monitoring and Control of Corrosion Environments in Petroleum Production Operations. It was reaffirmed in 2001 and 2007 by Specific Technology Group (STG) 31 on Oil and Gas Production—Corrosion and Scale Inhibition and is issued by NACE International under the auspices of STG 31.

In NACE standards, the terms *shall*, *must*, *should*, and *may* are used in accordance with the definitions of these terms in the *NACE Publications Style Manual*, 4th ed., Paragraph 7.4.1.9. *Shall* and *must* are used to state mandatory requirements. *Should* is used to state something considered good and is recommended but is not mandatory. *May* is used to state something considered optional.

⁽¹⁾ American Petroleum Institute (API), 1220 L Street NW, Washington, DC 20005.

SP0273-2007

NACE International Standard Practice

Handling and Proper Usage of Inhibited Oilfield Acids

Contents

1. General.....	1
2. General Guidelines for Using Inhibited Acid in Wells.....	1
3. Field Test of Oilfield Acids for Presence or Absence of Corrosion Inhibitors.....	3
4. Laboratory Test for Solubility-Dispersibility of Corrosion Inhibitors in Oilfield Acids	5
5. References	6
Figures	
Figure 1: Preloaded test ampoule, which is submerged in the test position in glass beaker of water.....	4

Section 1: General

1.1 This standard presents guidelines for minimizing acid corrosion, including general corrosion, pitting, and stress corrosion cracking (SCC), in the oil field. Topics covered include preparation of the well, preparation of the acid solution, acid solution pumping and injection, and return fluids handling.

1.2 This standard presents a field test of oilfield acids of 15% or less concentration for the presence or absence of corrosion inhibitors.

1.3 This standard presents a laboratory test for solubility-dispersibility of corrosion inhibitors in oilfield acids.

Section 2: General Guidelines for Using Inhibited Acid in Wells

2.1 This section provides guidelines that should be followed to minimize acid corrosion problems including general corrosion, pitting, and SCC. Guidelines pertaining to preparation of the well, preparation of the acid, injection of the acid, and subsequent cleanup of the well are presented. While all these guidelines may not be applicable for each acid treatment, the merits of each should be weighed carefully.

2.2 Well Preparation Guidelines

2.2.1 Pipe Conditions: The condition of the pipe in the well should be examined for evidence of corrosion or scaling. Leaks may result from the removal of scale or corrosion products and not from acid corrosion of pipe material. Effects of the acid solution on downhole nonmetallic materials (e.g., plastic-coated or cement-lined tubular goods) should be considered.

2.2.2 Metallic Material Precautions: Acid inhibitors do not protect certain metals from corrosion by acid solutions. Consideration should be given to removal of galvanized metal, aluminum, magnesium, and chrome-plated metal from the well prior to initiating treatment. Stainless steel may be susceptible to SCC. Acetic acid can be inhibited for use in the presence of chrome-plated metal, stainless steels, and aluminum, but cannot be adequately inhibited for use in the presence of magnesium or galvanized metal.

2.2.3 Leak Check: Precautions should be taken to ensure that the tubing string and the packer do not leak. If acid solution becomes trapped in the annular space, it can cause damage even if the acid initially was properly inhibited. Severe damage resulting from trapped acid cannot be attributed to lack of inhibitor or inhibitor failure.

2.2.4 Hydrogen Sulfide (H₂S) Precautions: Although inorganic acids can cause general corrosion and SCC, H₂S may contribute to increasing corrosiveness and SCC of metals. Therefore, sour fluids should be displaced to prevent contamination of the acid solution with H₂S. In addition, H₂S can be produced by acid contact with iron sulfide present on the pipe surface. Inorganic inhibitors can be precipitated by H₂S.

Organic inhibitors are preferred for H₂S service although they too can be adversely affected by H₂S.

2.2.5 Well Cooling Considerations: Consideration should be given to the practice of cooling a very hot well by injecting oil or water ahead of the acid solution to lower the temperature of the tubular goods. However, precautions should be taken so that the tubular goods will not be cooled to the point of tensile failure or packer release. If the well cannot be cooled below 163°C (325°F), use of organic acids should be considered. These organic acids can be effectively inhibited for safe use above 204°C (400°F).

2.2.6 Displacement into Formation: If possible, an acceptable pump-in rate should be established in advance using an inert fluid such as oil or water. This procedure makes certain that the formation is open to receive the acid solution to prevent trapping of acid in the tubular goods with no means to effectively displace the acid solution.

2.2.7 Vent Piping: Piping shall be arranged to prevent venting of gases near the wellhead or anywhere rig operators or other personnel may be present. This is especially important if any sulfide or arsenic compounds are present in the well. Personnel must be warned that H₂S and arsine gases are heavier than air and tend to collect in low spots (gullies, draws, ravines, etc.), creating a lethal environment. Lethal amounts of H₂S or arsine gas can be produced (1) when wells containing sulfides or arsenic materials are acidized, or (2) when acid containing arsenic materials is being used. If the possibility of H₂S or arsine gas exists, testing equipment and appropriate safety equipment shall be on hand to monitor the working area and protect personnel in the area. Special scrubbing equipment may be required for removal of toxic gases.

2.2.8 Arsenic Inhibitor Precautions: Arsenic inhibitors are still occasionally used in acidizing deep, hot wells. Many refineries use catalysts that can be severely damaged by traces of arsenic in the parts-per-billion range. Some pipelines and refineries refuse delivery of production containing trace quantities of arsenic. When use of an arsenic inhibitor is being considered,