



NACE Standard TM0294-2001
Item No. 21225

Standard Test Method

Testing of Embeddable Impressed Current Anodes for Use in Cathodic Protection of Atmospherically Exposed Steel-Reinforced Concrete

This NACE International standard represents a consensus of those individual members who have reviewed this document, its scope, and provisions. Its acceptance does not in any respect preclude anyone, whether he has adopted the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not in conformance with this standard. Nothing contained in this NACE International standard is to be construed as granting any right, by implication or otherwise, to manufacture, sell, or use in connection with any method, apparatus, or product covered by Letters Patent, or as indemnifying or protecting anyone against liability for infringement of Letters Patent. This standard represents minimum requirements and should in no way be interpreted as a restriction on the use of better procedures or materials. Neither is this standard intended to apply in all cases relating to the subject. Unpredictable circumstances may negate the usefulness of this standard in specific instances. NACE International assumes no responsibility for the interpretation or use of this standard by other parties and accepts responsibility for only those official NACE International interpretations issued by NACE International in accordance with its governing procedures and policies which preclude the issuance of interpretations by individual volunteers.

Users of this NACE International standard are responsible for reviewing appropriate health, safety, environmental, and regulatory documents and for determining their applicability in relation to this standard prior to its use. This NACE International standard may not necessarily address all potential health and safety problems or environmental hazards associated with the use of materials, equipment, and/or operations detailed or referred to within this standard. Users of this NACE International standard are also responsible for establishing appropriate health, safety, and environmental protection practices, in consultation with appropriate regulatory authorities if necessary, to achieve compliance with any existing applicable regulatory requirements prior to the use of this standard.

CAUTIONARY NOTICE: NACE International standards are subject to periodic review, and may be revised or withdrawn at any time without prior notice. NACE International requires that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of initial publication. The user is cautioned to obtain the latest edition. Purchasers of NACE International standards may receive current information on all standards and other NACE International publications by contacting the NACE International Membership Services Department, 1440 South Creek Dr., Houston, Texas 77084-4906 (telephone +1[281]228-6200).

Reaffirmed 2001-09-05
Approved March 1994
NACE International
1440 South Creek Drive
Houston, Texas 77084-4906
+1 281/228-6200

ISBN 1-57590-133-1
©2001, NACE International

Foreword

This NACE International standard has been prepared to provide users and manufacturers of embeddable anodes with a test method for evaluating the anode material to an expected lifetime criterion. It is applicable to embeddable anode materials, such as titanium mesh, commonly used for cathodic protection of atmospherically exposed steel-reinforced concrete. The test is intended to evaluate whether an embeddable anode material complies with minimum required specifications of design life expectancy at rated current output. This test method is not applicable to surface-mounted anodes or conductive coating materials.

This NACE International test method was originally prepared in 1994 by Task Group T-3K-6 on Test Procedure for Anodes Used in Concrete, a component of Unit Committee T-3K on Corrosion and Other Deterioration Phenomena Associated with Concrete. It was reviewed by Task Group (TG) 045 on Anodes Test Procedures and reaffirmed in 2001 by Specific Technology Group (STG) 01 on Concrete and Rebar. TG 045 is administered by STG 01 and sponsored by STG 05 on Cathodic/Anodic Protection. This standard is issued by NACE International under the auspices of STG 01.

In NACE standards, the terms *shall*, *must*, *should*, and *may* are used in accordance with the definitions of these terms in the *NACE Publications Style Manual*, 4th ed., Paragraph 7.4.1.9. *Shall* and *must* are used to state mandatory requirements. The term *should* is used to state something good and is recommended but is not mandatory. The term *may* is used to state something considered optional.

TM0294-2001

**NACE International
Standard
Test Method**

**Testing of Embeddable Impressed Current Anodes for Use in
Cathodic Protection of Atmospherically Exposed Steel-
Reinforced Concrete**

Contents

1. General	1
2. Definitions	2
3. Solution Preparation.....	2
4. Test Apparatus.....	3
5. Test Procedure	5
6. Acceptance Criterion.....	5
7. Reporting Test Results	5
References.....	5
Figures	
Figure 1: Test Cell with Luggin Probe Anode Potential Measurement Set-Up	3
Figure 2: Series Electrical Hook-Up for Duplicate Evaluations	4
Tables	
Table 1: Typical Results of Anode Life Testing 30 g/L NaCl Solution.....	6
Table 2: Typical Results of Anode Life Testing 40 g/L NaOH Solution.....	7
Table 3: Typical Results of Anode Life Testing Simulated Pore Water Solution	8

Section 1: General

1.1 Accelerated testing of anodes for use in concrete is intended to provide an indication of an anode's ability to perform satisfactorily for a specific number of years. Unfortunately, accelerated "life testing" cannot be conducted in concrete because testing at high current levels results in premature failure of the concrete as the test electrolyte. Accelerated life testing must therefore be conducted in an aqueous solution.

1.1.1 When using accelerated life tests, anodes shall be demonstrated to survive a minimum total charge density of 38,500 A-h/m² (3,580 A-h/ft²) of actual anode surface area. This is the amount of total charge density an anode is subjected to if operated at a current density of 110 mA/m² (10 mA/ft²) of anode surface for 40 years. If an anode is designed to operate at any other current density, the test should be modified to reflect the charge density equivalent to 40 years of operating life.

1.1.2 Under certain circumstances the user may require a greater total charge density than 38,500 A-h/m² (3,580 A-h/ft²) of anode surface, because of a longer life requirement than 40 years, or because of a higher operating current density. In these cases, the test may be extended or the charge density increased until the desired charge is met.

1.2 It is possible that a cathodic protection anode may be incorrectly powered cathodically during the initial system energization. This condition may not be noticed by merely observing the rectifier meters and can remain undetected until the depolarization test is performed after several days of operation. It is also possible that an anode may be exposed to current reversal caused by an electrical short between the anode and the steel. In this case, the anode is subjected to cathodic current until the system is energized and tested, sometimes several months later. In view of these possibilities and the serious implications of damage to the anode, the ability of the anode to survive a brief current reversal must be ensured.

1.2.1 Assuming the anode is operated at a reversed current density of 110 mA/m² (10 mA/ft²) of anode surface for a period of one month, the anode experiences approximately 71 A-h/m² (6.6 A-h/ft²) of cathodic charge density. It shall be tested to endure such a current reversal and then continue to provide an equivalent of at least 40 years, or 38,500 A-h/m² (3,580 A-h/ft²) of anode surface, of protection.

1.3 The anodic portion of life testing shall be conducted over a period of at least 180 days.

1.4 Life testing shall be conducted using a constant-current, filtered DC power supply having a maximum ripple of 5%.

1.5 Accelerated life testing shall be conducted in duplicate in the following aqueous solutions:

1.5.1 30 g/L of sodium chloride in distilled or deionized water

1.5.1.1 Cathodic protection anodes are often used to protect bridge piers and pilings in seawater and therefore are exposed to this chloride environment. This solution tests the ability of anodes to tolerate the chlorine evolution reaction.

1.5.2 40 g/L of sodium hydroxide in distilled or deionized water

1.5.2.1 This solution, though at a higher pH than concrete, is conductive enough to nullify effects of solution changes. The solution also tests the ability of the anode to tolerate oxygen evolution, a reaction more favored at low current density and the low chloride contamination level experienced with fresh overlays.

1.5.3 Simulated pore water in sand

1.5.3.1 The electrolyte available to the anode in a cured concrete structure is pore water. This solution tests the ability of the anode to tolerate the actual concentrations of the pore water components and any possible synergistic effects imposed by these components. The use of fine sand to encompass the electrode, eliminating convective mixing, tests the ability of the anode to tolerate the situation most closely simulating its operation in cured concrete. The composition by mass of simulated pore water used shall be as follows:

0.20% Ca(OH)₂
3.20% KCl
1.00% KOH
2.45% NaOH
93.15% distilled or deionized water

1.6 Failure of the anode shall be determined by loss of the electrochemical activity as evidenced by an increase in anode potential as defined in Paragraph 5.2.