



NACE Standard TM0190-2012  
Item No. 21221

## Standard Test Method

# Impressed Current Laboratory Testing of Aluminum and Zinc Alloy Anodes

This NACE International standard represents a consensus of those individual members who have reviewed this document, its scope, and provisions. Its acceptance does not in any respect preclude anyone, whether he or she has adopted the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not in conformance with this standard. Nothing contained in this NACE International standard is to be construed as granting any right, by implication or otherwise, to manufacture, sell, or use in connection with any method, apparatus, or product covered by Letters Patent, or as indemnifying or protecting anyone against liability for infringement of Letters Patent. This standard represents minimum requirements and should in no way be interpreted as a restriction on the use of better procedures or materials. Neither is this standard intended to apply in all cases relating to the subject. Unpredictable circumstances may negate the usefulness of this standard in specific instances. NACE International assumes no responsibility for the interpretation or use of this standard by other parties and accepts responsibility for only those official NACE International interpretations issued by NACE International in accordance with its governing procedures and policies which preclude the issuance of interpretations by individual volunteers.

Users of this NACE International standard are responsible for reviewing appropriate health, safety, environmental, and regulatory documents and for determining their applicability in relation to this standard prior to its use. This NACE International standard may not necessarily address all potential health and safety problems or environmental hazards associated with the use of materials, equipment, and/or operations detailed or referred to within this standard. Users of this NACE International standard are also responsible for establishing appropriate health, safety, and environmental protection practices, in consultation with appropriate regulatory authorities if necessary, to achieve compliance with any existing applicable regulatory requirements prior to the use of this standard.

**CAUTIONARY NOTICE:** NACE International standards are subject to periodic review, and may be revised or withdrawn at any time in accordance with NACE technical committee procedures. NACE International requires that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of initial publication and subsequently from the date of each reaffirmation or revision. The user is cautioned to obtain the latest edition. Purchasers of NACE International standards may receive current information on all standards and other NACE International publications by contacting the NACE International *FirstService* Department, 1440 South Creek Dr., Houston, TX 77084-4906 (telephone +1 281-228-6200).

Revised 2012-10-05  
Reaffirmed 2006-07-18  
Revised 1998-06-26  
Approved April 1990  
NACE International  
1440 South Creek Drive  
Houston, TX 77084-4906  
+1 281-228-6200

ISBN 1-57590-060-2  
©2012, NACE International

This is a preview of "NACE TM0190-2012". [Click here to purchase the full version from the ANSI store.](#)

---

## Foreword

This standard test method describes a quality assurance procedure for determining the potential and current capacity characteristics under laboratory conditions for aluminum and zinc alloy anodes used for cathodic protection (CP). Field performance of anodes should be evaluated to correspond to actual anode performance.

This standard is intended primarily for users, designers, and manufacturers involved with the application of CP in marine environments. This standard can be used by manufacturers and users of aluminum and zinc anodes for quality control verification. The most common usage is expected to be by manufacturers to meet quality control requirements requested by the purchasing user. This standard is based on experiences from the paper by J.F. Brown Jr., —Quality Control Testing of Aluminum Anodes: T-7L-2 Task Group Progress Report,<sup>1</sup> and from ANSI/NACE SP0607/ISO 15589-2,<sup>2</sup> and Military Specification MIL-A-18001.<sup>3</sup>

This standard was originally prepared in 1990 by NACE International Task Group T-7L-2 on Aluminum Anode Quality Control, a component of Unit Committee T-7L on Cathodic Protection, in conjunction with ASTM<sup>(1)</sup> Task Group G01-09-02 T-1. This standard was revised by Task Group T-7L-12 in 1998, and was reaffirmed by Specific Technology Group (STG) 30, —Oil and Gas Production: Cathodic Protection,” in 2006, and was revised in 2012 by Task Group (TG) 459, —Review and Revise as Necessary NACE Standard TM0190-2006.” It is issued by NACE under the auspices of STG 30. These committees are composed of industry representatives, including producers, consumers, and interested individuals.

In NACE standards, the terms *shall*, *must*, *should*, and *may* are used in accordance with the definitions of these terms in the *NACE Publications Style Manual*. The terms *shall* and *must* are used to state a requirement, and are considered mandatory. The term *should* is used to state something good and is recommended, but is not considered mandatory. The term *may* is used to state something considered optional.

---

<sup>(1)</sup> ASTM International, 100 Barr Harbor Dr., West Conshohocken, PA 19428-2959.

TM0190-2012

---

**NACE International  
Standard Test Method**

**Impressed Current Laboratory Testing of  
Aluminum and Zinc Alloy Anodes**

**Contents**

1. General.....	1
2. Summary of Test Method.....	2
3. Test Apparatus.....	2
4. Reagents.....	5
5. Preparation of Test Specimens.....	6
6. Preparation of Apparatus for Test.....	6
7. Procedure.....	7
8. Calculation of Efficiency.....	8
References.....	9
FIGURES	
Figure 1: Hydrogen Evolution Test Set-Up.....	3
Figure 2: Alternate Test Cell Set-Up (Without Hydrogen Evolution Test).....	4
Figure 3: Sacrificial Copper Plate and Copper Coulometer.....	4
Figure 4: Wiring Diagram.....	5
TABLES	
Table 1: Nominal Alloy Composition Ranges for Anodes Tested.....	1
Table 2: Range of Evaluation Results.....	1

---

**Section 1: General**

1.1 This standard test method describes a laboratory procedure for determining the potential and current capacity characteristics of aluminum and zinc alloy anodes used for CP. It provides a means for screening various heats or lots of anodes to determine performance consistency on a regular basis from lot to lot. Items such as sampling frequency and performance criteria (i.e., test values and intermediate times) are left to the discretion of the user of the test method.

1.2 One test method for anode potential evaluation and two test methods for anode current capacity evaluations are described.

1.3 The actual values obtained in these tests should not be used for design purposes because they represent laboratory testing.

1.4 This procedure can be validated by using zinc anode samples as a reference in the test to verify results of aluminum anodes tested. Zinc samples shall be as defined in ASTM B418<sup>4</sup> or Military Specification MIL-A-18001 for zinc anodes.

1.5 This procedure was evaluated by testing alloys of Al-Zn-Sn, Al-Zn-Hg, Al-Zn-In-Mg, and MIL-A-18001 zinc of the respective nominal alloy composition ranges shown in Table 1. The results of the test are reported in Paper No. 346 presented at CORROSION/84.

1.6 The precision of the test has not been validated. The scatter in the test results is considered to result from heterogeneities in aluminum alloy anode materials in general, as tested, rather than the test method itself. Only anode materials exhibiting good, reproducible performance (in accordance with this test method) and meeting manufacturer or user specifications are acceptable.

1.6.1 Ranges of performance from those alloys tested are listed in Table 2.

**Table 1  
Nominal Alloy Composition Ranges for Anodes Tested (%)**

	Al-Zn-Sn	Al-Zn-Hg	Al-Zn-In-Mg	Zinc (MIL-A-18001)
Zn	6.0 to 8.0	1.25 to 2.00	1.0 to 3.0	Remainder
Sn	0.10 to 0.20	—	—	—
Si	—	—	—	0.125 max.
Hg	—	0.030 to 0.08	—	—
Pb	—	—	—	0.006 max.
Mg	—	—	0.50 to 1.0	—
In	—	—	0.20	—
Fe	0.10 max.	0.10 max.	0.10 max.	0.005 max.
Cd	—	—	—	0.025 to 0.15
Cu	0.003 max.	0.003 max.	0.010 max.	0.005 max.
Al	Remainder	Remainder	Remainder	0.10 to 0.50

**Table 2  
Range of Evaluation Results**

Alloy	Operating Potential (SCE <sup>(A)</sup> -mV)	Hydrogen Evolution (% Efficiency)	Impressed Current Capacity	
			A-h/kg	A-h/lb
Al-Zn-Sn	940 to 1,176	70 to 94	1,014 to 2,711	460 to 1,230
Al-Zn-Hg	830 to 1,114	96	2,623 to 2,949	1,190 to 1,338
Al-Zn-In-Mg	1,032 to 1,140	90	2,354 to 2,742	1,068 to 1,244
Zinc	969 to 1,051	98	754 to 804	342 to 365

<sup>(A)</sup> Saturated calomel electrode.