



NACE TM0294-2016
Item No. 21225

Standard Test Method

Testing of Embeddable Impressed Current Anodes for Use in Cathodic Protection of Atmospherically Exposed Steel-Reinforced Concrete

This NACE International (NACE) standard represents a consensus of those individual members who have reviewed this document, its scope, and provisions. Its acceptance does not in any respect preclude anyone, whether he or she has adopted the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not in conformance with this standard. Nothing contained in this NACE standard is to be construed as granting any right, by implication or otherwise, to manufacture, sell, or use in connection with any method, apparatus, or product covered by letters patent, or as indemnifying or protecting anyone against liability for infringement of letters patent. This standard represents minimum requirements and should in no way be interpreted as a restriction on the use of better procedures or materials. Neither is this standard intended to apply in all cases relating to the subject. Unpredictable circumstances may negate the usefulness of this standard in specific instances. NACE assumes no responsibility for the interpretation or use of this standard by other parties and accepts responsibility for only those official NACE interpretations issued by NACE in accordance with its governing procedures and policies which preclude the issuance of interpretations by individual volunteers.

Users of this NACE standard are responsible for reviewing appropriate health, safety, environmental, and regulatory documents and for determining their applicability in relation to this standard prior to its use. This NACE standard may not necessarily address all potential health and safety problems or environmental hazards associated with the use of materials, equipment, and/or operations detailed or referred to within this standard. Users of this NACE standard are also responsible for establishing appropriate health, safety, and environmental protection practices, in consultation with appropriate regulatory authorities if necessary, to achieve compliance with any existing applicable regulatory requirements prior to the use of this standard.

CAUTIONARY NOTICE: NACE standards are subject to periodic review, and may be revised or withdrawn at any time in accordance with NACE technical committee procedures. NACE requires that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of initial publication and subsequently from the date of each reaffirmation or revision. The user is cautioned to obtain the latest edition. Purchasers of NACE standards may receive current information on all standards and other NACE publications by contacting the NACE *FirstService* Department, 15385 Park Ten Place, Houston, TX 77084-5145 (telephone +1 281-228-6200).

Revised 2015-11-28
Revised 2007-06-22
Reaffirmed 2001-09-05
Approved March 1994
NACE International
15385 Park Ten Place
Houston, Texas 77084-5145
+1 281-228-6200
ISBN 1-57590-133-1
©2015, NACE International

Foreword

This NACE International test method has been prepared to provide users and manufacturers of embeddable anodes with a test method for evaluating the anode material to an expected lifetime criterion. It is applicable to embeddable anode materials, such as titanium (Ti) mesh, commonly used for cathodic protection (CP) of atmospherically exposed steel-reinforced concrete.

This test method presents two methods for evaluating the anode material; Test Method Part A is intended to evaluate whether an embeddable anode material complies with minimum required specifications of design life expectancy at rated current output. Test Method Part B is a quicker test to ensure that a sample from a particular batch of material is suitable. Test Method Part B shall only be conducted on samples of a product that has passed Test Method Part A for the required design life. The test methods are not applicable to surface-mounted anodes or conductive coating materials.

The test method was originally prepared in 1994 by Task Group (TG) T-3K-6, "Test Procedure for Anodes Used in Concrete," a component of Unit Committee T-3K, "Corrosion and Other Deterioration Phenomena Associated with Concrete." It was reviewed by TG 045, "Anodes Test Procedures" and reaffirmed in 2001 by Specific Technology Group (STG) 01, "Concrete and Rebar." It was revised by TG 045 in 2007 and in 2015 by TG 472 (new designation). TG 472 is administered by STG 01, "Reinforced Concrete"; and sponsored by STG 05, "Cathodic/Anodic Protection." This standard is issued by NACE under the auspices of STG 01.

In NACE standards, the terms *shall*, *must*, *should*, and *may* are used in accordance with the definitions of these terms in the *NACE Publications Style Manual*. The terms *shall* and *must* are used to state a requirement, and are considered mandatory. The term *should* is used to state something good and is recommended, but is not considered mandatory. The term *may* is used to state something considered optional.

TM0294-2016

**NACE International
Standard Test Method**

**Testing of Embeddable Impressed Current Anodes for
Use in Cathodic Protection of Atmospherically
Exposed Steel-Reinforced Concrete**

Contents

1. General	1
2. Definitions	1
3. Test Method Part A	2
4. Solutions Preparation	3
5. Test Apparatus	4
6. Test Procedure.....	6
7. Anode Failure.....	7
8. Reporting Test Results	7
9. Test Method Part B	10
10. General Operation	12
11. Reporting Test Results	13
References.....	13
FIGURES	
Figure 1a: Test Cell with Luggin Probe Anode Potential Measurement Setup.....	4
Figure 1b: Test Cell with Current Reversal Anode Setup.....	5
Figure 2: Series Electrical Hookup for Duplicate Evaluations	6
Figure 3: Schematic of Standard Test Cell.....	12
Figure 4: Schematic Representation of Linear Potential vs Time Plot Showing Curve Leading to Failure of the Anode.....	13
TABLES	
Table 1: Typical Results of Anode Life Testing 30g/L NaCl Solution.....	8
Table 2 Typical Results of Anode Life Testing 40 g/L NaOH Solution	9
Table 3 Typical Results of Anode Life Testing Simulated Pore Water Solutions	10

Section 1: General

1.1 Accelerated testing of anodes for use in concrete is intended to provide an indication of an anode's ability to perform satisfactorily for a specific number of years. Unfortunately, accelerated life testing cannot be conducted in concrete because testing at high-current levels results in premature failure of the concrete as the test electrolyte. Accelerated life testing must therefore be conducted in an aqueous solution.

1.2 Test Method Part A is designed to evaluate the anode material to an expected lifetime criterion, and is conducted over a period of at least 180 days. (See Section 3.)

1.3 Test Method Part B uses accelerated life testing to verify that anodes comprised of a Ti substrate, to which a mixed metal oxide (MMO) catalytic coating has been applied, meet minimum service-life requirements in accordance with the expected design life. The test is operated at higher current densities than the application's design to accelerate the time to failure. (See Section 8.)

1.3.1 The minimum test period is 65 hours for anodes with an expected design life of 100 years at a maximum current density of 108 mA/m² (10 mA/ft²).

1.3.2 The minimum test period is 78 hours for anodes with an expected design life of 120 years at a maximum current density of 108 mA/m² (10 mA/ft²).

Section 2: Definitions

Accelerated life: The lifetime of an MMO anode under accelerated testing condition, usually in the specific electrolyte applied with large current density. The total period of testing until the deactivation of the MMO anode is taken as the accelerated life.

Cell voltage: Voltage between anode and cathode in a single cell.

Charge density: The product of applied current density multiplied by operating time.

Mixed metal oxide (MMO) anode: An impressed current anode for cathodic protection consisting of conductive coating of MMO formed on titanium substrate.

Luggin Probe: A device used in measuring the potential of an electrode with a significant current density imposed on its surface. (The probe minimizes the IR drop that would otherwise be included in the measurement and without significantly disturbing the current distribution on that electrode.)

Ripple: The alternating current (AC) component in the output of a direct current (DC) power supply, arising within the power supply from incomplete filtering or from commutator action in a DC generator.