



**NACE SP0104-2014
(formerly RP0104)
Item No. 21105**

Standard Practice

The Use of Coupons for Cathodic Protection Monitoring Applications

This NACE International (NACE) standard represents a consensus of those individual members who have reviewed this document, its scope, and provisions. Its acceptance does not in any respect preclude anyone, whether he or she has adopted the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not in conformance with this standard. Nothing contained in this NACE standard is to be construed as granting any right, by implication or otherwise, to manufacture, sell, or use in connection with any method, apparatus, or product covered by letters patent, or as indemnifying or protecting anyone against liability for infringement of letters patent. This standard represents minimum requirements and should in no way be interpreted as a restriction on the use of better procedures or materials. Neither is this standard intended to apply in all cases relating to the subject. Unpredictable circumstances may negate the usefulness of this standard in specific instances. NACE assumes no responsibility for the interpretation or use of this standard by other parties and accepts responsibility for only those official NACE interpretations issued by NACE in accordance with its governing procedures and policies which preclude the issuance of interpretations by individual volunteers.

Users of this NACE standard are responsible for reviewing appropriate health, safety, environmental, and regulatory documents and for determining their applicability in relation to this standard prior to its use. This NACE standard may not necessarily address all potential health and safety problems or environmental hazards associated with the use of materials, equipment, and/or operations detailed or referred to within this standard. Users of this NACE standard are also responsible for establishing appropriate health, safety, and environmental protection practices, in consultation with appropriate regulatory authorities if necessary, to achieve compliance with any existing applicable regulatory requirements prior to the use of this standard.

CAUTIONARY NOTICE: NACE standards are subject to periodic review, and may be revised or withdrawn at any time in accordance with NACE technical committee procedures. NACE requires that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of initial publication and subsequently from the date of each reaffirmation or revision. The user is cautioned to obtain the latest edition. Purchasers of NACE standards may receive current information on all standards and other NACE publications by contacting the NACE FirstService Department, 15838 Park Ten Place, Houston, TX 77084-5145 (telephone +1 281-228-6200).

Reaffirmed 2014-04-07
Approved 2004-12-03
NACE International
15835 Park Ten Place
Houston, Texas 77084-5145
+ 1 281-228-6200

ISBN 1-5790-196-X
©2014, NACE International

This is a preview of "NACE Standard SP0104...". [Click here to purchase the full version from the ANSI store.](#)

Foreword

Coupons are used to determine the level of corrosion protection provided by a cathodic protection (CP) system to a variety of structures, such as buried or submerged pipelines, underground storage tanks (USTs), aboveground (on-grade) storage tank bottoms, and steel in reinforced concrete structures. Structure-to-electrolyte potential measurements have long been used as the basis for assessing CP levels and compliance with CP criteria. It is well known that a voltage (IR) drop exists in the soil and across the coating, and that this IR drop produces an error in the structure-to-electrolyte potential measurement. This IR drop can be a function of reference electrode placement, soil resistivity, burial depth of the structure, coating condition, stray currents, local or long-line corrosion cells, and the amount of CP current applied.

CP coupons have been used since the 1930s by several pioneers of the corrosion-control industry, both in North America and in Europe. CP coupons have been shown to be a practical tool for determining the level of polarization of a structure and to confirm the IR drop in a potential measurement. Research sponsored by the pipeline industry has explored the use of CP coupons and has helped validate the use of this technology. The purpose of this standard practice is to provide a method for evaluating the effectiveness of a CP system using coupons. It is intended for use by people who design and maintain CP systems for buried or submerged pipelines, USTs, on-grade storage tank bottoms, reinforcing steel in concrete, water storage tanks, and various other structures in buried or aqueous environments.

The body of the standard primarily addresses applications for coupons attached to buried pipelines. Appendixes cover the use of coupons for other applications, including USTs, aboveground storage tanks (ASTs), internal surfaces of water tanks, and reinforced concrete structures.

This standard was originally prepared in 2004 by Task Group (TG) 210, "Coupon Technology for Cathodic Protection Applications." It was reaffirmed in 2014 by Specific Technology Group (STG) 35, "Pipelines, Tanks, and Well Casings." TG 210 is administered by STG 35 and is sponsored by STG 05, "Cathodic/Anodic Protection." This standard is issued by NACE under the auspices of STG 35.

In NACE standards, the terms *shall*, *must*, *should*, and *may* are used in accordance with the definitions of these terms in the *NACE Publications Style Manual*. The terms *shall* and *must* are used to state a requirement, and are considered mandatory. The term *should* is used to state something good and is recommended, but is not considered mandatory. The term *may* is used to state something considered optional.

SP0104-2014

**NACE International
Standard Practice**

**The Use of Coupons for Cathodic Protection Monitoring
Applications**

Contents

1. General	1
2. Definitions	1
3. Applications	2
4. Design of CP Coupons	4
5. Selection of CP Coupon Locations	6
6. Installation.....	7
7. Construction Precautions.....	10
8. Monitoring and Interpretation.....	10
9. Maintenance and Record Keeping	18
References.....	19
Bibliography	20
Appendix A.....	23
Appendix B.....	24
Appendix C.....	25
Appendix D.....	27
Figures	
Figure 1(a): Coupon with Cable Connections.....	5
Figure 1(b): Coupon with Built-In Reference Electrode	5
Figure 2(a): CP Coupon Test Station—End View.....	8
Figure 2(b): CP Coupon Test Station—Elevation	8
Figure 3: Possible Reference Electrode Placements	13
Figure 4: Typical Coupon Test Lead Measuring Schematic.....	15
Figure C1: Rebar Probe Installation.....	26
Tables	
Table 1: Equipment Commonly Used to Measure Coupons.....	11

Section 1: General

1.1 A CP coupon may be used to determine the level of CP of a buried or submerged metallic structure. CP coupons are installed in the electrolyte near the structure and are then connected to it through a test station. This allows the CP coupon to be connected to the CP system on the structure, thus simulating a similar-sized bare area of the structure's surface, such as at a holiday in the coating. The CP coupon may be disconnected from the circuit during periodic testing, and its instant-disconnect potential measured. The potential of the CP coupon may then continue to be monitored and the depolarization calculated. These measurements represent the polarized and depolarized potentials of the structure in the vicinity of the CP coupon. They also allow the IR drop in the electrolyte to be calculated for use in conventional potential measurements made from grade level. A second, freely corroding (native) coupon may be installed at the same location as the CP coupon to measure the free-corrosion potential of the structure in open-circuit conditions.

1.2 NACE SP0169¹ includes criteria for determining the CP status of a buried or submerged structure. For voltage measurements that are made when CP current is applied, IR drops other than those across the structure-to-electrolyte boundary must be considered. NACE SP0169 includes a number of ways this may be done and NACE Standard TM0497² includes a number of test methods used for these criteria. CP coupons may also be used to evaluate compliance with CP criteria, including considering the IR drop. The practices described in this standard must be followed with careful evaluation of the specific situation in which the coupons are to be used.

1.3 CP coupons have several advantages. Structure-to-electrolyte potentials that have the IR drop considerably reduced or eliminated may be obtained without interrupting multiple CP sources. CP coupons may also be used on buried structures with direct-connected galvanic anodes, which must not be interrupted. Using CP coupons, depolarization testing may be performed in most cases without de-energizing the CP system. An additional advantage is the ability to record accurate structure-to-electrolyte potentials on structures affected by stray currents.

1.4 When CP coupons are used, there may be differences between polarized potentials of the CP coupon and the structure. This is because the polarized structure-to-electrolyte potential measured at grade is usually the combined potential of the structure over a rather large area, including holidays in the coating and locations where the electrolyte or other conditions that affect the potential of a structure may vary. Errors caused by these variations are included in a potential measured at any given point along a structure and may be significant. These errors generally do not occur with coupons because of their small size and uniform conditions. Coupons located in areas where these variables are different can provide a good representation of the CP effectiveness on a structure.

1.5 A typical problem in measuring a structure-to-electrolyte potential is the effect of IR drops from uninterruptible current sources. By design, CP coupons may be disconnected from the structure and CP system, thereby eliminating the IR drop attributable to these current sources. Even when all current sources have been interrupted, long-line currents can still affect the structure-to-electrolyte potential readings measured at grade on a pipeline. Because the effective reference point of a CP coupon is very close to the CP coupon surface, IR drops caused by long-line currents are minimized.

Section 2: Definitions

Automated Coupon Reader: A portable electronic instrument capable of taking several types of measurements at multiple coupon test stations and storing these values to be later uploaded to a computer.

Buried Stationary Reference Electrode: A reference electrode, usually copper-copper sulfate (Cu/CuSO₄ or CSE), designed to last for many years permanently installed in a buried position.

Cathodic Protection (CP) Coupon: A coupon that is connected to the external surface of, and immersed in the electrolyte adjacent to, the structure being protected by cathodic protection.

Concentric CP Coupon and Reference Electrode: A device containing a CP coupon and a reference electrode that have the same geometric center point.

Coupon-to-Electrolyte Potential: The potential difference between the surface of a buried or submerged coupon and the electrolyte that is measured with reference to an electrode in contact with the electrolyte.