

**NEMA RN 1-2005 (R2013)**

*Polyvinyl-Chloride (PVC) Externally Coated Galvanized Rigid Steel Conduit  
and Intermediate Metal Conduit*

*Published by:*

**National Electrical Manufacturers Association**

1300 North 17th Street, Suite 900  
Rosslyn, Virginia 22209

[www.nema.org](http://www.nema.org)

© 2013 National Electrical Manufacturers Association. All rights, including translation into other languages, reserved under the Universal Copyright Convention, the Berne Convention for the Protection of Literary and Artistic Works, and the International and Pan American copyright conventions.

## NOTICE AND DISCLAIMER

The information in this publication was considered technically sound by a consensus among persons engaged in its development at the time it was approved. Consensus does not necessarily mean there was unanimous agreement among every person participating in the development process.

The National Electrical Manufacturers Association (NEMA) standards and guideline publications, of which the document herein is one, are developed through a voluntary standards development process. This process brings together volunteers and/or seeks out the views of persons who have an interest in the topic covered by this publication. Although NEMA administers the process and establishes rules to promote fairness in the development of consensus, it does not write the documents, nor does it independently test, evaluate, or verify the accuracy or completeness of any information or the soundness of any judgments contained in its standards and guideline publications.

NEMA disclaims liability for any personal injury, property, or other damages of any nature, whether special, indirect, consequential, or compensatory, directly or indirectly resulting from the publication, use of, application, or reliance on this document. NEMA disclaims and makes no guaranty or warranty, express or implied, as to the accuracy or completeness of any information published herein, and disclaims and makes no warranty that the information in this document will fulfill any particular purpose(s) or need(s). NEMA does not undertake to guarantee the performance of any individual manufacturer's or seller's products or services by virtue of this standard or guide.

In publishing and making this document available, NEMA is not undertaking to render professional or other services for or on behalf of any person or entity, nor is NEMA undertaking to perform any duty owed by any person or entity to someone else. Anyone using this document should rely on his or her own independent judgment or, as appropriate, seek the advice of a competent professional in determining the exercise of reasonable care in any given circumstance. Information and other standards on the topic covered by this publication may be available from other sources, which the user may wish to consult for additional views or information not covered by this publication.

NEMA has no power, nor does it undertake to police or enforce compliance with the contents of this document. NEMA does not certify, test, or inspect products, designs, or installations for safety or health purposes. Any certification or other statement of compliance with any health- or safety-related information in this document shall not be attributable to NEMA and is solely the responsibility of the certifier or maker of the statement.

## CONTENTS

	<b>Page</b>
	Foreword ..... ii
Section 1	GENERAL ..... 1
	1.1 Scope ..... 1
	1.2 Referenced Standards ..... 1
Section 2	RIGID CONDUIT AND IMC..... 3
	2.1 Galvanized Rigid Steel Conduit..... 3
	2.2 Intermediate Metal Conduit ..... 3
	2.3 Interior Coatings ..... 3
	2.4 Thread Protectors..... 3
Section 3	EXTERNAL COATINGS ..... 4
	3.1 Thickness ..... 4
	3.2 Coating Material ..... 4
	3.3 Application of Coating..... 4
	3.3.1 Cleaning ..... 4
	3.3.2 Priming ..... 4
	3.3.3 Coating ..... 4
	3.4 Elbows ..... 4
	3.5 Couplings..... 4
	3.6 Workmanship and Appearance..... 5
	3.7 Performance Requirements ..... 5
	3.8 Adhesion..... 5
Section 4	CORROSION RESISTANT INTERNAL COATINGS (OPTIONAL) ..... 6
	4.1 Thickness ..... 6
	4.2 Coating Material ..... 6
	4.3 Application of Coating..... 6
	4.3.1 Cleaning ..... 6
	4.3.2 Priming ..... 6
	4.3.3 Coating ..... 6
	4.4 Elbows/Bendability..... 6
	4.5 Workmanship and Appearance..... 6

## Foreword

The purpose of this Standards Publication is to describe plastic coatings which are applied to galvanized rigid steel conduit and galvanized steel intermediate metal conduit. This Standard covers the properties and dimensions of these coatings and is intended as an aid for selecting and obtaining the proper coating for added corrosion protection in various applications of these electrical raceways.

Publication No. RN 1-2005 supersedes RN 1-1998. NEMA Standards and Authorized Engineering Information, which appears in this publication unchanged from earlier editions of this standard dating back to RN 1-1980, was reaffirmed. Metric designators and dimensions have been added. Information which has been revised is followed by the appropriate classification and the revision date.

User needs have been considered in the development of this Standards Publication.

This Standards Publication is reviewed periodically by the Steel Rigid Conduit and Electrical Metallic Tubing Section of NEMA for changes which may be necessary to keep it up-to-date with advancing technology. Proposed or recommended revisions should be submitted to:

Vice President, Technical Services  
National Electrical Manufacturers Association  
1300 North 17th Street, Suite 1752  
Rosslyn, Virginia 22209

This Standards Publication was developed by the NEMA Steel Rigid Conduit and Electrical Metallic Tubing Section. Section approval of the standard does not necessarily imply that all section members voted for its approval or participated in its development. At the time it was approved, the Section was composed of the following members:

Allied Tube and Conduit Corporation—Harvey, IL  
Beck Manufacturing, Inc. – Picoma Industries—Waynesboro, PA  
Maverick Tube/Republic Conduit—Chesterfield, MO  
Robroy Industries, Inc.—Verona, PA  
Thomas & Betts Corporation—Memphis, TN  
Western Tube and Conduit Corporation—Long Beach, CA  
Wheatland Tube—Collingswood, NJ

## Section 1 GENERAL

### 1.1 SCOPE

These standards cover continuous polyvinyl chloride exterior coatings, corrosion resistant interior coatings, and the galvanized steel conduit, galvanized steel intermediate metal conduit, threaded couplings, and elbows to which they may be applied.

### 1.2 REFERENCED STANDARDS

The following publications are adopted in whole or in part, as indicated by reference in this Standards Publication.

#### **American National Standards Institute (ANSI)**

11 West 42nd Street  
New York, NY 10036

C80.1-2005 *American National Standard for Rigid Steel Conduit-Zinc Coated*

C80.6-2005 *American National Standard for Intermediate Metal Conduit*

#### **American Society for Testing and Materials (ASTM)**

100 Barr Harbor Drive  
West Conshohocken, PA 19428

D149-97a(2004) *Standard Test Methods for Dielectric Breakdown Voltage and Dielectric Strength of Solid Electrical Insulating Materials at Commercial Power Frequencies*  
This method describes a procedure for the determination of dielectric strength of solid, semi-solid, and liquid electrical insulating materials.

D638-03 *Standard Test Method for Tensile Properties of Plastics*  
This test method is used to determine the tensile strength and the percent elongation of plastic coating compounds. A Type IV specimen is tested at a crosshead speed of 2 inches (50.8 mm) per minute.

D1790-02 *Standard Test Method for Brittleness Temperature of Plastic Film by Impact*  
This method covers the determination of that temperature at which plastic film 0.25 mm (10 mils) or less in thickness exhibits a brittle failure.

D2240-04 *Standard Test Method for Rubber Property – Durometer Hardness*  
This method is used to determine the Shore A and Shore D hardness of PVC coating compounds.

G6-88(1998) *Standard Test Method for Abrasion Resistance of Pipeline Coatings*  
This method is used to determine the abrasion resistance of the applied coating material. It measures the time to loss of infinite resistance when the coating is subjected to an abrasive slurry.