



NFPA Recommended Standard
NFPA/T2.6.1 R2-2001 (R2019)
Third edition
5 March 2001

AN INDUSTRY STANDARD FOR FLUID POWER

Fluid power components – Method for verifying the fatigue and establishing the burst pressure ratings of the pressure containing envelope of a metal fluid power component

(Revision of NFPA/T2.6.1 R1-1991, R2-2001)
Reaffirmed 2019

Descriptors: fluid power components method verifying fatigue burst pressure ratings envelope metal test statistical data verification capability aluminum magnesium steel iron copper based alloys cobalt titanium stainless nickel monel

published by

NATIONAL FLUID POWER ASSOCIATION, INC.

6737 W. Washington St., Suite 2350/ Milwaukee, WI 53214 USA
PHONE: +1 414 778 3344 / FAX: +1 414 778 3361 / E-mail: nfpa@nfpa.com

Copyright 2001 by the
NATIONAL FLUID POWER ASSOCIATION
Printed in the USA

All standards, recommended practices, information reports, and bibliographies (collectively, "NFPA Documents") are advisory only. Use thereof by anyone for any purpose is entirely voluntary and in any event without risk of any nature to the National Fluid Power Association (NFPA), its officers, directors or authors of such work. There is no agreement by or between anyone to adhere to any NFPA Document. In formulating and approving NFPA Documents, NFPA and/or its councils and committees will not investigate or consider citations, references or patents which may or may not apply to such subject matter since prospective users of such NFPA Documents alone are responsible for establishing necessary safeguards in connection with utilization of such matters, including technical data, proprietary rights or patentable materials.

The information and data contained in NFPA Documents has been obtained from sources believed to be reliable. However, it should not be assumed that all acceptable or applicable sources of information, procedures, methods or techniques are contained in NFPA Documents, or that additional measures may not be required under certain circumstances or conditions.

NFPA Documents and/or policies and procedures are subject to periodic review and may be changed without notice. NFPA Documents are only current as of their publication date. NFPA Documents, after publication, may be revised or withdrawn at any time and current information on all NFPA Documents may be received by calling or writing NFPA. Additionally, the various codes and regulations referenced in NFPA Documents may be amended from time to time and it should not be assumed that the versions referenced therein are the most current versions of such codes and regulations. Please consult the appropriate regulatory authorities for the most up-to-date versions.

NFPA Documents imply a consensus of those substantially concerned with their scope and provisions and are intended as a guide to aid the manufacturer, the consumer and the general public. The publication of NFPA Documents does not in any respect preclude anyone, whether they have participated in the development of or approved such NFPA Documents or not, from manufacturing, marketing, purchasing, or using of products, processes or procedures not conforming to the NFPA Documents. NFPA Documents do not constitute or indicate a warranty of any sort, express or implied, including but not limited to a warranty or representation as to quality, merchantability or fitness for a particular use or purpose.

Participation by federal agency representative(s) or person(s) affiliated with the industry is not to be interpreted as government or industry endorsement of an NFPA Document(s).

NOTICE

NFPA Documents do not express or imply any judgment, certification or endorsement of or with respect to, the safety, design or performance of any product, component, or its use.

NFPA does not examine, investigate, test, recommend, or certify the design, use or safety of any product or component, even those which may incorporate one or more NFPA Documents. NFPA Documents therefore have no application to and do not express or imply any recommendation, representation or warranty, with respect to the safety, design, use, performance, or functional interchangeability of components or products which incorporate NFPA Documents.

This publication may not, in whole or in part, be reproduced, copied or disseminated, entered into or stored in a computer database or retrieval system, or otherwise utilized without the prior written permission of NFPA.

Foreword

This Foreword is not part of National Fluid Power Association Recommended Standard *Fluid power components – Method for verifying the fatigue and establishing the burst pressure ratings of the pressure containing envelope of a metal fluid power component*, NFPA/T2.6.1 R2-2001 (Revision of NFPA/T2.6.1 R1-1991).

NFPA/T2.6.1 was granted final approval by the NFPA Board of Directors on 18 February 1974. On 18 January 1977 the NFPA Pressure Rating Coordinating Committee voted to initiate a revision to NFPA/T2.6.1. Shortly thereafter, another NFPA project group (NFPA/T2.6.2) was organized in 1978 to evaluate fundamental aspects of fatigue testing, such as consistency among labs and whether endurance life was affected by the length of time a component is subjected to test pressure. Data from a round robin test program was analyzed by a professional statistical consultant and a conclusion was reached in February 1986 that pulse duration was a factor in fatigue life results, necessitating its control during a test.

During the period of 1984-1987, Chair Berninger developed the mathematical analysis for the basic theory and reviewed it several times with committee members, especially former Chair Skaistis who had used it intuitively in the earlier edition. This was eventually published in the proceedings of the NCFP in October 1988.

The Technical Board granted final approval to NFPA/T2.6.1 R1 on 9 May 1991.

At the 26 September 1996 meeting of T2.6 it was decided to revise the NFPA/T2.6.1 R1-1991 document. The TSP was approved at the 5 December 1996 Technical Board meeting. Draft No. 1 of the revised document was reviewed at the 11 February 1997 T2.6 meeting. It was agreed at this meeting that with a few additional changes that the document be sent out for General Review. The updated document was received at Headquarters on 4 April 1997. The document was sent out for General Review on 17 April 1997. A number of comments were received and some changes were accordingly made.

Before proceeding to ballot draft, however, a TSP to update the individual component standards to correspond with the new R2 level of NFPA/T2.6.1 had been approved by the Technical Board at its 10 April 1997 meeting. All 10 of the component standards were updated and sent to the individual component committees for their review at the September 1998 cluster meeting, along with a draft of the updated NFPA/T2.6.1 R2. At the 17 November 1998 Technical Board meeting, it was agreed to submit these drafts for general review, along with the updated NFPA/T2.6.1 R2 for a concurrent second general review.

All documents were sent out for general review on 30 December 1998. Comments were then reviewed at the 9 February 1999 meeting of T2.6 and further changes made, especially to the burst testing section. The Technical Board gave approval for a ballot draft on 8 April 1999 and headquarters prepared the ballot draft on 26 July 1999. The T2.6 committee reviewed the comments and negative ballots at the 22 September 1999 meeting. Explanations were sent to the commentators. All but three of the negative balloters changed their votes; the remaining three were reviewed by the Technical Board at its meeting of 18 November 1999 and the negatives were overridden. The standard was then approved by the Technical Board.

Project Group Members who developed this standard:

John Berninger

Project Chairman and
Technology Committee Chairman
Parker Hannifin Corp.

Paul Schacht

Technical Auditor
Bosch Automation Technology

June VanPinsker

Technical Coordinator
National Fluid Power Association

Shirley C. Seal*

Manager of Standards Development –
Industry/National
National Fluid Power Association

Jim Dietvorst

Wilkserson Corp.

Richard McAfee

Vickers, Inc.

Kendall McBroom

Nelson Ind.

John Montague

Robert Bosch Fluid Power

Mike Savage

SafeWay Hydraulics

Steve Wagner

Donaldson Co.

Jack Walrad

Vickers, Inc.

Wayne Wilcox

NAVSEA

*Retired

This is a preview of "NFPA/T2.6.1 R2-2001 ...". [Click here to purchase the full version from the ANSI store.](#)

Introduction

In fluid power systems, power is transmitted and controlled through a fluid (liquid or gas) under pressure within an enclosed circuit. During operation, components in a system may be loaded from internal pressure, gravity, inertia, thermal variations and external forces. The nature of these loads can vary from a single static application, to continuously varying amplitudes, repetitive loadings and even shock.

It is important to know how well a component can withstand these loads but this standard addresses only the loading due to internal pressure.

There are many ways in which internal pressure loads are imposed upon a component. This standard considers a broad range of waveforms but within prescribed time limits, temperatures, environmental conditions and only upon certain metals. It is anticipated that these limitations could still provide sufficient common ground for comparing products. This rating method, therefore, provides the system designer with certain information to assist in a selection of components for an application. The designer still has the responsibility to consider the other loading characteristics described above and to determine how they might affect the component's ultimate pressure retaining capability.

There are many standards already in existence for pressure rating individual components (e.g. maximum allowable operating pressure) and this standard is not intended to displace them. Instead, a method of fatigue verification is provided.

This standard serves as a universal "verification test" to give credibility to the many in-house and other methods of determining component pressure ratings. The credibility is based upon the fundamental nature of fatigue of metals with its statistical treatment, and a mathematical development of the theory is included. Nevertheless, design knowledge of the component population and its representative samples, including consistency in materials, shapes, fabrication techniques, etc. is necessary to maximize accuracy in the verification method.

This standard establishes a common set of requirements for fluid power components listed below, but does not specify the details for any particular one. Therefore, application of the verification method requires the use of NFPA standards written specifically for the particular type of component as follows:

Accumulators	NFPA/T3.4.7 R2-2000
Hydraulic valves	NFPA/T3.5.26 R2-2000
Cylinders, Tie rod or bolted	NFPA/T3.6.29 R2-2000
Cylinders, Telescopic and non-bolted	NFPA/T3.6.31 R2-2000
Pumps and motors	NFPA/T3.9.22 R2-2000
Hydraulic filters & separators	NFPA/T3.10.5.1 R2-2000
Pneumatic FRL	NFPA/T3.12.10 R2-2000
Quick-action couplings	NFPA/T3.20.8 R2-2000

Pneumatic valves

NFPA/T3.21.4 R2-2000

Pressure switches

NFPA/T3.29.2 R2-2000

This version of NFPA/T2.6.1 R2 replaces the earlier editions and utilizes the same basic theory. However, products rated under the first earlier edition NFPA/T2.6.1 may not be rated to the same values as under editions NFPA/T2.6.1 R1 or NFPA/T2.6.1 R2. See 13.1 for the differences in rating identification.

This is a preview of "NFPA/T2.6.1 R2-2001 ...". [Click here to purchase the full version from the ANSI store.](#)

Fluid power components – Method for verifying the fatigue and establishing the burst pressure ratings of the pressure containing envelope of a metal fluid power component

1 Scope

1.1 This standard provides:

- test and statistical methods for generating fatigue distribution data;
- test and statistical methods for conducting a verification of the pressure ratings on fluid power components;
- common requirements and an industry-wide philosophy in judging one type of pressure capability for fluid power components;
- uniform methods of product comparison.

1.2 This standard limits conditions as follows:

- constant amplitude, pressure induced loading of the elements that constitute or maintain the pressure containing envelope;
- product life of at least 100,000 cycles;
- defined conditions for pressure levels and pulse durations;
- temperatures from the charpy impact transition temperature to the threshold of creep sensitivity;
- environments which are chemically compatible with the materials of the pressure containing envelope;
- materials that are aluminum, magnesium, steel, iron, copper based alloys, cobalt, titanium, stainless steels, nickel steels and monel. Specifically excluded are creep sensitive materials such as: zinc, plastic, rubber and sealing devices.

1.3 This standard encourages manufacturers to use this common method to enhance the credibility of their pressure ratings.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this document. At the time of publication, the editions indicated were valid. All documents are subject to revision, and parties to agreements based on this document are encouraged to investigate the possibility of applying the most recent editions of the documents indicated below. NFPA maintains registers of currently valid NFPA standards.

NFPA/T2.12.1, *Hydraulic fluid power – Systems and products – Method of measuring average steady-state pressure.*